

TABELLA DI COMPATIBILITÀ DEI FLUIDI
Legenda

eccellente	↑
buono (OK per tenute statiche)	↗
discutibile (talvolta OK per tenute statiche)	→
scarso	↓

Guida ai materiali

NBR	Gomma Nitrilica
EPDM	Etilen-Propilene
FKM	Fluoroelastomero (Viton)
TPU	Poliuretano
HNBR	Gomma Nitr. Idrogenata
CR	Neoprene
FMQ	Fluoro-Silicone
MQ	Silicone
IIR	Butile
BR	Butadiene
IR	Isoprene
SBR	Stirene-Butadiene
FFKM	Perfluoroelastomero (Kalrez)
ACM	Poliacrilato
PTFE	Politetrafluoroetilene

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Abietate di metile	↑	↑	→	↓	↗	↓	↓	↓	↓	↓	↑	↓			
Acetaldeide	↓	↗	↓	↓	↓	→	↓	↗	↗	↗	↗	→	↑	↓	
Acetammide	↑	↑	↓	↓	↑	↑	↑	↗	↗	↓	↓	↑	↑	↓	↑
Acetanilide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di alluminio	↗	↑	↓	↓	↗	↗	↓	↓	↑	↓	↑	↗	↑	↓	
Acetato di ammonio	→	↑	→	↓	→	↗	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di benzile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di bornile	↗	↓	↑	→	↗	↓	↗	↓	↓	↓	↓	↑	↑	↓	
Acetato di calcio	↗	↑	↓	↗	↗	↗	↓	↓	↑	↓	↑	↑	↑	↓	
Acetato di cellulosa	→	↗	→	↑	→	↓	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di cobalto	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di isoamile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di isobutile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di isopropile	↓	↗	↓	↓	↓	↓	↗	↓	↗	↓	↓	↑	↑	↓	↑
Acetato di manganese	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acetato di metilamide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↗	↑	↑	↓	
Acetato di metile	↓	↗	↓	↓	↓	↗	↓	↗	↓	↗	↓	↓	↑	↑	↓
Acetato di nichel	↗	↑	↓	↓	↗	↗	↓	↓	↑	↓	↑	↑	↑	↓	↑
Acetato di ottile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acetato di piombo	↗	↑	↓	↓	↗	↗	↓	↓	↑	↓	↑	↑	↑	↑	↑
Acetato di potassio	↗	↑	↗	↗	↗	↗	↓	↓	↑	↓	↑	↑	↑	↓	↑
Acetato di propile	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↑	↑	↓	
Acetato di rame	↗	↑	↓	↓	↗	↗	↓	↓	↑	↓	↑	↑	↑	↓	
Acetato di sodio	↗	↑	↓	↓	↗	↗	↓	↓	↑	↓	↑	↑	↑	↓	
Acetato di stronzio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acetato di terpinal	↗	↓	↑	→	↗	↓	↗	↓	↓	↓	↓	↑	↑	↓	
Acetato di vinile	↗	↑	→	↗	↗	↗	↗	↗	↗	↗	↗	↗	↗	↗	↑
Acetato di zinco	↗	↑	↓	↓	↗	↗	↓	↓	↑	↓	↑	↑	↑	↓	↑
Acetato esilico	↑	↓	↑	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	↑
Acetato fenilmurcurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acetato ferrico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acetato mercurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acetato perfluorurato di potassio	↗	↑	↓	↗	↗	↗	↗	↗	↗	↗	↗	↗	↗	↗	↑
Acetilacetone	↓	↑	↓	↓	↓	↓	↓	↓	↑	↓	↓	↑	↑	↓	
Acetilene	↑	↑	↑	↓	↑	↗	↗	↗	↗	↗	↗	↗	↗	↑	↑
Acetilene monovilico	↑	↑	↑	↑	↑	↗	↗	↗	↑	↗	↗	↗	↗	↑	
Acetilene tetrabromuro	↓	↑	↑	↓	↓	↗	↗	↗	↑	↑	↑	↑	↑	↑	
Aceto	↗	↑	↗	↓	↗	↗	→	→	↗	↗	↗	↗	↗	↑	↓
Acetobutirrato di cellulosa	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acetofenetidina	↗	↓	↑	→	↗	↓	↗	↗	↓	↓	↓	↑	↑	↓	
Acetofenone	↓	↑	↓	↓	↓	↓	↓	↓	↗	↓	↓	↑	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acetone	↓	↑	↓	↓	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	↑
Acetone cianidrina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acetonitrile	→	↑	↑										↑		
Acetotoluidide	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acidi grassi	↗	→	↑	↗	↗		→	→	↓	↓	↓	↑			↑
Acidi misti	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Acidi, non organici													↑		
Acidi, organici													↑		
Acido abietico													↑		
Acido acetico al 5%	↗	↑	↑	↓	↗	↑	↗	↑	↑	↗	↗	↗	↑	↓	
Acido acetico glaciale	↗	↑	↗	↓	↗	↓	↗	↑	↗	↗	↗	↗	↑	↓	
Acido acetico, al 30%		↑											↑		
Acido acetico, caldo alta pressione	↓	→	↓	↓	↓	↓	↓	→	↓	↓	↓	↓	↑	↓	
Acido acetilsalicilico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido acetoacetico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido aconitico													↑		
Acido acrilico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido adipico	↑	↑	↑	↓	↑	↑							↑	↓	
Acido alcano-solfonico	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Acido alchilontaftalinico solfonico	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Acido alifatico dicarbossilico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido aminobenzoico													↑		
Acido aminosalicilico													↑		
Acido antranilico													↑		
Acido arachico													↑		
Acido arsenico	↑	↑	↑	→	↑	↑	↑	↑	↑	↑	↑	↑	↑	→	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acido ascorbico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido aspartico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido benzenosolfonico 10%	↓	↓	↑	↓	↓	↗	↗	↓	↓	↓	↓	↓	↑	↓	
Acido benzilico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido benzoico	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Acido benzoilesuofonico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido bisolfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido borico	↑	↑	↑	↗	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↓
Acido bromico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido bromidrico	↓	↑	↑	↓	↓	↓	→	↓	↑	↑	↑	↑	↑	↑	↑
Acido bromidrico 40%	↓	↑	↑	↓	↓	↗	→	↓	↑	↑	↑	↑	↑	↑	↓
Acido butilbenzoico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido butirrico	↗	→	↗	↓	↗	→			↗	↓	↓	↑	↓	↑	↑
Acido camforico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido caprico	↑	↓	↑	↑	↑	↗	↑	↗	↗	↓	↓	↓	↑	↑	
Acido caproico	↑	↓	↑	↑	↑	↗	↑	↗	↗	↓	↓	↓	↑	↑	
Acido carbonico	↑	↑	↑	↗	↑	↗	↑	↑	↑	↗	↑	↗	↗	↑	↓
Acido chaulmoogric														↑	
Acido cianidrico	↗	↑	↑		↗	↗	↗	→	↑	↗	↗	↗	↑	↓	↑
Acido cinnamico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido citrico	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Acido clorico	↓	↗	↗	↓	↓	↓	↑	↗	↑	↑	↑	↑	↑	↓	↑
Acido cloridrico (anidro)															↑
Acido cloridrico (caldo) 37%	↓	→	↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Acido cloridrico (freddo) 37%	↓	→	↑			↓							↑		
Acido cloridrico concentrato (a 20 °C)	↗	↗	↑		↗								↑		↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acido cloridrico concentrato (a 70 °C)	↓	↓	↑	↓	↓	↓	↓	↓	↓			↓	↑	↓	↑
Acido cloridrico, 3 moli a 70 °C	↗	↑	↑	↓	↗	↗	→	↓	↑			→	↑	→	
Acido cloroacetico	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑
Acido cloroamino benzoico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido clorosolfonico	↓	→	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	↑	↑
Acido cresilico	↓	↓	↑	↓	↓	↓		↓	↓	↓	↓	↑	↓	↓	
Acido cromico	↓	↗	↑	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	↑
Acido crotonico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	↓
Acido di tricloruro di fosforo	↓	↑	↑		↓	↓							↑		
Acido dicloroacetico	→	↓	→	→	→	↓	↗		↓	↓	↓	↓	↑	↓	↑
Acido diclorofenossiacetico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido diglicolico	→	↑	↗	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Acido eptanoico	↑	↓	↑	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	
Acido erucico													↑		
Acido etilacrilico	↓	↗		↓	↓	↗	↓	↓	↗	↓	↓	↓		↓	
Acido etilsulfurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido fenico (fenolo)	↓	↗	↑	→	↓	↓	↑	↓	↗	↓	↓	↑	↓		
Acido fenilacetico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido fenolsulfonico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido fluoridrico (anidro)													↑		↑
Acido fluoridrico (conc.) caldo	↓	↓	↓	↓	↓								↑	↓	
Acido fluoridrico (conc.) freddo	↓	↗	↗	↓	↓	↓							↑	↓	
Acido fluoroborico	↑	↑											↑		
Acido fluorofosforico													↑		
Acido fluorosulfonico													↑		
Acido fluosilicico	↗	↑	↑		↗	↗							↑		↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE	
Acido formico	↓	↗	↓	↓	↓	↓	↗							↑	↓	↑
Acido fosforico 3 molare a 70 °C	↑	↑	↑	↓	↑	↑	↗	↗	↗	↗	↑			↗	↑	→
Acido fosforico concentrato a 20 °C	↗	↑	↑	↓	↗	↗	→	→	→	↑				↑	↑	↗
Acido fosforico concentrato a 70 °C	↓	↑	↑	↓	↓	→	→	↓	↑				↗	↑	→	
Acido fosforico, 20 %														↑		
Acido fosforico, 45 %	↗	↑	↑	↓	↗	↗								↑	→	
Acido ftalico	↗	↑	↗	↓	↗	↗	↑	↗	↗	↑	↑	↑	↑	↑	↓	↑
Acido fumarico	↑	↗	↑		↑	↗	↑	↗	↗	↓	↗	↑	↗	↑	↓	
Acido furoico														↑		
Acido gallico	↑	↗	↑	↓	↑	↗	↑						↗	↑	↓	
Acido glicerofosforico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓	
Acido glicolico	↑	↑	↗	↓	↑	↗	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Acido gliossilico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓	
Acido gluconico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓	
Acido glutammico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓	
Acido idrofluorosilico	↗	↑	↑		↗	↗	↓	↑	↑				↑	↗	↑	
Acido idrossiacetico	↓	↑	↓	↓	↓	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓	
Acido iodico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓	
Acido iodidrico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↑	↓	
Acido ipocloroso	↓	↗	↑		↓	↓			↗	↓	↗	↓	↑	↑	↓	
Acido isobutirrico	↑	↗	↓		↑	↓			↗					↑		
Acido lattico Dextro	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓	
Acido lattico, caldo	↓	↓	↑		↓	↓	↗	↗	↓	↓	↓	↓	↑	↓	↑	
Acido lattico, freddo	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	↑
Acido laurico	↑	↓	↑	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	↑	
Acido linoleico	↗	↓	↗	↗	↗	↗			↗	↓	↓	↓	↑	↑		↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acido maleico	↗	↑	↑	→	↗	↗			↓	↓	↓	↓	↑	→	↑
Acido malico	↑	↗	↑	↓	↑	↗	↑	↗	↓	↗	↑	↗	↑	↑	↓
Acido mandelico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido metacrilico	↓	↗	↓	↓	↓	↗	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido metilacrilico	↓	↗	→	↓	↓	↗	↓	↗	↓	↓	↓	↑	↑	↑	↓
Acido metilsulfurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido miristico		↑	→		↓	↗			↓	↓	↓	↑	↑	↓	
Acido molibdico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido monocloroacetico	↓	↑	↓	↓	↓	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑
Acido naftalenico		↑	→		↓	↗			↓	↓	↓	↓	↑	↓	
Acido naftenico	↗	↓	↑		↗	↓	↑	↓	↓	↓	↓	↓	↑		
Acido Neville	↓	↗	↑		↓	↓	↗	↓	↗	↓	↓	↓	↑	↓	
Acido nitrico (0 - 50%)	↓	↗	↑										↑		
Acido nitrico (50-100%)	↓	↓	→										↑		
Acido nitrico 3 molare a 70 °C	↓	↗	→	↓	↓	↓	↓	↓	↗		→	↗	↓		
Acido nitrico concentrato a 20 °C		↓	↗										↑		↑
Acido nitrico concentrato a 70 °C	↓	↓	↓	↓	↓	↓	↓	↓	↓		↓	↗	↓	↑	
Acido nitrico, bianco fumante												↗		↑	
Acido nitrico, rosso fumante	↓	↓	↗		↓	↓						↑		↑	
Acido nitrobenzoico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido nitrosilsolfurico													↑		
Acido nitroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido oleico	↗	↓	↑	↗	↗	↓			↓	↓	↓	↓	↑	↓	↑
Acido orthophos													↑		
Acido ossalico	↗	↑	↑		↗	↗	↑	↗	↑	↗	↗	↗	↑		↑
Acido palmitico	↗	→	↑	↗	↗	↗	↑	↑	↓	↗	↗	↗	↑	↑	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acido para-aminobenzoico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido para-aminosalicilico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido para-nitrobenzoico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido pelagonico														↑	
Acido peracetico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑
Acido perchlorico - 2N	↓	↗	↑	↓	↓	↗	↑	↗	↗	↓	↓	↓	↑	↓	↑
Acido permanganico															↑
Acido persulfurico (acido di Caro)															↑
Acido picrico (aq)	↑	↑	↑					↑	↑	↗	↑	↗	↑	↑	↑
Acido picrico fuso	↗	↗	↑					↗	↗	↓	↗	↗	↗	↑	
Acido pirolegnoso	↓	↗	↓	↓	↓	↗	↓		↗	↓	↓	↓	↑	↓	
Acido pirosulfurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Acido piruvico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Acido propionico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Acido ricinoleico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido salicilico	↗	↑	↑	↑	↗	↑	↑		↑	↗	↑	↗	↑		↑
Acido sebacico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Acido selenico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Acido selenioso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Acido solfammico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Acido solfanilico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Acido solfonico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Acido solfonico amminobenzene															↑
Acido solfonico benzidina 3	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido solfonico cloroetano	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Acido solfonico clorotoluene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	



Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acido solfonico di piridina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido solfonico naftalene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Acido solfonico para-toluene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido solforico (20% Oleum)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido solforico concentrato a 20 °C	→	↑	→										↑		↑
Acido solforico concentrato a 70 °C	↓	↓	↑	↓		↓	↓	↓	↓			↓	↑	↓	↑
Acido solforico, 3 molare a 70 °C	↗	↑	↑	↓	↗	↗	↑	↑	↑			→	↑	↗	
Acido solforoso		↗	↑	↓				↓	↗	↗	↗	↗	↑	↓	
Acido stearico	↗	↗	↑	↑	↗	↗		↗	↗	↗	↗	↗	↑	↑	
Acido succinico	↑	↑	↑	↓	↑	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑
Acido tannico (10%)	↑	↑	↑		↑	↑	↑	↗	↑	↑	↑	↗	↑	↓	↑
Acido tartarico	↑	↗	↑	↓	↑	↗	↑	↑	↑	↗	↑	↓	↑	↓	↑
Acido tereftalico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido tetrafosforico														↑	
Acido tioacetico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido tioglicolico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido toluensolfonico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido tricloroacetico	↗	↗	↓	↓	↗	↓	↓		↗	↗	↗	↗	↑	↓	
Acido trifluoroacetico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↗	↓	
Acido tungstenico														↑	
Acido undecilenoico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido undecilici	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido urico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido valerico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acqua	↑	↑	↗	↓	↗	↗	↑	↑	↑	↑	↑	↑	↑	↓	↑
Acqua deionizzata ozonizzato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↗	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acqua deionizzata ultrapura (UPDI)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acqua DI	↗	↑	↗	↓		↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acqua di bromo	↓	↗	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Acqua di cloro	↓	↗	↑	↓	↓	↓							↑	↓	↑
Acqua di mare (salata)	↑	↑	↗	→	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓	↑
Acqua pesante	↑	↑		↓	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓	
Acqua potabile	↑	↑	↑	↓	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓	
Acque reflue	↑	↑	↑	↓	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓	
Acridina														↑	
Acrilato di butile	↓	↓	↓		↓	↓	↓	↗	↓	↓	↓	↓	↑	↓	
Acrilato di etile	↓	↗	↓	↓	↓	↓	↓	↗	↗	↓	↓	↓	↑	↓	↑
Acrilato di metile	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑
Acrilonitrile	↓	↓	↓	↓	↓	↓	↓	↓	↓	→	→	↑	↓	↑	
Acroleina	→	↑	↓	↓	→	→	↑	↗	↑	↑	↑	↑	↑	↓	
Aero Lubriplate	↑	↓	↑	↑	↑	↑	↑	↑	↗	↓	↓	↓	↗	↑	↑
Aero Shell 17 grasso	↑	↓	↑	↑	↑	↗	↑	↑	↗	↓	↓	↓	↑	↑	
Aero Shell 750	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Aero Shell 7A grasso	↗	↓	↑	↑	↗	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Aero Shell IAC	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Aerosafe 2300	↓	↑	↓	↓	↓	↓	→	→	↗	↓	↓	↓	↑	↓	
Aerosafe 2300W	↓	↑	↓	↓	↓	↓	→	→	↗	↓	↓	↓	↑	↓	
Aerozene 50 (50% Idrazina, 50% UDMH)	↓	↑	↓	↓	↓	↓	↓	↓	↑	↓	↓	↓	↗		
Alcani (idrocarburi paraffinici)	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Alcheni (idrocarburi olefinici)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Alchile acetone	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Alchile alcol	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Alchile ammina	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Alchile arile sulfoni	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Alchile arile suolfonati	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Alchile benzene	→	↓	↑	→	→	↓	↗		↓	↓	↓	↓	↑	↓	
Alcol amilico	↗	↑	↗	↓	↗	↗	↑	↓	↑	↗	↗	↗	↑	↓	↑
Alcol benzilico	↓	↗	↑	↓	↓	↗	↗	↗	↗	↓	↓	↓	↑	↓	↑
Alcol butilico	↑	↗	↑	↓	↑	↑	↑	↗	↗	↑	↑	↑	↑	↓	↑
Alcol butilico (secondario)	↗	↗	↑	↓	↗	↗	↗	↗	↗	↗	↗	↗	↑	↓	
Alcol butilico (terziario)	↗	↗	↑	↓	↗	↗	↗	↗	↗	↗	↗	↗	↑	↓	
Alcol cetilico	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Alcol cinnamico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Alcol denaturato	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓
Alcol etilico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Alcol feniletilico			↑	→		↓	↗		↓	↓	↓	↓	↑		
Alcol furfuralico	↓	↗		↓	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓	↑
Alcol idroabietilico													↑		
Alcol isobutilico	↗	↑	↗	↓	↗	↑	↗	↑	↑	↗	↑	↗	↑	↓	↑
Alcol isopropilico	↗	↑	↑	↓	↗	↗	↗	↑	↑	↗	↑	↗	↑	↓	
Alcol metilico	↗	↑	↓	↓	↗	↗	↑	↑	↑	↑	↑	↑	↑	↑	↓
Alcol oleil			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	↑
Alcol ottilico	↗	→	↑	↓	↗	↗	↗	↗	↗	↗	↗	↗	↑	↓	↑
Alcol propilico	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓
Alcol tioamilico	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑		
Alcole esilico	↑	↗	↑	↓	↑	↗	↗	↗	→	↑	↑	↑	↑	↑	↓
Aldeide caproico		↗	↓	↓			↓	↗	↗	↗	↗	↗	↑	↓	
Aldeide cinnamico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Aldeide furanica	↓	↗	↓	→	↓	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓
Aldeide tolile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Alfa picolina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Alfa terpineolo	↗	→	↑	↗	↗	↓	↑		→	↓	↓	↓	↑	↑	
Alkazene	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Allume di cromo	↑	↑	↑		↑	↑		↑	↑	↑	↑	↑	↑	↑	
Allume di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Allumi -NH3 -Cr -K	↑	↑	↓		↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	
Alluminato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Alluminio solfato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Alotano	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Ambrex 33 (Mobil)	↑	↓	↑	↗	↑	↗	→	↓	↓	↓	↓	↓	↑	↑	
Ambrex 830 (Mobil)	↑	↓	↑	↑	↑	↗	↑	↗	→	↓	↓	↓	↑	↑	
Amil mercaptano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Amil metil etere terziario (TAME)													↑		
Amilchetone di metile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Amile acetato	↓	↗	↓	↓	↓	↓	↓	→	↓	↓	↓	↑	↑	↓	↑
Amile borato	↑	↓	↑		↑	↑			↓	↓	↓	↓	↑		
Amile cinnamico aldeide	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Amile cloronaftalena	↓	↓	↑		↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Amile cloruro	↓	↓	↑		↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Amile naftalena	↓	↓	↑		↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Aminopiridina													↑		
Ammina benzilico													↑		
Ammine - misto	↓	↗	↓	↓	↓	↗	↓	↗	↗	↗	↗	↗	↗	↗	↓
Amminoantrachinone													↑		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Amminoazobenzene												↑			
Ammoniaca (anidra)	↗	↑	↓	↓	↗	↑	↓	↗	↑	↓	↓	↓	↗	↓	↑
Ammoniaca e litio, metallo in soluzione	↗	↗	↓	↓	↗		↓	↓	↗	↓	↓	↓	↓		
Ammoniaca, gas, caldo	↓	↗	↓	↓	↓	↗	↓		↗	↓	↓	↓	↗	↓	
Ammoniaca, gas, freddo	↑	↑	↓	↓	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↓
Ammoniaca, liquida (anidro)	↗	↑	↓	↓	↗	↑	↓	↗	↑	↓	↓	↗	↓	↑	↑
Ammonio cloruro di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Ammonio persolfato 10%	↓	↑		↓	↓	↑			↑		↑	↓			↓
Ammonio persolfato soluzione	↓	↑		↓	↓				↑		↑	↓	↑	↑	↓
Ammonio triellina												↑			
AN-O-3 grado M	↑	↓	↑	↑	↑	↗	↑	↗	↗	↓	↓	↓	↑	↑	
AN-O-366	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
AN-O-6	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
AN-W-O-366b Fluido idraulico	↑	↓	↑	↑	↗	↑	↗	↑	↓	↓	↓	↓	↑	↑	
ANDEROL, L - 826 (di estere)	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↑	↗		
ANDEROL, L - 829 (di estere)	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↑	↗		
ANDEROL, L-774 (di estere)	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↑	↗		
ANG-25 (estere Di Base) (TG749)	↗	↓	↑	↓	↗	↓	↗	↗	↓	↓	↓	↓	↑	↗	
ANG-25 (Estere glicerico)	↗	↑	↑	↓	↗	↗	↗	↗	↗	↗	↗	↑	↓		
Anidride acetica	↓	↗	↓	↓	↓	→	↓	↗	↗	↗	↗	↑	↓	↑	
Anidride butirrica	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Anidride carbonica (per decompressione esplosiva)	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑		
Anidride ftalica	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Anidride maleica	↓	↓	↗		↓	↓		↗	↓	↓	↓	↑	↓		
Anilina	↓	↗	→	↓	↓	↓	→	↓	↗	↓	↓	↑	↓	↑	
Anisolo	↓	↓	↓	↓	↓	↓						↑	↓	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Ansul etere 161 o 181	→	→	↓	↗	→	↓	→	↓	→	↓	↓	↓	↑	↓	
Antigelo prestone	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓
Antimonato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Antimonato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Antracene	↗	↓	↑	→	↓	↗			↓	↓	↓	↑	↓		
Antrachinone														↑	
Antrachinone disulfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Antranilato di metile						↑	→	↓	↗	↓	↓	↓	↑	↓	
Aqua Regia	↓	→	↗		→	↓							↗		↑
Argon	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Aria 0-90 °C	↗	↑	↑	↗	↗	↑	↑	↑	↑	↗	↗	↗	↑	↑	
Aria 150-200 °C	↓	↓	↑	↓	↓	↓	↗	↑	↓	↓	↓	↑	↑	↓	
Aria 200-260 °C	↓	↓	→	↓	↓	↓	↓	↗	↓	↓	↓	↓	↗	↓	↑
Aria 90-150 °C	→	↗	↑	→	→	↗	↑	↑	↗	↓	↓	↓	↑	↗	↑
Aril ortosilicato														↑	
Aroclor 1248	→	↗	↑	↓	→	↓	↗	↗	↗	↓	↓	↓	↑	↓	
Aroclor, 1254	↓	↗	↑	↓	↓	↗	→	↓	↓	↓	↑	↑	↓		
Aroclor, 1260	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Arsenato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Arsenato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Arsenato di piombo	↑	↑		↗	↑		↑	↗	↑	↑	↑	↑	↑		
Arsenato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Arsenite														↑	
Arsina														↑	
Asfalto	↗	↓	↑	↗	↗	↗	↗	↗	↗	↓	↓	↓	↑	↗	↑
ASTM olio, n. 1	↑	↓	↑	↗	↑	↗	↗	↑	↑	↓	↓	↓	↑	↑	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
ASTM olio, n. 2	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	↑
ASTM olio, n. 3	↑	↓	↑	↗	↑	↓	↑	→	↓	↓	↓	↓	↑	↑	↑
ASTM olio, n. 4	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
ASTM olio, n. 5	↑	↓	↑		↑	↗							↑		
ASTM, Riferimento combustibile A	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	↑
ASTM, Riferimento combustibile B	↑	↓	↑	→	↑	↓	↑	↓	↓	↓	↓	↓	↑	↓	↑
ASTM, Riferimento combustibile C	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
ASTM, Riferimento combustibile D	↗	↓	↑		↗	↓							↑		
ATL-857	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Atlantic Dominion F	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Atlantic Lube Utro Gear-EP	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Atlantic Utro Gear-e	↑	↓	↑		↑	↗							↑		
Aure 903R (Mobil)	↑	↓	↑	↑	↑	↗	↓	↓	↓	↓	↓	↓	↑	↑	
AUREX 256													↑		
AXAREL 9100													↑		
Azobenzene													↑		
Azoto	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Azoturo di piombo													↑		
Bardol B	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Bayol 35	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Bayol D	↑	↓	↑	↓	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Benzaldeide	↓	↗	↓	↓	↓	↓	↓	↗	↑	↓	↓	↓	↑	↓	↑
Benzaldeide acido disolfonico													↑		
Benzamide	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzantrone	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzene	↓	↓	↑	↓	↓	↓	→	↓	↓	↓	↓	↓	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Benzene di vinile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzene esaclorato															↑
Benzidina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzil butil-ftalato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Benzil fenolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzil salicilato	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzina	↑	↓	↑	↗	↑	↓	↑	↓	↓	↓	↓	↓	↑	↓	↗
Benzina (Ligroin)	↑	↓	↑	↗	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	
Benzoato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Benzoato di benzile	↓	↓	↑	↓	↓	↓	↑	↓	↗	↓	↓	↓	↑	↓	
Benzoato di butile o benzoato di n-butile	↓	↑	↑		↓	↓	↑		↑	↓	↓	↗	↑	↓	
Benzoato di calcio	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzoato di etile	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Benzoato di metile	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Benzoato di sodio	↑	↑	↑	↓	↑	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑
Benzoato di vinile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzocatecolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzochinone	↗	↑	↓						↗	↓	↓	↓	↑	↓	
Benzocloruro	↓	↑	↑		↓	↓	↑		↗	↓	↓	↓	↑	↓	
Benzofenone		↗	↑	↓			↑		↗	↓	↓	↓	↑	↓	
Benzoino	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzotricloruro	↓	↑	↑		↓	↓							↑		
Benzotrifluoruro	↓	↑	↑		↓	↓							↑		
Bicarbonato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Bicarbonato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Bicarbonato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bicarbonato di sodio	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Bicromato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bicromato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bifluoruro di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bifluoruro di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Biossido di carbonio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Biossido di cloro	↓	→	↑	↓	↓	↓	↗		→	↓	↓	↓	↑	↓	
Biossido di cloro, 8% Cl	↓	↓	↑	↓	↓	↓	↗		↓	↓	↓	↑	↓		
Biossido di manganese	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Biossido di piombo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Biossido di titanio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Biossido di zolfo (anidride solforosa), liquefatto	↓	↑	↓		↓	↓	↗	↗	↗	↓	↓	↓	↑	↓	
Biossido di zolfo (anidride solforosa), secco	↓	↑	↓		↓	↓	↗	↗	↗	↗	↗	↗	↑	↓	
Biossido di zolfo (anidride solforosa), umido	↓	↑	↓		↓	↗	↗	↗	↑	↓	↓	↑	↓		
Birra	↑	↑	↑	→	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	↑
Bisodio solfito di toluene															
Bisolfato di chinino	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bisolfato di potassio	↑	↑	↑	↓	↑	↗	↑	↗	↑	↑	↑	↑	↑	↑	
Bisolfato di sodio o bisolfito	↑	↑	↑		↑	↑	↑	↑	↗	↗	↗	↑	↓	↑	
Bisolfato stannoso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bisolfito di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bisolfito di calcio	↗	↑	↗	→	↗	↗	→	→	↑	↓	↓	↗	↑	→	↑
Bisolfito di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bisolfuro di carbonio	↓	↓	↑		↓	↓	↑	↓	↓	↓	↓	↑	→		
Bisolfuro di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Bisulfide di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bitartrato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bitartrato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Borace	↗	↑	↑	↗	↗	↗	↗	↗	↗	↗	↗	↗	↗	↗	
Borato di sodio	↗	↑	↑	↓	↗	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Bordolese	↗	↑	↑	↓	↗	↗	↗	↗	↗	↗	↗	↗	↗	↗	
Borica	→	↑	→	↓	→	↑	↗	↑	↑	↑	↑	↑	↑	↓	
Borneolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Bray GG-130	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Brayco 719-R (VV-H-910)	→	↑	↓	↓	→	↗	↗	↗	↗	↗	↗	↗	↑	↓	
Brayco 885 (MIL-L-6085A)	↗	↓	↑	↑	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Brayco 910	↗	↑	↓	→	↗	↗	↓	↑	↑	↑	↗	↑	↗	→	
Bret 710	↗	↑	↓	→	↗	↗	↓	↓	↑	↑	↑	↗	↑	→	
Brom - 113	→	↓			→	↓			↓					↓	
Brom - 114	↗	↓	↗		↗		↗		↗	↗	↗	↗	↗	↗	
Bromato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bromo	↓	↓	↗	↓	↓	↗	↓	↗	↓	↓	↓	↓	↑	↓	
Bromobenzene	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Bromobenzene cianuro	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bromoclorotrifluoretano (alotano)	↓	↓	↑	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓		
Bromoformio	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↑	↓		
Bromometano (bromuro di metile)	↗	↓	↑		↗	↓	↑		↓	↓	↓	↑	↑	→	
Bromopentane	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bromotrifluoroetilene (BFE)														↑	
Bromotrifluorometano (F-13B1)														↗	
Bromuro benzilico	↓	↓	↑	↓	↓	↑	↓	↑	↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Bromuro di acetile	↓	↑	↑	↓	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	
Bromuro di alluminio	↑	↑	↑	→	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Bromuro di ammonio	↑	↑	↑	↑	↑	↑			↑			↑	↑		
Bromuro di argento	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Bromuro di calcio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Bromuro di cobalto	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓
Bromuro di etile	↗	↓	↑	↓	↗	↓	↑		↓	↓	↓		↑		
Bromuro di idrogeno (anidro)													↑		
Bromuro di litio (salamoia)	↑	↑	↑	↓	↑	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Bromuro di metile	↓	↓	↑	↓	↓	↓	↑		↓	↓	↓	↓	↑	↓	↑
Bromuro di metilene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Bromuro di piombo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Bromuro di potassio	↑	↑	↑	↓	↑	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑
Bromuro di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Bromuro stannoso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Burro-animale grasso	↑	↗	↑	↗	↑	↗	↑	↗	↗	↓	↓	↓	↗	↑	
Butadiene (monomero)	↓	↓	↗	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	↑
Butandiolo	↗	↑	→	↓	↗	↗	↑	↗	↑	↑	↑	↑	↑	↑	↑
Butano	↑	↓	↑	↗	↑	↗	→	↓	↓	↓	↓	→	↑	↑	
Butano, 2, 2-dimetile	↑	↓	↑	↓	↑	↗	→	↓	↓	↓	↓	→	↑	↑	
Butano, 2, 3-dimetile	↑	↓	↑	↓	↑	↗	→	↓	↓	↓	↓	→	↑	↑	
Butanolo (alcol butilico)	↑	↗	↑	↓	↑	↑	↑	↗	↗	↑	↑	↑	↑	↑	↓
Butene 2-etil (2-etil 1-Butene)	↑	↓	↑	↓	↑	↓	→	↓	↓	↓	↓	↓	↑	↑	
Butil Acetil Ricinoleato	↗	↑	↑	↓	↗	↗	↗		↑	↓	↓	↓	↑		
Butil etere	↓	→	→	→	→	↓	→	↓	→	↓	↓	↓	↑	↓	
Butil mercaptano (terziario)	5	↓	↓	↓	↓	↓		↓	↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Butil mercaptano terziario	↓	↓	↑		↓									↑	
Butil perossido di-terz														↑	
Butile acetato o acetato di n-butile	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑
Butile ammina o ammina N-butile	↑	→	↓	↓	↑	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Butile benzoato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Butile benzolate														↑	
Butile carbitolo	↓	↑	→		↓	→	↓	↑	↓	↓	↓	↓	↑	↓	
Butile Cellosolve	→	↗	↓	↓	→	→	↓		↗	↓	↓	↓	↑	↓	
Butile Cellosolve acetato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Butile Cellosolve adipato	↓	↗	↗	↓	↓	↓	↗	↗	↗	↓	↓	↓	↑	↓	
Butile glicolato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Butile lattato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Butile oleato	↓	↗	↑		↓	↓	↗		↗	↓	↓	↓	↑	↑	
Butilene	↗	↓	↑	↓	↗	→	↗	↓	↓	↓	↓	↓	↑	↓	↑
Butirolacetone	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Butirraldeide	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑
Butirrato amilico	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Butirrato di butile o butirrato di n-butile	↓	↑	↑		↓	↓	↑		↑	↓	↓	↓	↑	↓	
Caffè	↑	↑	↑		↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Calce Bleach	↑	↑	↑		↑	↑								↑	
Calce caustica	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Calcine liquori	↑	↑	↑	↓	↑		↑		↑					↑	
Canfene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Canfora	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	↑
Caprolattame	↑	↓	↑	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	
Capronaldeide	↑	↓	↑	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	



Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Carbammato	→	↗	↑	↓	→	↗	↑	↗	↓	↓	↓	↑	↓	↑	↓
Carbammato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Carbazolo														↑	
Carbitol	↗	↗	↗	↓	↗	↗	↗	↗	↗	↗	↗	↗	↑	↓	
Carbonato di ammonio	→	↑	↑	↓	→	↑			↑				↑	↑	↓
Carbonato di bario	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Carbonato di bismuto	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Carbonato di calcio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Carbonato di litio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Carbonato di manganese	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Carbonato di piombo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Carbonato di potassio	↑	↑	↑	↓	↑	↗	↑	↗	↑	↑	↑	↑	↑	↑	→ ↑
Carbonato di rame	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Carbonato di sodio (Soda Ash)	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓
Carbonato di stronzio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Carbonato ferroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Carburante aromatico -50%	↗	↓	↑	→	↗	↓	↗	↓	↓	↓	↓	↓	↑	→	
Carburante tipo I - MIL-S-3136 (ASTM rif. carburante A)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Carburante tipo II - MIL-S-3136	↗	↓	↑	↗	↗	↓	↗	↓	↓	↓	↓	↓	↑	→	
Carburante tipo III - MIL-S-3136 (ASTM rif. carburante B)	↗	↓	↑	↗	↗	↓	↗	↓	↓	↓	↓	↓	↑	→	
Carburo di calcio														↑	
Caseina	↑	↗	↑	↓	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Catecolo butilico terziario o p-ter-butilcatecolo	↓	↗	↑	↓	↓	↗	↑	↗	↗	↓	↗	↑	↑	↓	
Catrame di carbone	↗	↓	↗	↓	↗									↑	
Cellosolve	↓	↗	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	↑
Cellosolve butirrato di metile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Cianuro di potassio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Cupro															
Cianuro di rame	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Cianuro di sodio	↑	↑			↑			↑	↑	↑	↑	↑			
Cianuro di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cianuro mercurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Cicloesano	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	↑
Cicloesanolo	↑	↓	↑		↑	↗	↑	↓	↓	↓	↓	↓	↑		↑
Cicloesanone	↓	↓	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑
Cicloesene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑		↓
Ciclosilammina	↓	→	↓	↓	↓	↑	↗	↓	↓	↓	↓	↑	↓	↑	
Ciclosilammina carbonato												↑			
Ciclosilammina laurato	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Ciclopentadiene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Ciclopentano	↑	↓	↑	↑	↑	→	↑	↓	↓	↓	↓	↓	↑		↗
Ciclopolieolefine	↑	↓	↑	↑	↑	→	↑	↓	↓	↓	↓	↓	↑		↗
Cimene o p-cimene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Citrato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Citrato di litio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Citrat di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Citrat di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloradio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloramina													↑		↑
Clorato di alluminio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Clorato di bario	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Clorato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Clorato di potassio	↓	↑	↑	↓	↓	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Clorato di sodio	↗	↑	↑	↑	↗	↗	↗	↑	↗	↑	↑	↑	↑	↑	↑
Clordano	↗	↓	↑			↗	→	↗	↓	↓	↓	↓	↓	↑	
Cloridrato di anilina	↗	↗	↗	↓	↗	↓	↗	→	↗	↓	↗	→	↑	↓	
Cloridrato di etilene	↓	→	↑	↓	↓	↓	→	↓	→	↓	↓	↓	↑	↓	
Clorito di sodio	↓	↑	↑	↓	↓	↓	↑	↗	↑	↑	↑	↑	↑	↓	
Cloro (bagnato)														↗	↑
Cloro (Plasma)														↗	
Cloro (secco)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	↑
Cloro 1-Nitro Etano (1-cloro-1-Nitro Etano)	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Cloro acetaldeide	↓	↑	↓	↓	↓	↓	↑	↗	↑	↑	↑	↑	↑	↗	↓
Cloro ossifluoruri														↗	
Cloro xilenoli	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cloroacetato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Cloroacetyl cloruro														↑	
Cloroacetone	↓	↑	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↗	
Cloroanilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Cloroantrachinone	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Clorobenzaldeide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Clorobenzene	↓	↓	↗	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	
Clorobenzene (Mono)	↓	↓	↑	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	
Clorobenzocloruro	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Clorobenzotrifluoruro	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Clorobromo metano	↓	↗	↑	↓	↓	↓	↗		↗	↓	↓	↓	↑	↓	
Clorobromo propano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Clorobutadiene	↓	↓	↗	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	
Clorobutano (cloruro di butile)	↑	↓	↑	↑	↑	↑	↗		↗	↓	↓	↓	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Clorocarbonato di etile	↓	↗	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Clorododecano	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Cloroestolo	↗	↓	↑	↓	↗	↗	↗	↓	↓	↓	↓	↓	↑	↗	
Cloroetano	↑	↓	↑	↑	↑	↗	↗	↑	↗	↓	↓	↓	↑	↑	
Cloroetilenbenzene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↑	↓		
Clorofenolo	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓		
Cloroformiato di etile	↓	↗	↓	↓	↓	↓	↓	↓	→	↓	↓	↓	↑	↓	
Cloroformiato di metile	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Cloroformio	↓	↓	↗	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Cloroidrine	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloroidrine di etilene	↓	↗	↓	↓	↗	↗	→	↗	↗	↗	↗	↗	↓	↑	
Cloroidrine di propilene		↑	→		↓	↗		↓	↓	↓	↓	↑	↓		
Cloroidrine solforico (Acido clorosolforico)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↓		
Clronaftalene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓		
Cloronitrobenzene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↓		
Cloropicrina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↑	↓		
Cloroprene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↑	↓		
Clorosilani												↑			
Clorosilano metilico												↑			
Clorotoluene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓		
Clorotolidine	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↑	↓		
Clorotrifluoroetilene (CTFE)												↗			
Clrox	↗	↗	↑	↓	↗	↗	↑		↗	↓	↓	↓	↑	↓	
Clroxylolo												↑			
Cloruri di cromile												↑			
Cloruro ceroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Cloruro cromico															↑
Cloruro d'argento	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di acetile	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Cloruro di alchile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di Allile	↗	↓	↑		↗	↑								↑	
Cloruro di alluminio	↑	↑	↑	→	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑
Cloruro di ammonio, 2N	↑	↑	↑	↑	↑	↑	↑				↑		↑	↑	
Cloruro di Anisolo														↑	
Cloruro di antimonio	↑	↗	↑	→	↑	↗	↑	↑	↓	↓	↓	↓	↑	↗	
Cloruro di bario	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Cloruro di benzile	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Cloruro di benzolle									↑	→	↓	↓	↓	↑	↓
Cloruro di berillio	↑	↑	↑	→	↑	→	→	→	↑	→	→	→	↑	→	
Cloruro di bornile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di butile	↑	↓	↑	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	
Cloruro di butirrato di metile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di butirile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di cadmio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di calcio	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↑	↗	↑
Cloruro di cianogeno														↑	
Cloruro di cianuro														↑	
Cloruro di clorobenzene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di cobalto	↑	↑	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Cloruro di cobalto, 2N	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Cloruro di etile	↓	↗	↗	↓	↓	↗	↑	↑	↓	↓	↗	↑	↓	→	↑
Cloruro di etilene	↓	↗	↗	↓	↓	↗	↗	↑	↓	↓	↓	↓	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Cloruro di idrogeno gas	↓	↑	↑		↓	→						↑		↑	
Cloruro di isobutile	↓	↓	↑		↓	↓						↑			
Cloruro di isocrotile			↑ →		↓	↗		↓	↓	↓	↓	↑	↓		
Cloruro di isopropile	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓	↑	
Cloruro di litio	↑	↑	↑	↓	↑	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Cloruro di magnesio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑		↑
Cloruro di manganese	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di mercurio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Cloruro di metallile			↑ →		↓	↗		↓	↓	↓	↓	↑	↓		
Cloruro di metile	↓	↓	↗	↓	↓	↓	↗	↓	→	↓	↓	↓	↑	↓	↑
Cloruro di metilene	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Cloruro di naftalene			↑ →		↓	↗		↓	↓	↓	↓	↑	↓		
Cloruro di nichel	↑	↑	↑	→	↑	↗	↑	↑	↑	↑	↑	↑	↑	→	↑
Cloruro di nitrosilici															↑
Cloruro di ottile	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Cloruro di piombo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Cloruro di pirosulfuro	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di potassio	↑	↑	↑	→	↑	↗	↑	↑	↑	↑	↑	↑	↑	→	↑
Cloruro di propilene			↑ →		↓	↗		↓	↓	↓	↓	↑	↓		
Cloruro di rame	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↑
Cloruro di sodio	↑	↑	↑	↓	↑	↑		↑	↑	↑	↑	↑	↑	↓	↑
Cloruro di stagno	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑		
Cloruro di stagno ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di stronzio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di Surfuryl	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di tiofosforile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↓

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Cloruro di tionile	↓	↗	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↓	↑	↑
Cloruro di tricloroacetile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	↓
Cloruro di vinile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	↑
Cloruro di vinilidene	↓	↓	↑	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	↓
Cloruro di zinco	↑	↑	↑		↑	↑	↑		↑	↑	↑	↑	↑	↓	
Cloruro di zolfo	↓	↓	↑	↓	↓	↓	↑	→	↓	↓	↓	↓	↑	↓	↑
Cloruro ferrico	↑	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑
Cloruro ferroso															↑
Cloruro manganoso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Cloruro mercurico	↑	↑	↑		↑	↑			↑	↑	↑	↑	↑	↑	
Cloruro stannoso (15%)	↑	↑	↑		↑	↑	↑	↗	↑	↑	↑	↑	↑		
Cobalto linoleato															↑
Cobalto naftelato															↑
Codeina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	↓
Colesterolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	↓
Colla	↑	↑	↑	↑	↑	↑	↑		↑		↑	↑	↑	↑	↑
Colofonia	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	↓
Coloranti all'anilina	↓	↗	↗	↓	↓	↗	↗	→	↗	↗	↗	↗	↑	↓	↓
Combustibile Jet A	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	↓
Convelex 10	↓			↗	↓	↓			↓	↓	↓	↓			
Coolanol 20 25R 35R 40 & 45A (Monsanto)	↑	→	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↓	↓
Creosoto, catrame di carbone	↑	↓	↑	→	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	
Creosoto, legno	↑	↓	↑	→	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	
Cresoli	↓	↓	↗		↓	↓			↓	↓	↓	↓	↑	↓	↑
Cresolo (metil fenolo)					↑										↑
Cromati di potassio	↗	↑	↑	↑	↓	↗	↗	↑	↗	↑	↑	↑	↑	↑	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Cromato di calcio	→ ↑ → ↓ → ↑ ↑ ↗ ↑ ↑ ↑ ↑ ↑ ↑ ↓														
Cromato di piombo	→ ↑ → ↓ → ↑ ↑ ↗ ↑ ↑ ↑ ↑ ↑ ↑ ↓														
Cromato di sodio	→ ↑ → ↓ → ↑ ↑ ↗ ↑ ↑ ↑ ↑ ↑ ↑ ↓														
Cromato di zinco	→ ↑ → ↓ → ↑ ↑ ↗ ↑ ↑ ↑ ↑ ↑ ↑ ↓														
Cromo solfato di potassio (allume)	↗ ↗ ↑											↑			
Crotonaldeide	↓ ↑ ↓ → ↓ ↓ ↗ ↓ ↓ ↓ ↓ ↑ ↓ ↑														
Cumaldeide	↗ ↓ ↑ → ↗ ↓ ↗ ↓ ↓ ↓ ↓ ↑ ↓														
Cumene	↓ ↓ ↑ ↓ ↓ ↓ ↗ ↓ ↓ ↓ ↓ ↑ ↓														
DDT (diclorodifenilticloroetano)	↗ ↓ ↑ → ↗ ↓ ↗ ↓ ↓ ↓ ↓ ↑ ↓														
Decalin	↓ ↓ ↑			↓ ↓ ↑ ↓ ↓ ↓ ↓ ↓ ↑											
Decano (idrocarburo)	↑ ↓ ↑ ↓ ↑ ↓ ↗ ↓ ↓ ↓ ↓ ↑ ↑														
Destrina	↑ ↑ ↑ ↓ ↑ ↑ ↗ ↓ ↓ ↓ ↓ ↑ ↓														
Destrosio	↗ ↑ ↗ → ↗ ↑ ↑ ↗ ↑ ↑ ↑ ↑ → ↑														
Dexron	↑ ↓ ↑ ↗ ↑ ↑ ↗ ↓ ↓ ↓ ↓ ↑ ↑														
Dextron	↑ ↓ ↑			↑ ↗								↑			
Diacetato Allilico	→ ↑ → ↓ → ↑ ↑ ↗ ↑ ↑ ↑ ↑ ↑ ↓														
Diachetone	↓ ↑ ↓ → ↓ ↓ ↓ ↓ ↑ ↓ ↓ ↓ ↓														
Diachetone alcol	↓ ↑ ↓ ↓ ↗ ↓ ↗ ↓ ↓ ↓ ↓ ↑ ↓														
Dialchil sulfati	→ ↑ → ↓ → ↑ ↑ ↗ ↑ ↑ ↑ ↑ ↑ ↓														
Diamilamine	↗ → ↗ ↓ ↗ → ↑ ↗ ↑ ↗ ↓ ↓ ↓ ↑ ↓														
Diazinone	→ ↓ ↗ → → ↗ ↓ ↓ ↓ ↓ ↑ ↓														
Dibenzile	↗ ↓ ↑ → ↗ ↓ ↗ ↓ ↓ ↓ ↓ ↑ ↓														
Dibenzile etere	↓ ↗ → ↗ ↓ ↓ ↗ ↓ ↓ ↓ ↓ ↑ → ↑														
Dibenzile sebacato	↓ ↗ ↗ ↗ ↓ ↓ ↗ → ↗ ↓ ↓ ↓ ↓ ↑ ↓														
Diborano												↑			
Dibromoetano	↗ ↓ ↑ → ↗ ↓ ↗ ↓ ↓ ↓ ↓ ↑ ↓														

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Dibromoetilen benzene	↓ ↓	↑ ↓	↑ ↓	↓ ↓	↓ ↓	↓ ↗	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↑ ↓		
Dibromuro di etilene	↓ ↓	↑ ↓	↑ ↓	↓ ↓	↓ ↓	↓ ↗	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↑ ↓		
Dibutil Cellosolve adipato	→ ↑	→ ↓	→ ↓	→ ↑	↑ ↑	↗ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↓		
Dibutil etere	↓ →	→ ↗	→ ↗	↓ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	↑ →		
Dibutil Metilenditio glicolato	↗ ↓	↑ →	→ ↗	↓ ↗	↗ ↗	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↑ ↓			
Dibutilammina	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	→ ↓	→ ↓	→ ↓	→ ↓	→ ↓	→ ↓	→ ↓	↑ ↓		
Dibutile sebacato	↓ ↗	↗ ↓	→ ↓	↓ ↗	↗ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	↑ ↓		
Dibutile tiourea	↗ ↓	↑ →	→ ↗	↓ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	↑ ↓		
Dicloroanilina	→ ↑	→ ↓	→ ↗	→ ↑	↑ ↑	↗ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↓		
Diclorobenzene o o-Diclorobenzene	5 ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↗	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↑ ↓	↑ ↓		
Diclorobenzene o p-Diclorobenzene	5 ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↗	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↑ ↓	↑ ↓		
Diclorobutano	↗ ↓	↑ ↓	→ ↓	↗ ↓	↗ ↗	→ ↓	→ ↓	→ ↓	→ ↓	→ ↓	→ ↓	→ ↓	↑ ↓		
Diclorobutene	↗ ↓	↑ →	→ ↗	↓ ↗	↗ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	↑ ↓		
Dicloroetano	→ ↓	↗ →	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	↑ ↓		
Dicloroetano (DDD)	↗ ↓	↑ →	→ ↗	↓ ↗	↗ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	↑ ↓		
Dicloroetilene	→ ↓	↗ ↓	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	↑ ↓		
Dicloroexilamina	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	↑ ↓		
Diclorofenolo	↗ ↓	↑ →	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	↑ ↓		
Dicloroidrina	→ ↑	→ ↓	→ ↗	→ ↑	↑ ↑	↗ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↓		
Dicloroisopropilico etere	↓ →	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	↑ →		
Diclorometano	→ ↓	↗ →	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	↑ ↓		
Dicloropropano	↗ ↓	↑ →	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	↑ ↓		
Dicloropropene	↗ ↓	↑ →	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	→ ↗	↑ ↓		
Diclorosilano													↑		
Dicloruro di etilene	↓ ↓	↑ ↓	↓ ↓	↓ ↓	↓ ↗	→ ↓	→ ↓	→ ↓	→ ↓	→ ↓	→ ↓	→ ↓	↑ ↓		
Dicloruro di metile			↑ →		↓ ↗		↓ ↗		↓ ↗		↓ ↗		↑ ↓		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Dicloruro di propilene	↓	↓			↓		↗		↓	↓	↓	↓	↑	↓	
Dicromato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Dicromato di potassio	↑	↑	↑	→	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓	↑
Dieldrin	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dietanolammina (DEA)	→	↗	→	↓	→	↓	↑	↗	↑	↑	↑	↑	↑	↓	
Dietil benzene	↓	↓	↑	↓	↓								↑	↓	
Dietil carbonato	→	→	→	↓	→	→	↑	↗	↑	↑	↑	↑	↑	↑	↓
Dietil ftalato	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dietil sebacato	↓	↗	↗	↓	↓	↗	↗	↗	↗	↓	↓	↓	↑	↓	↑
Dietilammina	↓	↗	↓	↓	→	↑	↗	↑	↑	↑	↑	↑	↑	↓	↑
Dietilanilina	→	↑	→	↓	→	→	↑	↗	↑	↑	↑	↑	↑	↓	
Dietilditiocarbammato di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Dietilentriammina	↓	↑	↓	↓	↓								↑	↓	
Difenilammina (DPA)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Difenile	↓	↓	↑	↓	↓	↗		↓	↓	↓	↓	↓	↑	↓	↑
Difenile solfonato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Difenilpropano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Difluorodibromometano	↓	↗		↓	↓			↓	↗	↓	↓	↓	↑	↓	
Difluoroetano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Difluoromonocloroetano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Difosfato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Difosfato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Difosfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Diglicole cloroformiato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Diidrogeno fosfato di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Diidroxidifenilsulfone	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Diisobutil carbinolo	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Diisobutil chetone	↓	↑	↓		↓	↓	↓						↑	↓	↑
Diisobutilene	↗	↓	↑	↓	↗	↓	→	↓	↓	↓	↓	↓	↑	↓	
Diisocianato di toluene (TDI)	↓	↗	↓		↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	
Diisoctyl sebacato	→	→	↗	↓	→	↓	→	→	↓	↓	↓	↓	↑	↓	
Diisopropil benzene	↓	↓	↑		↓	↓	↓	↗	↓	↓	↓	↓	↑	↓	
Diisopropil chetone	↓	↑	↓		↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	
Diisopropil etere (DIPE)														↑	
Diisopropilidene Acetone	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Diluente per vernici, Duco	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Dimetil acetammide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Dimetil fenil carbinolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dimetil fenil metanolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dimetil formaldeide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Dimetil idrazina asimmetrica (UDMH)	↗	↑	↓		↗	↗	↓	↑	↑	↑	↑	↑	↗	↑	
Dimetil tereftalato (DMT)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dimetilanilmina (DMA)	↓	↗	↓	→	↓	↓	↓	↗	↗	↗	↗	↗	↗	↑	↑
Dimetilanilina (xilidina)	↓	→	→	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	
Dimetildisulfide (DMD)	↑	↓	↑	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	
Dimetilformammide (DMF)	↗	↗	↓	↓	↗	↓	↓	↗	↗				↓	↑	↓
Dimetilidrazina	↗	↑	→	↓	↗	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Dimetilsolfossido (DMSO)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Dinitroclorobenzene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dinitrotoluene (DNT)	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Dioctilamine	↑	↓	↑	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	
Diossano	↓	↗	↓	↓	↓	↓	↓	↓	↓	↗	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Diossano	↓	↗	↓	↓	↓	↓	↓	↓	→	↓	↓	↓	↑	↓	
Diottol sebacato	↓	↗	↗	↗	↓	↓	→	→	↗	↓	↓	↓	↑	↓	↑
Dipentene	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↑	↓	↑	
Disilane													↑		
Disilicato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Disolfuro di carbonio	↓	↓	↑		↓	↓	↑	↓	↓	↓	↓	↓	↑	→	↑
Dodecilbenzene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dow Chemical 50-4		↑	↓			↗	↓		↗			↑	↗		
Dow Chemical ET378	↓			↗	↓	↓		↓	↓	↓	↓	↓		→	
Dow Chemical ET588	→	↑	↓		→	↗	↓		↗			↑	↗		
Dow Corning -11	↗	↑	↑	↑	↗	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Dow Corning -200	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning -220	↑	↑	↑		↑	↑							↑		
Dow Corning -3	↗	↑	↑	↑	↗	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Dow Corning -33	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning -4	↗	↑	↑	↑	↗	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Dow Corning -44	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning -5	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning -510	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning -55	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning 1208, 4050, 6620, F-60, XF-60	↑	↑	↑		↑	↑							↑		
Dow Corning F-61	↑	↑	↑		↑	↑							↑		
Dow Corning-1265 fluorosilicone fluido	↗	↑	↑	↑	↗	↑	→	↑	↑	↑	↑	↑	↑	↑	
Dow Corning-550	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning-704	↗	↑	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	
Dow Corning-705	↗	↑	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Dow Corning-710	↗	↑		↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	
Dow Guard	↑	↑	↑	→	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	→
Dowanol P Mix															↑
Dowtherm, 209	→	↑	↓		→	↗	→	→	↗						↑
Dowtherm, A	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↓	↑	↓
Dowtherm, E	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↓	↑	↓
DTE 20 serie, Mobil	↗	↓	↑	↑	↗	↑	↗	↓						↑	↗
DTE denominata serie, Mobil, leggero-pesante	↑	↓	↑	↑	↑	↗	↑	→	↓	↓			↓	↑	
Elio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Emulsione di Acetato polivinilico	↑					↗			↑			↓	↑		
Epicloridrina	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑
Eptacloro	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Eptaclorobutene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Eptaldeide (Heptanal)	↑	↓	↑	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑
Eptano o n-eptano	↑	↓	↑	↑	↗	↑	↗	→	↓	↓	↓	↓	↑	↑	↑
Esacloroacetone	→	↑	→	↓	→	↗	→	↑	↗	↑	↑	↑	↑	↑	↓
Esaclorobutadiene	↓	↓	↑	↗	↓	↓	↗		↓	↓	↓	↓	↑	↓	↑
Esaclorobutene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Esacloroetano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Esacloruro di uranio		↑												↑	
Esaetil tetrafosfato														↑	
Esafluoroetano (F-116)														↗	
Esafluoroxilene														↑	
Esafluoruro di tungsteno														↗	
Esafluoruro di zolfo	↗	↑	↗		↗	↑	↑		↑					↗	↗
Esaldeide o n-Esaldeide	↓	↑	↓	→	↓	↑	↗		↗	↓	↓	↓	↑	↑	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Esametildisilazano												↑			
Esametilen (cicloesano)	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	↑
Esametilen Adipato di diammonio	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Esametilendiammina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↗	↓	
Esametilentetrammina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↗	↓	
Esano o n-esano	↑	↓	↑	↗	↑	↗	→	↓	↓	↓	↓	↓	↑	↑	↑
Esene-1 o n-esene-1	↗	↓	↑	↗	↗	↗	↓	↓	↓	↓	↓	↓	↑	↑	↑
Esilresorcinolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Esso - Benzina Oro	↗	↓	↑	↓	↗	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Esso - Carburante 208	↑	↓	↑	↓	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Esso - fluido di trasmissione (tipo A)	↑	↓	↑	→	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Esso - Lubrificante XP90-EP	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Esso - Olio motore	↑	↓	↑	↓	↑	→	↑	↓	↓	↓	↓	↓	↑	↑	
Esso - WS2812 (MIL-L-7808A)	↑	↓	↑	↓	↑	↓	↑	↓	↓	↓	↓	↓	↑	↗	
ESSTIC 42, 43	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Estere etile acetato-organico	↓	↗	↓	↓	↓	↓	↗	↗	↓	↓	↓	↓	↑	↓	
Esteri di silicato	↗	↓	↑	↑	↗	↑	↑	↓	↓	↓	↓	↓	↑		
Etano	↑	↓	↑	↗	↑	↗	→	↓	↓	↓	↓	↓	↑	↑	
Etanolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Etanolo ammina	→	↑	↓	→	→	↗	↓	↗	↗	↗	↗	↗	↑	↓	
Etere di cellulosa	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Etere di diallile													↑		
Etere di feniletile	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	↑
Etere di isobutile	↗	↓	↓	↗	→								↑		
Etere dietilico	↓	↓	↓	↗	↓	→	→	↓	↓	↓	↓	↓	↑	→	↑
Etere dimetilico	↓	↗	↓	↗	↓	↓							↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Etere etilico	→	→	↓	↗	→	↓	→	↓	→	↓	↓	↓	↑	↓	
Etere isopropilico	↓		↓	↓	↓	→	↓	↓	↓	↓	↓	↓	↑	↓	↑
Etere para-bromofenilbenzilico															↑
Eteri	↓	→	↓	↗	↓	↓	→	↓	↓	↓	↓	↓	↑	→	
Etil etere butilico terziario															↑
Etil mercaptano	↓		↗		↓	→	→	↓	↓	↓	↓	↓	↑		
Etilammina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Etilato di alluminio															↑
Etilbenzene	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	↑
Etilcellulosa	↗	↗	↓	↓	↗	↗	↓	↗	↗	↗	↗	↗	↗	↑	
Etilciclopentane	↑	↓	↑	↑	↑	→	↑	↓	↓	↓	↓	↓	↑	↗	
Etile Acetato	↓	↗	↓	↓	↓	↓	↓	↗	↗	↗	↗	↗	↑	↓	↑
Etile Cellosolve	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	
Etile cloruro di ammonio															↑
Etile esanolo	↑	↑	↑	↓	↑	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Etile nitrito	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Etile pentaclorobenzene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Etile piridina	↗	↑	↓	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	
Etile Valerate	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Etilene	↗	↓	↑	↗	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Etilene cianidrina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Etilene diammina	↓	↑	↓	↓	↓	↓	↑	↑	↗	↑	↗	↗	↗	↓	↑
Etileneimine															↑
Eilmorfolen stannoso octotate (miscela 50/50)	↓	↗	↓						↗					↓	↑
Eilmorfolina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Etossietile acetato (EGMEEA)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
F-60 fluido (Dow Corning)	↑	↑	↑	↑	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	
F-61 fluido (Dow Corning)	↑	↑	↑	↑	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	
FC-43 eptacosofluorotributilammina	↑	↑	↑		↑	↑	↑	↑	↑			↓	↑		
FC75 & FC77 (fluorocarbone)	↑	↑	↗		↑	↑	↗	↑	↑			↓	↑		
Fenil acetato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fenil acetato di metile			↑	→		↓	↗		↓	↓	↓	↑	↓		
Fenilacetammide			↑	→		↓	↗		↓	↓	↓	↑	↓		
Fenilbenzene	↓	↓	↗	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑	
Fenilene diammina												↑			
Feniletille malonico estere *			↑	→		↓	↗		↓	↓	↓	↑	↓		
Fenilglicerina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fenilidrazina	↓	↓	↗	↓	↓	↓			↓	↗	↑	↗	↑	↓	
Fenilidrazina cloridrato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fenolato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fenolo	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓	→	
Fenolo di amile												↑			
Fenolo, 70% / 30% H ₂ O	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓		
Fenolo, 85% / 15% H ₂ O	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓		
Fenolsolfonato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fenolsulfonato di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fenossido di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ferricianuro di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ferricianuro di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ferro ammonio citrato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ferrocianuro di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ferrocianuro ferrico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Fluidi di boro (HEF)	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Fluidi di lavaggio a secco	→	↓	↑	↓	→	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Fluido di trasmissione automatica (ATF)	↑	↓	↑	↗	↑	↗		↓	↓	↓	↓	↓	↑	↓	↑
Fluido esam-6	↑	↓				↗	↓		↗			↑	↑		
Fluido Freno DOT3 (tipo glicole)	→	↑	↓	↓	→	↗	↓	→	↗		↑	↑	↑		
Fluido per trasmissione tipo A	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	↑	
Fluoro (gas)															↗
Fluoro (liquido)	↓	↓	↗											↗	↑
Fluoro ceroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fluorobenzene	↓	↓	↗		↓	↓	↗		↓	↓	↓	↑	↓	↑	
Fluorolube	↑	↑	↗		↑	↑	↗	↑	↑			↓	↑		
Fluorosilicato di alluminio															↑
Fluorurati eteri ciclici	↑														↑
Fluoruri cromico															↑
Fluoruri di carbonio	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Fluoruro acido di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fluoruro di alluminio	↑	↑	↑	→	↑	↑	↑	↗	↑	↑	↑	↑	↑		
Fluoruro di ammonio	↑	↑	↗	→	↑	↗					↑		↑	↑	↓
Fluoruro di berillio	↑	↑	↑	→	↑	→	→	→	→	↑	→	→	↑	→	
Fluoruro di calcio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Fluoruro di idrogeno	↓	↗		↓	↓										↑
Fluoruro di idrogeno (anidro)	↓	↑	↓		↓				↑	↓	↓	↑	↓		
Fluoruro di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fluoruro di silicio															↑
Fluoruro di sodio	↑	↑	↑	↗	↑				↑	↗	↑	↑	↑	↑	↓
Fluoruro di vinile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Fluoruro stannoso	→ ↑	↑	→ ↓	→	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Fluorursilicone di zinco												↑			
Fluosilicato di ammonio												↑			
Fluosilicato di sodio	→ ↑	→ ↓	→	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓
Fluosilicato di zinco												↑			
Formaldeide	→ ↑	↓	↓	→	↓	↓	↗	↗	↗	↗	↗	→	↑	↓	↑
Formammide	↗	↗	↗	↓	↗	↓	↑	↗	↑	↑	↑	↑	↑	↓	↑
Formiato di alluminio	→ ↑	→ ↓	→	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓
Formiato di ammonio	→ ↑	→ ↓	→	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓
Formiato di bornile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	↑
Formiato di etile	↓	↗	↑		↓	↗	↑		↗	↓	↓	↓	↑		
Formiato di metile	↓	↗	↓		↓	↓			↗	↓	↓	↓	↑		
Forone	↓	→	↓	↓	↓	↓	↓	↓	→	↓	↓	↓	↑	↓	↓
Fosfato acido	→ ↑	→ ↓	→	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓
Fosfato cromica												↑			
Fosfato di alluminio	↑	↑	↑	↓	↑	↑	↗					↑	↑		
Fosfato di ammonio	↑	↑	↓		↑		↑	↑		↑	↑	↑			
Fosfato di ammonio bilbasico	↑	↑			↑	↑		↑	↑		↑	↑			
Fosfato di ammonio, monobasico	↑	↑			↑	↑		↑	↑		↑	↑			
Fosfato di ammonio, tribasico	↑	↑			↑	↑		↑	↑		↑	↑			
Fosfato di boro												↑			
Fosfato di calcio	↑	↑	↑	↑	↑	↗		↑	↑	↑	↑	↑	↑	↑	↑
Fosfato di isobutile	→ ↑	→ ↓	→	↑	↑	↗	↑	↗	↑	↑	↑	↑	↑	↑	↓
Fosfato di manganese	→ ↑	→ ↓	→	↑	↑	↗	↑	↗	↑	↑	↑	↑	↑	↗	
Fosfato di potassio (acido)	→ ↑	↑	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓
Fosfato di potassio (alcalino)	→ ↑	→ ↓	→	↑	↑	↗	↑	↗	↑	↑	↑	↑	↑	↑	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Fosfato di potassio (di/tri basico)	→ ↑	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Fosfato di sodio (bibasico)	↑	↑	↑	↑	↑	↑	↗		↓	↑	↑	↑	↑	↑	↑
Fosfato di sodio (Mono)	↑	↑	↑	↑	↑	↑	↑	↗		↓	↑	↑	↑	↑	↑
Fosfato di sodio (tribasico)	↑	↑	↑	↑	↑	↑	↑	↗		↑	↑	↑	↑	↑	↑
Fosfato di zinco	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓
Fosfato tripotassico	→ ↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑
Fosfato trisodico	→ ↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑
Fosfina	↓	↑	↗	↓	↓	↗							↑	↓	
Fosfito di ammonio	→ ↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓
Fosforo (fuso)													↑		
Fosgene													↑	↑	↑
Freon, 11	↑	↓	↗	↓	↑	↓	↗	↓	↓	↓	↓	↓	↗	↓	↑
Freon, 112 (tetrachlorodifluoretano)	↗	↓	↗	↗	↗	↗	↗	↓	↓				↓	↑	
Freon, 113	↑	↓	↗	↗	↑	↑	↓	↓		↗	→				↑
Freon, 113 olio di alta e bassa anilina	↑												→		
Freon, 114	↑	↑	↗	↑	↑	↑	↓	↑		↑	↗				↑
Freon, 114B2	↗	↓	↗	↗	↗	↗	↗	↓	↓		↗				↗
Freon, 115, 116	↑	↑	↗	↗	↑	↑	↑			↑		↑			↗
Freon, 12	↗	↗	↗	↗	↗	↑	↑	→	↓	→	↓	↓	↗		↑
Freon, 12 e ASTM olio # 2 (miscele 50/50)	↗	↓	↑	↗	→	↗	↓	↓	↓	↓	↓	↓	↑		
Freon, 12 e Suniso 4 G (miscele 50/50)	↗	↓	↑	↗	→	↗	↓	↓	↓	↓	↓	↓	↑		
Freon, 123 (diclorotrifluoretano)														↓	
Freon, 124 (clorotetrafluoroetano)													↗		
Freon, 125 (pentafluoroetano)													↗		
Freon, 13	↑	↑	↗	↗	↑	↑	↑	↓	↓	↑	↑	↑	↑	↑	↑
Freon, 131b (dichlorofluoroetane)													↑		



Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Freon, 134a (tetrafluoroetano)	↑			↑								→		↑	
Freon, 13B1	↑	↑	↗	↗	↑	↑	↗	↓	↑			↑	↗		
Freon, 14	↑	↑	↗	↑	↑	↑		↓	↑			↑	↑		
Freon, 142b	↑	↑	↓		↑	↑						→			
Freon, 152a (difluoroetano)	↑	↑	↓		↑	↑						→			
Freon, 21	↓	↓	↓	↗	↓	↗		↓	↓	↓	↓	↓	↑	↓	
Freon, 218	↑	↑	↑		↑	↑							↑		
Freon, 22 (clorodifluoroetane)	↓	↑	↓	↓	↓	↑	↓	↓	→			↑	↑	↗	↑
Freon, 22 e ASTM olio # 2 (miscela 50/50)	↓	↓	↗		↓	↗	↗	↓	↓			↓	↑	↗	
Freon, 23 (trifluorometano)														↑	
Freon, 31	↓	↑	↓	↗	↓	↑		↑				↗	↗		
Freon, 32	↑	↑	↓	↗	↑	↑		↑				↑	↗		
Freon, 502	↗	↑	↗		↗	↑		↑				↑	↗		
Freon, BF (R112)	↗	↓	↑	↓	↗	↗		↓	↓			↓	↗		
Freon, C316	↑	↑			↑	↑							↗		
Freon, C318	↑	↑	↗		↑	↑		↑				↑	↗		
Freon, K-142b	↑	↑	↓		↑	↑		↑				↑	↓		
Freon, K-152a	↑	↑	↓		↑	↑		↑				↑	↓		
Freon, MF (R11)	↗	↓	↗	↗	↗	↓		↓	↓			↓	↗		
Freon, PCA (R113)	↑	↓	↗	↑	↑	↑		↓	↓			↗	↑		
Freon, T-P35	↑	↑	↑	↑	↑	↑							↗		
Freon, T-WD602	↗	↗	↑										↗		
Freon, TA	↑	↑	↓	↑	↑	↑							↗		
Freon, TC	↑	↗	↑	↑	↑	↑							↗		
Freon, TF (R113)	↑	↓	↑	↑	↑	↑		↓	↓			↗	↗		
Freon, TMC	↗	↗	↑	↗		↗							↗		



Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Germano (germanio tetraidride)														↑	
Gliceril fosfato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Glicerina (glicerolo)	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	↑
Glicerolo dchloroidrina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Glicerolo monoclchloroidrina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Glicerolo triacetato	↗	↑	↓	↓	↗	↗	↑	↗	↑	↑	↑	↑	↑	↓	
Glicidolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Glicole dietilenico	↑	↑	↑	↓	↑	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Glicole esilenico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Glicole etilenico	↑	↑	↑	↗	↑	↗	↑	↑	↑	↑	↑	↑	↑	↗	↑
Glicole monoetere															↑
Glicole propilenico	↑	↑	↑	↓	↑	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Glicole trietilenico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Glicoli	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Glucocianate di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Gluconato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Glucosio	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑		↑
Glutammato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Grassi al silicone	↑	↑	↑	↑	↑	↑	↗	→	↑	↑	↑	↑	↑	↑	↑
Grassi animali	↑	↗	↑	↑	↑	↗								↑	↑
Grasso al bisolfuro di molibdeno	↑	↓	↑			↓								↑	
Grasso Gulfcrown	↑	↓	↑	↑	↑	↗	↑	↑	↓	↓	↓	↓	↓	↑	↑
Grasso leggero	↑	↓	↑		↑	↓								↑	
Grasso multiuso Sunoco	↑	↓	↑	↑	↑	↗	↑	↑	↓	↓	↓	↓	↓	↑	↑
Gulf - oli di sicurezza	↑	↓	↑	↗	↑	↗	↑	↑	↓	↓	↓	↓	↓	↑	↑
Gulf - oli Legion	↑	↓	↑	↑	↑	↗	↑	↑	↓	↓	↓	↓	↓	↑	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Idrazide maleica	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Idrazina	↗	↑	→	↓	↗	↗	↓	↗	↑			↗	↑	→	
Idrazina (anidro)	↓	↗	↓	↓	↓	↗	↓	↗	↓	↓	↑	↑	↑	↓	
Idrazina dicloridrato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Idrazina idrato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑
Idrocarburi saturi	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↑	↑	↑	
Idrochinolo	↓	↓	↑		↓	↓						↗			
Idrochinone	↓	↗	↓		↓	↓	↗		↓	↓	↗	↓	↑	↗	↑
Idrogeno sulfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Idroperossido di cumene													↑		
Idrosolfito di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Idrosolfuro di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Idrosolfuro di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Idrossido cromico													↑		
Idrossido di alluminio	↗	↑	↗					↗							↑
Idrossido di ammonio, 3 molare	↑	↑	→	↓	↑	↑	↑	↑	↑	↗	↗	↗	↗	↓	
Idrossido di ammonio, concentrato	↓	↑	↓	↓	↓	↑	↑	↑	↑	→	→	→	↗	↓	
Idrossido di bario	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Idrossido di calcio	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Idrossido di litio	↓	↑	→	↓	↓	↓	↑	↗	↑	↑	↑	↑	↑	↑	↓
Idrossido di magnesio	↗	↑	↑	↓	↗	↗			↑	↗	↗	↗	↑	↓	
Idrossido di potassio 50%	↗	↑	→	↓	↗	↗	→	→	↑	↗	↗	↗	↑	↓	
Idrossido di sodio, 3 molare	↗	↑	↗	↗	↗	↗	↗	↗	↑	↑	↑	↗	↑	↑	↓
Idrossido di stronzio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Idrossido ferrico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Idrosulfito di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Idroxicitronella															
Idruro di boro															↑
Idruro di calcio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Idruro di sodio															↑
Immina di propilene		↑	→				↓	↗		↓	↓	↓	↓	↑	↓
Indolo			↑	→			↓	↗		↓	↓	↓	↓	↑	↓
Industron FF44	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Industron FF48	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Industron FF53	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Industron FF80	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Insulina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Iodato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Iodio	↗	↗	↑			↗	↓	↑		↗	↓	↗	↑	↑	
Iodoformio		↑	↑				↗	↓	↓	↓	↓	↑	↑	↑	
Ioduro d'ammonio	↑	↑	↑	↑	↑	↑	↑						↑	↑	
Ioduro di bario	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Ioduro di idrogeno (anidro)															↑
Ioduro di metile	↑	↓	↑	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑
Ioduro di metilene			↑	→			↓	↗		↓	↓	↓	↑	↑	↓
Ioduro di potassio	↑	↑	↑	↓	↑	↗	↑	↗	↑	↑	↑	↑	↑	↑	↑
Ioduro di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Ioduro ferroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Ioduro mercurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Ipoclorito di calcio	↗	↑	↑	↓	↗	↗	↗	↗	↑	↗	↗	↗	↗	↗	↓
Ipoclorito di litio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Ipoclorito di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Ipoclorito di sodio	↗	↑	↑	↓	↗	↗	↗	↗	↑	↗	↗	↗	↑	↓	↑
Ipofosfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Ipofosfato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Ipofosfato di manganese	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Ipofosfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Iposolfito di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Isoamilico butirrato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Isoamilico Valerate	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Isoboreolo			↑	→		↓	↗		↓	↓	↓	↓	↑	↑	↓
Isobutano	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	↑
Isobutile n-butirrato	↓	↑	↑		↓	↓	↑		↑	↓	↓	↓	↑	↓	
Isobutilene	↑	↓	↑	↓	↑	↓	↗		↓	↓	↓	↓	↑	↓	
Isobutirraldeide	↓	↑	↓	↓	↓	↓							↗	↓	
Isocianato di metile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Isodecanolo	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Isododecano	↑	↓	↑	↓	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	↓
Isoeugenolo	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Isoforone (chitone)	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑
Isoottano	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	↑
Isopentano	↑	↓	↑	↗	↑	↓	↑	↗	↓	↓	↓	↓	↑	↑	
Isopropanolo	↗	↑	↑	↓	↗	↗	↗	↑	↑	↗	↑	↗	↑	↓	↑
Isopropilacetone	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Isopropilammina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
JP-10	→	↓	↑	→	→	↓	↑	↓	↓				↓	↑	↓
JP-3 (MIL-J-5624)	↑	↓	↑		↑	↓							↑		↑
JP-4 (MIL-T-5624)	↑	↓	↑	↗	↑	↓	↗	↓	↓	↓	↓	↓	↑	↗	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
JP-5 (MIL-T-5624)	↑	↓	↑	↗	↑	↓	↗	↓	↓	↓	↓	↓	↓	↑	↗
JP-6 (MIL-J-25656)	↑	↓	↑	↗	↑	↓	↗	↓	↓	↓	↓	↓	↓	↑	↗
JP-8 (MIL-T-83133)	↑	↓	↑	↑	↑	→	↗	↓	↓					↑	↑
JP-9 (MIL-F-81912)	→	↓	↑	→	→	↓	↗	↓	↓					↓	↑
JP-9-11	↓	↓	↑	↓	↓	↓	↗	↓	↓					↓	↑
JPX (MIL-F-25604)	↑	↓	↓		↑	↗									↑
Keystone # 87HX (grasso)	↑	↓	↑		↑	↑	↑	↑	↓	↓	↓	↓	↓	↑	↑
Lacca solventi	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓
Lacche	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓
Lardo grasso animale	↑	↗	↑	↑	↑	↗	↑	↗	↗	↓	↓	↓	↑	↑	↑
Lattami-aminoacidi	↓	↗	↓		↓	↗	↓		↗	↓	↓	↓	↑	↑	
Lattato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑
Lattato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑
Lattato di etile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑
Lattato di metile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑
Lattato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑
Latte	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Lattoni (esteri ciclici)	↓	↗	↓	↓	↓	↓	↓	↗	↗	↓	↓	↓	↑	↑	↓
Laurato di amile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↑	↓
Laurato di butile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
LB 135	↑	↑	↑		↑	↑									↑
Lehigh X1169	↑	↓	↑		↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑
Lehigh X1170	↑	↓	↑		↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑
Ligroin (etere di petrolio o benzene)	↑	↓	↑	↗	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	↑
Lindol, fluido idraulico (tipo estere di fosfato)	↓	↑	↗	↓	↓	↓	→	→	↑	↓	↓	↓	↑	↑	↓
Linoleato di alluminio	↑	↓	↑	↗	↑	↑	↗	↑	↗	↑	↑	↑	↑	↑	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Linoleato di manganese	→ ↑ → ↓ → ↑ ↑ → ↑ ↑ → ↑ ↑ ↑ ↑ ↑ ↑ ↓														
Linoleato di piombo	→ ↑ → ↓ → ↑ ↑ → ↑ ↑ → ↑ ↑ ↑ ↑ ↑ ↓														
Liquidi di zucchero di barbabietola	↑ ↑ ↑			↑ ↑								↑			
Liquidi Kel F	↑ ↑ ↗			↑ ↗ ↑ ↑							↑ ↑				
Liquido freni auto	→ ↑ ↓ ↓ → ↗ ↓ → ↗										↑ ↑ ↓ ↑				
Liquido freni Delco	→ ↑ ↓			→ ↗ ↓ → ↗							↑ ↑				
Liquido freni Girling	→ ↑ ↓			→ ↗ ↓			↗				↑ ↑				
Liquido freni Mopar	→ ↑ ↓			→ ↗ ↓ → ↗							↑ ↑				
Liquimoly	↑ ↓ ↑ ↗			↑ ↗ ↑ ↓ ↓							↓ ↓ ↓ ↑ ↑ ↑				
Liquore bianco	↑ ↑ ↑			↑ ↑							↑	↑			
Liquore di Bleach	→ ↑ ↑ ↓			→ ↗ ↗ ↗			↑ ↗ ↗ ↗		→ ↗		↑ ↓				
Liquore di solfato verde	↗ ↑ ↑ ↓			↗ ↗ ↗			↑ ↗ ↗ ↗				↑ ↑ ↓				
Liquore nero	↗ ↗ ↗ ↓										→ ↓ ↑				
Liquori di caliche	↑ ↑ ↑ ↑			↑ ↑ ↑ ↗			↑ ↑ ↑ ↗				↑ ↑ ↑ ↑				
Liquori di solfito	→ ↑ → ↓			→ ↑ ↑ ↗			↑ ↑ ↑ ↗				↑ ↑ ↑ ↓				
Liquori di zolfo	↗ ↗ ↑			↗ ↗ ↗ ↓			↗ ↗ ↗ ↗				↑ ↑ ↓				
Liquori di zucchero di barbabietola	↑ ↑ ↑ ↓			↑ ↗ ↑ ↑			↑ ↑ ↑ ↓				↑ ↑ ↑ ↓				
Liquori di zucchero di canna	↑ ↑ ↑ ↓			↑ ↑ ↑ ↑			↑ ↑ ↑ ↑				↑ ↑ ↑ ↓				
Litopone	→ ↑ → ↓			→ ↑ ↑ ↗			↑ ↑ ↗				↑ ↑ ↑ ↓				
Lube Sinclair opalino CX-EP	↑ ↓ ↑ ↑			↑ ↗ ↑ ↓			↓ ↓ ↓ ↓				↑ ↑ ↑ ↑				
Lubrificante alta viscosità H2	↑ ↑ ↑ ↓			↑ ↗ ↗ ↑			↑ ↗				↑ ↑ ↑ ↓				
Lubrificante alta viscosità U4	↑ ↑ ↑ ↓			↑ ↗ ↗ ↑			↑ ↗				↑ ↑ ↑ ↓				
Lubrificante di-estere MIL-L-7808	↗ ↓ ↑ ↓			↗ ↓ ↗ ↓			↓ ↓ ↓ ↓				↑ ↑ ↗				
Lubrificante EP 28 ELCO	↑ ↓ ↑ ↑			↑ → ↑ ↗			↓ ↓ ↓ ↓				↑ ↑ ↑ ↑				
Lubrificanti di-estere sintetici	↗ ↓ ↑ ↓			↗ ↓ ↗ ↑			↓ ↓ ↓ ↓				↑ ↑ ↑ ↑				
Malatione	↗ ↓ ↑			↗ ↗ ↓			↓ ↓ ↓ ↓				↑ ↑ ↑ ↑				

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Manganese gluconato	→ ↑		→ ↓	→ ↑											
Manganese naftenato															↑
Mannitolo	→ ↑	→ ↓	→ ↑	↑ ↑	↗ ↑										
MCS 312	↓ ↓	↑		↓ ↓	↑ ↑	↓ ↓									
MCS 352	↓ ↑	↓ ↓	↓ ↓	↓ ↓	→ →	↗ ↓	↓ ↓								
MCS 463	↓ ↑	↓ ↓	↓ ↓	↓ ↓	→ →	↗ ↓	↓ ↓								
MDI (metilene isocianato di p-fenilene)	→ ↑	→ ↓	→ ↑	↑ ↑	↗ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Mercaptano	↓ ↑	↓ ↓	↓ ↓	↓ ↓	↑ ↑	↗ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Mercaptano metilico	↑										↑				↑
Mercaptobenzotiazolo (MBT)		↑ →		↓ ↗			↓ ↓	↓ ↓	↓ ↓	↓ ↓	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Mercurio	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑						↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Meta-cresolo		↑ →		↓ ↗			↓ ↓	↓ ↓	↓ ↓	↓ ↓	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Meta-nitroanilina	→ ↑	→ ↓	→ ↑	↑ ↑	↗ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Meta-toluidina		↑ →		↓ ↗			↓ ↓	↓ ↓	↓ ↓	↓ ↓	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Metabisolfito di potassio	→ ↑	→ ↓	→ ↑	↑ ↑	↗ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Metachromate di potassio	→ ↑	→ ↓	→ ↑	↑ ↑	↗ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Metacrilato di butile	→ ↑	→ ↓	→ ↑	↑ ↑	↗ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Metacrilato di metile	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Metafosfato di ammonio	→ ↑	→ ↓	→ ↑	↑ ↑	↗ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Metafosfato di sodio	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↗ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Metaldeide	→ ↑	→ ↓	→ ↑	↑ ↑	↗ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Metano	↑ ↓	↑ ↓	↑ ↓	↑ ↑	↗ ↑	→ ↓	↓ ↓	↓ ↓	↓ ↓	↓ ↓	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Metanolo	↗ ↑	↓ ↓	↗ ↑	↗ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Metasilicato di potassio															↑
Metasilicato di sodio	→ ↑	→ ↓	→ ↑	↑ ↑	↗ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑
Metyl acetofenone *			↑ →		↓ ↗		↓ ↓	↓ ↓	↓ ↓	↓ ↓	↑ ↑	↑ ↑	↑ ↑	↑ ↑	↑ ↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Metil butil chetone	↓	↑	↓	↓	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	
Metil butil etere terziario (MTBE)	→	→	→	→	→	→							↑		
Metil carbonato	↓	↓	↓	↓	↓	↗	↓	↓	↓	↓	↓	↓	↑	↓	
Metil Cellosolve	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	
Metil cellulosa	↗	↗	↗	↗	↗	↗	↓	↗	↗	↗	↗	↗	↑	↓	
Metil cloroformio	↓	↓	↑		↓	↓							↑		
Metil etere	↑	↓	↑		↑	→	↑	↑	↓	↑	↑	↓	↑	↓	
Metil etil chetone (MEK)	↓	↗	↓	↓	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	↑
Metil etil chetone perossido	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Metil isobutil chetone	↓	↑	↓	↓	↓	↓	↑	↗	↑	↑	↑	↑	↑	↓	
Metil isobutil chetone (MIBK)	↓	→	↓	↓	↓	↓	↓	↓	→	↓	↓	↓	↑	↓	
Metil isopropil chetone	↓	↗	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↑	↓	
Metil Isovalerate			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Metil-2-pirrolidone o n-metil-2-pirrolidone		↗											↑		
Metilal													↑		
Metilammina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Metilito di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Metilchetone esilico (2-ottanone)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Metilciclopentano	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Metile acetoacetato	↓	↗	↓	↓	↓	→	↓	↗	↗				↑	↓	
Metile cicloesanone	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Metile cloroacetato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Metile etile oleato			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Metile oleato	↓	↗	↑		↓	↗		↗	↓	↓	↓	↑	↑	↑	
Metile Pentadiene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Metilglicerolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Metilisobutil carbinolo	↑	↓	↑	↑	↑	↗	↑	↗	↗	↓	↓	↓	↑	↑	
Metilpirrolidina			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Metilpirrolidone			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Metossietanolo (DGMMA)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Metoxiclor														↑	
MIL-A-6091	↗	↑	↑	↓	↗	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓
MIL-C-4339	↑	↓	↑	↑	↑	↓	↑	→	↓	↓	↓	↑	↑	↑	
MIL-C-7024	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-C-8188	↗	↓	↗	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	→	
MIL-E-9500	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
MIL-F-16884	↑	↓	↑	→	↑	→	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-F-17111	↑	↓	↑	→	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-F-25558 (RJ-1)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-F-25656	↑	↓	↑	↗	↑	↓	↗	↓	↓	↓	↓	↓	↑	↗	
MIL-F-5566	↗	↑	↑	↗	↗	↗	↑	↑	↑	↑	↗	↑	↗	↑	↓
MIL-F-81912 (JP-9)	→	↓	↑	→	→	↓	↗	↓	↓				↓	↑	↓
MIL-F-82522 (RJ-4)	↗	↓	↑	↑	↗	↓	↑	↓	↑	↑	↑	↑	↑	↑	
MIL-G-10924	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-G-15793	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-G-21568	↑	↑	↑	↑	↑	↑	↑	↑	↓	↑	↑	↑	↑	↑	
MIL-G-25013	↑	↑	↑	→	↑	↗	↑	↓	↑	↓	↓	↑	↑	↑	
MIL-G-25537	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-G-25760	↗	↓	↑	↗	↗	↗	↗	↓	↓	↓	↓	↓	↑	↗	
MIL-G-3278	↗	↓	↑	↗	↗	↓	↗	↓	↓	↓	↓	↓	↑	↑	
MIL-G-3545	↑	↓	↑	↑	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	
MIL-G-4343	↗	→	↑	↑	↗	↗	↑	→	→	↑	↑	↑	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
MIL-G-5572	↑	↓	↑	↗	↑	↓	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-G-7118	↗	↓	↑	→	↗	↗	↑	↓	↓	↓	↓	↓	↑	→	
MIL-G-7187	↑	↓	↑	↑	↑	↓	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-G-7421	↗	↓	↑	↗	↗	↗	↗	↗	↓	↓	↓	↓	↑	↓	
MIL-G-7711	↑	↓	↑	↑	↑	↓	↑	↗	↓	↓	↓	↑	↑	↗	
MIL-H-13910	↑	↑	↑	↓	↑	↑	↗	↓	↑	↑	↑	↑	↑	↗	
MIL-H-19457	↓	↗	↑	↓	↓	↓	↓	→	↑	↓	↓	↓	↑	↓	
MIL-H-22251	↗	↑			↗	↗			↓	↑			↗		
MIL-H-27601	↑	↓	↑	→	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
MIL-H-46170 da -25 a +200 °C	↑	↓	↑	↗	↑	↗	↑	↑	↓	↓	↓	↓	↑	↗	
MIL-H-46170 da -30 a +135 °C	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↑	↗		
MIL-H-46170 da -50 a +135 °C	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↑	↗		
MIL-H-46170 da -55 a +135 °C	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↑	↗		
MIL-H-5606 da -54 a +113 °C	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↑	↗		
MIL-H-5606 da -54 a +135 °C	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↑	↗		
MIL-H-6083	↑	↓	↑	↑	↑	↑	↑	↓	↓	↓	↓	↑	↑		
MIL-H-7083	↑	↑	↗	↓	↑	↗	↑	↑	↑	→	→	↗	↑	↓	
MIL-H-8446 (MLO-8515)	↗	↓	↑	↓	↗	↑	↑	↓	↓	↓	↓	↑	↗		
MIL-J-5161	↗	↓	↑	↗	↗	↓	↑	↓	↓	↓	↓	↑	↑		
MIL-L-15016	↑	↓	↑	↑	↑	↗	↗	↗	↓	↓	↓	↓	↑	↑	
MIL-L-15017	↑	↓	↑	↑	↑	↗	↗	↓	↓	↓	↓	↑	↑		
MIL-L-17331	↑	↓	↑		↑				↓	↓	↓	↓	↑		
MIL-L-2104	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↑	↑		
MIL-L-21260	↑	↓	↑	↑	↑	↗	↗	↑	↓	↓	↓	↑	↑		
MIL-L-23699	↗	↓	↑	→	↗	→	↗	↓	↓	↓	↓	↑	→		
MIL-L-25681	↗	↑	↑	→	↗	↗	↗	↓	↑	↗	↗	↑	↗		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
MIL-L-3150	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-L-6081	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↑	↑	↑	
MIL-L-6082	↑	↓	↑	↑	↑	↗	↑	→	↓	↓	↓	↑	↑	↑	
MIL-L-6085	↗	↓	↑	→	↗	↓	↗	↓	↓	↓	↓	↑	↗		
MIL-L-6387	↗	↓	↑	↑	↗	↓	↗	↓	↓	↓	↓	↑	↗		
MIL-L-7808	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↑	↗		
MIL-L-7870	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↑	↑		
MIL-L-9000	↑	↓	↑	→	↑	↗	↗	↓	↓	↓	↓	↑	↑		
MIL-L-9236	↗	↓	↑	↗	↗	↓	↗	↓	↓	↓	↓	↑	↗		
MIL-O-3503	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↑	↗		
MIL-P-27402	↗	↑			↗	↗			↑			↗			
MIL-R-25576 (RP-1)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↑	↑		
MIL-S-3136, carburante tipo I	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↑	↑		
MIL-S-3136, carburante tipo II	↗	↓	↑	↗	↗	↓	↗	↓	↓	↓	↓	↑	→		
MIL-S-3136, carburante tipo III	↗	↓	↑	↗	↗	↓	↗	↓	↓	↓	↓	↑	→		
MIL-S-3136, carburante tipo IV, alto assorbimento	↑	↓	↑	↑	↑	↓	↑	↗	↓	↓	↓	↑	↑		
MIL-S-3136, carburante tipo IV, basso assorbimento	↑	↓	↑	↑	↑	↑	↑	→	↓	↓	↓	↑	↑		
MIL-S-3136, carburante tipo V, medio assorbimento	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑		
MIL-S-81087	↑	↑	↑	↑	↑	↑	↗	→	↑	↑	↑	↑	↑		
MIL-T-5624, JP-4, JP-5	↑	↓	↑	↗	↑	↓	↗	↓	↓	↓	↓	↑	↗		
MIL-T-83133	↑	↓	↑	↑	↑	↗	↓	↓			↓	↑	↑		
MLO-7277 idr.	→	↓	↑	→	→	↓	→	↓	↓	↓	↓	↑	→		
MLO-7557	→	↓	↑	→	→	↓	→	↓	↓	↓	↓	↑	→		
MLO-8200 idr.	↗	↓	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑			
MLO-8515	↗	↓	↑	↑	↗	↑	↑	↓	↓	↓	↓	↑	→		
Mobil 24dte	↑	↓	↑		↑	↗							↑		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Mobil 254 lubrificante												↑			
Mobil Delvac 1100, 1110, 1130, 1120	↑	↓	↑		↑	↗						↑			
Mobil HF	↑	↓	↑		↑	↗						↑			
Mobil Nivac 20, 30	↑	↑	↑		↑	↑						↑			
Mobil SHC 500 serie	→	↓	↑	↗	→	↗	↗	↗	↗	↓			↑	↑	
Mobil SHC 600 serie	→	↓	↑	↑	→	↗	↗	↗	→	↓		↓	↑	↑	
Mobil Therm 600	↑	↓	↑		↑	↗						↑			
Mobil Velocite c	↑	↓	↑		↑	↗						↑			
Mobilgas WA200 ATF	↑	↓	↑		↑	↗						↑			
Mobilgear serie 600	→	→	↑	↗	→	↑	↑	↑	→	→	↓	↓	↑	↑	
Mobilgear serie SHC ISO	→	→	↑	↗	→	↗	↑	↑	→	→	↓	↓	↑	↑	
Mobilgrease HP	↗	↓	↑	↑	↗	↗	↑	↗	↗	↓	↓	↑	↑		
Mobilgrease HTS	↗	↓	↑	↑	↗	↗	↑	↗	↗	↓	↓	↑	↑		
Mobilgrease SM	↗	↓	↑	↑	↗	↗	↑	↗	↗	↓	↓	↑	↑		
Mobilith serie AW	↗	↓	↑	↑	↗	↗	↑	↗	↗	↓	↓	↑	↑		
Mobilith serie SHC	↗	↓	↑	↑	↗	→	↑	↗	↗	↓	↓	↑	↑		
Mobiljet II lubrificante												↑			
Mobilmistlube serie	→	→	↑	↗	→	↑	↑	↑	↑	→	→	↓	↓	↑	↑
Mobiloil SAE 20	↑	↓	↑		↑	↗							↑		
Mobilux	↑	↓	↑		↑	↗						↑			
Molibdenato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Monobromobenzene	↓	↓	↗	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑	
Monobromotoluene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Monoclorobenzene	↓	↓	↗	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓		
Monoclorobutene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Monocloroiodrina												↑			

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Monocloruro di zolfo	↑	↓	↑	↑	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑
Monocromato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Monoetanolamina (MEA)	↓	↗	↓	↓	↓	↓	↓	↗	↗	↗	↗	↗	↗	↗	↓
Monoetilico ammina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Monoisopropilamina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Monometil anilina	↓	↑	↗	↓		↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Monometil etere (etero dimetilico)															↑
Monometil etere (etero metilico)	↑	↓	↑												↑
Monometil idrazina	↗	↑													↗
Monometilamine (MMA)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Monometilanilina	↓	↗	↗	↓	↓										↑
Mononitrotoluene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Mononitrotoluene & Dinitrotoluene (miscela 40/60)	↓	↑	→	↓	↓	↓	→	↓	↓	↓	↓	↓	↗	↓	↓
Monossido di carbonio	↑	↑	↗	↑	↑	↗	↗	↗	↑	↑	↗	↗	↑	↑	↑
Mordenzanti ossido															↑
Morfolina															↑
Nafta	↗	↓	↑	↗	↗	↓	↗	↓	↓	↓	↓	↑	↗	↗	
Naftalene	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑		↑
Naftenato di calcio															↑
Naftilammmina															↑
Neon	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Nicotina															
Nicotinamide (Niacinamide)															
Nicotinamide cloridrata	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrati cromico															↑
Nitroso ceroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Nitrato d'argento	↗	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↗	↑
Nitrato di alluminio	↑	↑	↑	→	↑	↑		↗	↑	↑	↑	↑	↑	↑	↓
Nitrato di amile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrato di ammonio solfato	↑	↑	↓		↑	↑			↑	↑	↑	↗	↑	↓	
Nitrato di ammonio, 2N	↑	↑			↑	↑			↑			↑		↗	
Nitrato di bario	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrato di bismuto	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrato di cadmio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrato di calcio	↑	↑	↑	↗	↑	↑	↑	↗	↑	↑	↑	↑	↑	↗	↑
Nitrato di cellulosa *	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrato di dicloroexilammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrato di litio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrato di nichel	↑	↑	↑		↑	↑	↑	↗	↑	↑	↑	↑	↑		
Nitrato di piombo	↑	↑	↑	↓	↑	↗	↑	↗	↑	↑	↑	↑	↑		↑
Nitrato di potassio	↗	↑	↑	→	↗	↗	↑	↑	↑	↑	↑	↑	↑	→	↑
Nitrato di potassio mercuroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrato di rame	↗	↑	↑	↓	↗	↗						↑	↓	↑	
Nitrato di sodio	↗	↑	↑	↓	↗	↗		↓	↑	↑	↑	↗	↑	↓	↑
Nitrato di stronzio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrato di torio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrato di zinco	↑	↑	↑		↑		↑		↑	↑	↑	↑	↑	↑	↓
Nitrato di zirconio	↑	↑	↑	↓	↑	↑	↑	↑	↗	↗	↗	↑	↑	↑	↓
Nitrato ferrico	↑	↑	↑	↗	↑	↑	↑	↗	↑	↑	↑	↑	↑	↗	
Nitrato mercurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrito di amile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrito di ammonio	↑	↑			↑	↗		↗	↑	↑	↑	↑	↑		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Nitrito di litio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrito di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitroanilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrobenzene	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	↓	↑	↑	↓	↑
Nitrocellulosa	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitroclorobenzene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrocloroformio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrodietilanilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrodifeniletere															↑
Nitroetano	↓	↗	↓	↓	↓	↗	↓	↓	↗	↗	↗	↗	↗	↑	↓
Nitrofenolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrofluorobenzene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitroglicerina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑
Nitroglicerolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitroisopropilbenzene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrometano	↓	↗	↓	↓	↓	→	↓	↓	↗	↗	↗	↗	↗	↑	↑
Nitropropano	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↑	↑	↓	↑
Nitrotiofene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nitrotoluene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Nonano	↑	↓	↑	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	↑
Noryl GE fenolico	↑	↑													
Nuovi fluidi in sviluppo	↑	↗	↑		↑	↑	↑	↑	↗	↗	↗	↗	↗	↗	↑
Nyvac FR200 Mobil	↑	↑	↑		↑	↗			↓	↓	↓	↓	↑		
Octachloro Toluene	↓	↓	↑	↓	↓	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓
Oleato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Olefine						↑	→	↓	↗	↓	↓	↓	↓	↑	↓

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Oleum (acido solforico fumante)	↓	↓	↑	↓	↓	↓		↓	↓	↓	↓	↓	↑	↓	
Oleum spiriti	↗	↓	↑	→	↗	→	↗	↓	↓	↓	↓	↓	↑		
Oli di silicone	↑	↑	↑	↑	↑	↑	→	→	↑	↑	↑	↑	↑	↑	↑
Oli fluorocarbonati		↑											↗		↑
Oli idraulici (base sintetica)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Oli lubrificanti (a base di petrolio)	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Oli lubrificanti (base sintetica)			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Oli lubrificanti (Di ester)	↗	↓	↑		↗	→	↗	↓	↓	↓	↓	↓	↑	↗	
Oli lubrificanti (grezzi e raffinati)	↗	↓	↑		↗	→								↑	
Oli lubrificanti SAE 10, 20, 30, 40, 50	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Oli minerali	↑	↓	↑	↑	↑	↗	↑	↗	→	↓	↓	↓	↑	↑	
Oli motori	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑		↑
Oli solfonati	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Olio animale (olio di strutto)	↑	↗	↑	↗	↑	↗	↑	↗	↗	↓	↓	↓	↑		↑
Olio bianco	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Olio Bunker	↗	↓	↑	↗	↗	↓	↑	↗	↓	↓	↓	↓	↑	↑	
Olio Bunker C (olio combustibile)	↑		↑											↑	
Olio combustibile, # 6	↗	↓	↑	↗	↗	↓	↑	↑	↓	↓	↓	↓	↑	↑	↗
Olio combustibile, 1 e 2	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	↗
Olio combustibile, acido	↑	↓	↑	↗	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	↗
Olio d'oliva	↑	↓	↑	↑	↑	↗	↑	→	↗	↓	↓	↓	↑	↑	↑
Olio da taglio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑		↑
Olio del trasformatore	↗	↓	↑	↑	↗	↓	↑	↗	↓	↓	↓	↓	↑	↗	↑
Olio del trasformatore Askarel	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Olio del trasformatore Pyronol	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Olio di anilina	↓	↗	→	↓	↓	↓	→	↓	↗	↓	↓	↓	↗	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Olio di arachidi	↑	↓	↑	↑	↑	↓	↑	↑	↑	→	↓	↓	↓	↑	↑
Olio di cocco	↑	↓	↑	↑	↑	↗	↑	↑	↑	→	↓	↓	↑	↑	↑
Olio di colza	↗	↓	↑	↗	↗	↗	↑	↓	↑	↓	↓	↓	↑	↗	↑
Olio di fegato di merluzzo	↑	↑	↑	↑	↑	↗	↑	↗	↑	↓	↓	↓	↑	↑	↑
Olio di lavanda	↗	↓	↑	↓	↗	↓								↑	↗
Olio di legno	↑	↓	↑	→	↑	↗	↗	↓	→	↓	↓	↓	↑	↑	
Olio di legno cinese (olio di Tung)	↑	↓	↑	→	↑	↗	↗	↓	→	↓	↓	↓	↑		
Olio di mais	↑	↓	↑	↑	↑	↗	↑	↑	↑	→	↓	↓	↑	↗	↑
Olio di Neatsfoot	↑	↗	↑	↑	↑	↓	↑	↗	↗	↗	↓	↓	↑	↑	
Olio di pesce	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↑	
Olio di petrolio greggio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Olio di petrolio, sopra i 120 °C	↓	↓	↗	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑		
Olio di petrolio, sotto i 120 °C	↑	↓	↑	↗	↑	↗	↗	↗	↗	↓	↓	↓	↑	↗	
Olio di pino	↗	↓	↑	↑	↑	↗	↓	↑	↓	↓	↓	↓	↑	↑	
Olio di pino bianco	↗	↓	↑		↗	↓	↑	↓	↓	↓	↓	↓	↑		
Olio di piridina	↓	↗	↓		↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	
Olio di ricino	↑	↗	↑	↑	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	
Olio di semi di cotone	↑	↓	↑	↑	↑	↗	↗	↑	→	↓	↓	↓	↑	↑	
Olio di semi di lino	↑	→	↑	↗	↑	↗	↑	↑	→	↓	↓	↓	↑	↗	
Olio di soia	↑	↓	↑	↗	↑	↗	↑	↑	↑	→	↓	↓	↑	↗	
Olio di Tung (olio di legno della Cina)	↑	↓	↑	→	↑	↗	↗	↓	→	↓	↓	↓	↑		
Olio Halowax	↓	↓	↑		↓	↑	↑	↓	↓	↓	↓	↓	↑		
Olio idraulico (base di petrolio, industriale)	↑	↓	↑	↑	↑	↗	↑	↗	↗	↓	↓	↓	↑	↑	
Olio rosso (MIL-H-5606)	↑	↓	↑	↑	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	
Olio rosso linea 100	↑	↓	↑	↑	↑	↑	↗	↑	↑	↓	↓	↓	↑	↑	
Olio standard Mobilube GX90-EP Lube	↑	↓	↑	↑	↑	↑	↗	↑	↑	↓	↓	↓	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Olio turbina	↑	↓	↑	↑	↑	↓	↑	↓	↓	↓	↓	↓	↑	↑	
Olio turbina #15 (MIL-L-7808A)	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Olio Turbo #35	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Olio vegetale	↑	↓	↑		↑	↗	↑	↑	→	↓	↓	↓	↑	↗	
Oronite 8200	↗	↓	↑	↑	↗	↑	↑	↓	↓	↓	↓	↓	↑		
Oronite 8515	↗	↓	↑	↑	↗	↑	↑	↓	↓	↓	↓	↓	↑		
Orto-cloro etil Benzene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Orto-cloroanilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Orto-clorofenolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Orto-cresolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Orto-diclorobenzene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Orto-Nitrotoluene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ortosilicato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ortosilicato tetraetile (TEOS)													↑		
OS 45 tipo III (OS45)	↗	↓	↑	↓	↗	↑	↗	↓	↓	↓	↓	↓	↑		
OS 45 tipo IV (OS45-1)	↗	↓	↑	↓	↗	↑	↗	↓	↓	↓	↓	↓	↑		
OS 70	↗	↓	↑	↓	↗	↑	↗	↓	↓	↓	↓	↓	↑		
Ossalato di alluminio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossalato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossalato di butile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossalato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossalato di etile	↓	↗	↑	↑	↓	↓	↗	↓	↓	↓	↑	↑	↑	↓	
Ossalato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossalato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossicloruro di bismuto	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossicloruro di fosforo													↑		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Ossidi di azoto	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossido cromico	↓	↗	↑		↓	↓								↑	
Ossido di arsenico														↑	
Ossido di bario	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Ossido di berillio	↑	↑	↑	→	↑	→	→	→	↑	→	→	↑	→	→	
Ossido di cadmio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossido di calcio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Ossido di difenile	↓	↓	↑	↓	↓	↗	→	↓	↓	↓	↓	↑	↓	↑	
Ossido di difenilene														↑	
Ossido di etilene	↓	↗	↓	↓	↓	↓	↓	↓	→	↓	↓	↓	↑	↓	
Ossido di etilene, (12%) e Freon 12 (80%)	→	↗	↓	↓	→	↓	↓	↓	↗	↓	↓	↗	↓	↓	
Ossido di mesitile (chetone)	↓	↑	↓	↓	↓	↓	↓	↓	↗	↓	↓	↑	↓	↑	
Ossido di molibdeno	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossido di piombo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossido di propilene	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↑	↓	↑	
Ossido di rame	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Ossido di vanadio	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	↑	
Ossido di zinco	↑	↑	↑		↑				↑	↑	↑	↑	↑	↓	
Ossigeno liquido	↓	↓	↓		↓	↓								↗	
Ossigeno liquido (LOX)	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↗	↓	
Ossigeno, 150-200 °C	↓	↓	↗	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	↓	
Ossigeno, 90-150 °C	↓	↓	↗		↓									↑	
Ossigeno, freddo	↗	↑	↑	↑	↗	↑	↑	↑	↑	↗	↗	↗	↗	↗	
Ottadecano	↑	↓	↑	↗	↑	↗	↑	↑	↓	↓	↓	↑	↑	↗	
Ottanale (n-Octanaldeide)	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	↑	
Ottano o n-ottano	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↑	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Ozono	↓	↑													
Par-al-chetone	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓			↓
Para-clorofenolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Para-diclorobenzene	↓	↓	↑	↓	↓	↗	↓	↓	↓	↓	↓	↑	↑	↓	↓
Para-formaldeide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Para-nitroanilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Para-nitrofenolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Paracimene			↑	→			↓	↗	↓	↓	↓	↓	↑	↑	↓
Paracresol monobutiletere															↑
Paraffine	↑	↓	↑	↗	↑	↑	↑	↗	↓	↓	↓	↓	↑	↑	↑
Paraldeide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Paration			↑	→			↓	↗	↓	↓	↓	↓	↑	↑	↓
Parker O Lube	↑	↓	↑	↑	↑	↑	↑	↗	↓	↓	↓	↗	↑	↑	
Pectina (liquore)			↑	→			↓	↗	↓	↓	↓	↓	↑	↓	↑
Penicillina (liquido)			↑	→			↓	↗	↓	↓	↓	↓	↑	↓	
Pentacloroetano			↑	→			↓	↗	↓	↓	↓	↓	↑	↓	
Pentaclorofenolo	→	↗	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Pentacloruro di antimonio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Pentaeritrite	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Pentafluoroetano (F-125)															↗
Pentafluoruro di antimonio															↗
Pentafluoruro di bromo	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↗	↓	
Pentafluoruro di iodio	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↗	↓	
Pentano o n-pentano	↑	↓	↑	↓	↑	↗	→	↓	↓	↓	↓	↓	→	↑	↑
Pentano, 2 metile	↑	↓	↑	↓	↑	↗	→	↓	↓	↓	↓	↓	↑	↑	
Pentano, 3 metile	↑	↓	↑	↓	↑	↗	→	↓	↓	↓	↓	↓	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Pentano, dimetil 2-4	↑	↓	↑	↓	↑	↗	→	↓	↓	↓	↓	↓	↓	↑	↑
Pentanoato di pentile	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	↑
Pentossido di vanadio	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Pentoxone															↑
Perborato di sodio	↗	↑	↑			↗	↗	↑	↗	↑	↗	↗	↗	↑	
Percarbonato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Perchlorato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Perchlorato di litio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Perchlorato di potassio	↓	↑	↑	↓	↓	↗	↑	↗	↑	↑	↑	↑	↑	↑	↑
Perchlorato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Percloroetilene	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Perfluoropropano															↗
Perfluorotrielammine															↗
Permanganato di calcio															↑
Permanganato di potassio	↓	↑	↑	↗	↓	↗	↑	↗	↑	↑	↑	↑	↑	↑	→
Perossidisolfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Perossidisolfato ferrico	↑	↑	↑			↑	↑								↑
Perossido di bario	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Perossido di benzoile															↑
Perossido di calcio															↑
Perossido di idrogeno	↗	↑	↑			↗	↑	↑	↑	↑	↑	↑	↗	↑	↓
Perossido di idrogeno 90%	↓	→	↑			↓	↓	↗	→	↓	↓	↓	↑	↓	↑
Perossido di potassio															↑
Perossido di sodio	↗	↑	↑	↓	↗	↗	↑	↑	↗	↗	↗	↗	↗	↑	↓
Persolfato di potassio	↓	↑	↑	↓	↓	↗	↑	↗	↑	↑	↑	↑	↑	↑	↑
Petrolato	↑	↓	↑	↑	↑	↗	↑	↗	↑	↑	↑	↑	↑	↑	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Petrolato etere	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Petrolio a base di grasso	↑	↓	↑	↑	↑	→	↑	↓	↓	↓	↓	↓	↑	↑	
Petrolio greggio	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↑	
Petrolio greggio acido	→	↓	↑	↓	→	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Picrato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Pine Tar	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	↑	
Pinene	↗	↓	↑	↗	↗	↗	↑	↓	↓	↓	↓	↑	↑	↓	
Piombo (fuso)															↑
Piombo naftenato															↑
Piombo tetraetile	↗	↓	↑		↗	↓	↗		↓	↓	↓	↓	↑	↑	
Piombo tetraetile "Blend"	↗	↓	↑		↗	↓	↗		↓	↓	↓	↓	↑		
Piperazina				↑	→		↓	↗	↓	↓	↓	↓	↑	↓	
Piperidina	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓	↑	
Piranha (H2SO4:H2O2) (70:30)															↑
Piridina	↓	↓	↓	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	↑
Piridina solfonato di calcio															↑
Pirofosfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Pirogallolo (acido pirogallico)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Pirosulfato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Pirrolo	↓	↓	↓		↓	↓	↓	↗	↓	↗	↗	↗	↑	↓	↑
Plumbite di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Polietylene glicole	↗	↑	→		↗	↗									↑
Poliglicerina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Poliglicoli	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Polisolfuro di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Polisolfuro di bario	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Potassa caustica	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Potassio (fuso)															↓
Potassio sulfato di alluminio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
PRL - olio idr. per alta Temp	↗	↓	↑	↗	↗	↗	↑	↗	↓	↓	↓	↑	↑	↑	
Produttore di gas	↑	↓	↑	↑	↑	↗	↗	↗	↓	↓	↓	↑	↑	↗	
Propano	↑	↓	↑	↗	↑	↗	↗	↗	↓	↓	↓	↓	↑	↗	
Propil nitrato	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↑	↓	↑	
Propile Acetone o Acetone n-propilico	↓	↑	↓	↓	↓	↓	↓	↓	↑	↓	↓	↑	↓	↑	
Propilene	↓	↓	↑	↓	↓	↓	→	↓	↓	↓	↓	↑	↓	↑	
Propionaldeide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Propionato di amile	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	↑	
Propionato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Propionato di propile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Propionitriile	↑	↓	↑		↑	↗									↑
Propylamine	↓	↓	↓	↓	↓	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Propylbenzene			↑	→		↓	↗		↓	↓	↓	↑	↓		
Protossido di azoto	↑	↑	↑		↑				↑					↑	↑
Punto nero 77	↑	↑	↑	→	↑	→	→	→	↑	→	→	→	↑	→	
Pydraul, 10E	↓	↑	↓	↓	↓	↓	↓	↑	↑	↑	↓	↓	↑	↓	
Pydraul, 115E	↓	↑	↑	↓	↓	↓	→	↓	↑	↓	↓	↑	↓	↑	
Pydraul, 230 C, 312 C, 540 C, A200	↓	↓	↑	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓		
Pydraul, 29ELT 30E, 50E, 65E	↓	↑	↑	↓	↓	↑	↑	↑	↓	↓	↓	↑	↓		
Pydraul, 90e	↓	↑	↑		↓	↓									↑
Pyrogard 42, 43, 55	↓	↑	↑		↓	↓									↑
Pyrogard 53, Mobil estere fosfato	↓	↑	↑	↓	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	
Pyrogard D, emulsione acqua in olio Mobil	↑	↓	↓	↑	↑	↗	↗	↗	→	↓	↓	↓	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Pyrolube	↓	↗	↑	↓	↓	↓	↗	↗	↗	↓	↓	↓	↑	↓	
Quinizarin	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Radiazioni (Gamma, 1.0 E+07 Rads)	→	↗	↓	↓	→		↓	↗	↓				↗		
Raffinato	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Rame acetato di ammonio	↓	↗	↓	↓	↓	→	↑	↗	↑	↑	↑	↑	↑	↓	
Rame gluconato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Rame naftenato													↑		
Reagente di Fisher		↗													
Resine epossidiche	↑	↓			↑			↑					↑		
Resorcinolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Riboflavina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
RJ-1 (MIL-F-25558)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
RJ-4 (MIL-F-82522)	↗	↓	↑	↗	↗	↓	↑	↓	↓				↓	↑	↗
Rodio														↑	
RP-1 (MIL-R-25576)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Saccarina in soluzione	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Salamoia	↑	↑	↑		↑								↑		
Salamoia (acqua salata)	↑	→	↑		↑	↓							↑		
Sale ammoniaco	↑	↑	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Sale di Glauber	↓	↗	↑	↓	↓	↗	↑		↗	↓	↗	↓	↑	↓	
Sale di Wolmar	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↗	
Sali di alluminio	↑	↑	↑	→	↑	↑	↑		↑	↑	↑	↑	↑	↑	
Sali di ammonio	↑	↑	→		↑	↑	→	↑	↑		↑	↑	↑	→	
Sali di bario	↑	↑	↑	↑	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑
Sali di calcio	↑	↑	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Sali di magnesio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Sali di mercurio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑
Sali di nichel	↑	↑	↑	→	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	→
Sali di potassio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Sali di rame	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Sali di sodio	↑	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑
Sali di zinco	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Salicilato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Salicilato di litio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Salicilato di metile	↓	↗			↓	↓			↗				→	↑	
Salicilato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Santo Safe 300	↓	→	↑		↓	↓	↑	↑	→	↓	↓	↓	↑	↓	
Sapone in soluzione	↑	↑	↑	↗	↑	↗	↑	↑	↑	↑	↑	↑	↗	↑	↑
Seleniuro di idrogeno														↑	
Servizio Città # 65 # 120 # 250	↑	↓	↑	↗	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	↑
Servizio Città AP-Koolmoter olio cambio EP 140 Lube	↑	↓	↑	↑	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	
Servizio Città Pacemaker # 2	↑	↓	↑	↗	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	
Sesquisilicate di sodio														↑	
SF 1154 GE Silicone liquido	↗	↑	↑	↗	↗	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑
SF1147 GE Silicone liquido	↗	→	↑		↗				↓	→				↑	
SF96 GE Silicone liquido	↗	↑	↑	↗	↗	↑	↑	↑	↓	↑	↑	↑	↑	↑	
Shell 3XF fluido per miniera (resis. fuoco)	↑	↓	↑	↓	↑	↗	↑			↓	↓	↓	↑	↑	
Shell Alvania grasso #2	↑	↓	↑		↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	
Shell Carnea 19 e 29	↑	↓	↑	↗	↑	↓	↑			↓	↓	↓	↑	↑	
Shell Diala	↑	↓	↑	↗	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	
Shell Irlus 905	↑	↓	↑	↑	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	
Shell Lo Hydrax 27 e 29	↑	↓	↑	↗	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	



Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Shell Marin 72	↑	↓	↑ ↗	↑ ↗	↑ ↗	↗	↑ ↗	↓	↓	↓	↓	↓	↑	↑	
Shell Tellus #32 a base di petrolio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Shell Tellus #68	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Shell Tellus 27 (Base di petrolio)	↑	↓	↑		↑ ↗									↑	
Shell Tellus 33	↑	↓	↑		↑ ↗									↑	
Shell UMF (5% aromatici)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Shellac	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Silano															↑
Silicato di calcio	↑	↑	↑		↑	↑			↑	↑	↑	↑	↑	↑	
Silicato di etile	↑	↑	↑		↑	↑	↑		↑	↗	↗	↗	↗	↑	
Silicato di potassio															↑
Silicato di sodio	↑	↑	↑		↑	↑			↑	↑	↑	↑	↑	↑	
Skelly, solvente B, C, E	↑	↓	↑		↑	↓	↑		↓	↓	↓	↓	↑	↑	
Skydrol 500 B4	↓	↑	↓	↓	↓	↓	→	→	↗	↓	↓	↓	↑	↓	
Skydrol 7000	↓	↑	↗	↓	↓	↓								↑	↓
Skydrol LD-4	↓	↑	↓	↓	↓	↓	→	→	↗	↓	↓	↓	↑	↓	
Socony Mobile tipo A	↑	↓	↑	↗	↑	↗	↗	↗	↓	↓	↓	↓	↑	↑	
Socony Vacuum AMV AC781 (grasso)	↑	↓	↑	↗	↑	↗	↗	↗	↓	↓	↓	↓	↑	↑	
Socony Vacuum PD959B	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Soda Ash	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Soda caustica (idrossido di sodio)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Sodio (fuso)															↓
Sodio arsenito	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Sodio cianamidico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Sodio cianato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Sodio Diacetato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Sodio etilato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sodio monofosfato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sodio resinato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sodio sulfato di alluminio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sodio stannato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sodium Silicofluoride													↑		
Solfanilico cloruro	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Solfato acido di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato acido di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato alluminato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato cromico													↑		
Solfato d'argento	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di alluminio	↑	↑	↑	↓	↑	↑	↑		↑	↑	↑	↑	↗	↑	↓
Solfato di ammonio	↑	↑	↓		↑	↑			↑	↑	↑	↑	↗	↑	↓
Solfato di ammonio ferrico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di anilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di antimonio													↑		
Solfato di bario	↑	↑	↑	↑	↑	↑	↑						↑	↑	
Solfato di berillio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di Brucina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di cadmio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di calcio	↑	↑	↑	↑	↑			↑	↗	↑	↑	↑	↑	↓	
Solfato di cerio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di cobalto	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di dietile	↓	↑	↓	↓	↓	↓	↗						↑		
Solfato di etile	↓	↑	↓	↓	↓	↑							↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Solfato di manganese	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Solfato di nichel	↑	↑	↑	→	↑	↑	↑	↑	↑	↗	↗	↗	↑	↓	↑
Solfato di nichel ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di nicotina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di piridina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Solfato di potassio	↑	↑	↑	→	↑	↗	↑	↑	↑	↗	↗	↑	↑	↑	↓
Solfato di rame	↑	↑	↑	↑	↑	↑	↑	↑	↗	↗	↗	↑	↑	↓	↑
Solfato di rame 10 %	↑	↑	↑	↗	↑	↑	↑	↑	↗	↗	↗	↗	↑	↓	↑
Solfato di rame 50 %	↑	↑	↑	→	↑	↑	↑	↑	↗	↗	↗	↗	↑	↓	↑
Solfato di sodio	↗	↑	↑	↓	↗	↑	↑	↑	↑	↗	↗	↗	↑	↑	↓
Solfato di titanio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Solfato di zinco	↑	↑	↑	↓	↑	↑	↑	↑	↗	↗	↗	↑	↑	↑	↓
Solfato e solfito di magnesio	↑	↑	↑		↑	↑	↑	↑	↗	↗	↗	↑	↓	↑	
Solfato ferrico	↑	↑	↑		↑	↑									↑
Solfato ferroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Solfato ferroso di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Solfato manganoso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Solfato mercurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Solfato rameico	↗	↗	↑												↑
Solfato stannoso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Solfito di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Solfito di anilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Solfito di calcio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↗	↗	↗	↑	↑	↓
Solfito di potassio	↑	↑	↑	→	↑	↑	↑	↑	↑	↑	↗	↗	↑	↑	↓
Solfito mercurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Solfonato fenolico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Solfonilcloruro	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↗	↓
Solfuro d'idrogeno (secco, caldo)	↓	↑	↓		↓	↗	→	→	↑	↓	↓	↓	↑	↓	↑
Solfuro d'idrogeno (secco, freddo)	↑	↑	↓		↑	↑	→	→	↑	↑	↑	↑	↑	↓	↑
Solfuro d'idrogeno (umido freddo)	↓	↑	↓		↓	↑	→	→	↑	↓	↓	↓	↑	↓	↑
Solfuro d'idrogeno (umido, caldo)	↓	↑	↓		↓	↗	→	→	↑	↓	↓	↓	↑	↓	↑
Solfuro di alchile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Solturo di ammonio	↗	↑	↓	↓	↗	↗			↑	↑	↑	↗	↑	↓	
Solfuro di bario	↑	↑	↑	↑	↑	↑	↑	↑	↑	↗	↑	↗	↑	↑	↓
Solfuro di cadmio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Solfuro di calcio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↗	↗	↗	↑	↑	↓
Solfuro di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Solfuro di sodio e solfito	↑	↑	↑	↑	↑	↑	↑	↑	↑	↗	↗	↗	↑	↑	↑
Solfuro di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Soluzione decappante	↓	→	↗	↓	↓	↓	↓	↓	→	↓	↓	↑	↑	↓	↑
Soluzione di acqua detergente	↑	↑	↑	↓	↑	↗	↑	↑	↑	↗	↗	↑	↑	↓	↑
Soluzione elettrolitica (Co,Cu, Au,In,Fe,Pb,Ni,Ag,Sn,Zn)	↑	↑	↑		↑										↑
Soluzioni antigelo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑
Soluzioni di Bleach	↓	↑	↑	↓	↓	↓	↓								↑
Soluzioni di borace	↗	↑	↗	↓	↗	↓									↑
Soluzioni di liscivia	↗	↑	↗	↓	↗	↗	↗	↗	↑	↗	↗	↗	↑	↑	↓
Soluzioni di saccarosio	↑	↑	↑	↓	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↓
Soluzioni per cromatura	↓	↗	↑	↓	↓	↗	↗	↗	↗	↓	↓	↓	↑	↑	↓
Soluzioni per placcatura (altre)	↑	↑	↑		↑	↓			↓	↑			↓	↑	
Soluzioni per placcature di cromo	↓	↗	↑	↓	↓	↗	↗	↗	↗	↓	↓	↓	↑	↑	↓
Solvente Stoddard	↑	↓	↑	↑	↑	↑	↗	↑	↓	↓	↓	↓	↑	↑	↑
Solventi clorurati, secco	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↑	↓

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Solventi clorurati, umidi	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Solvesso 100, 150												↑			
Sorbitolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sovasol nr. 1, 2, e 3	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
Sovasol nr. 73 e 74	↗	↓	↑	↗	↗	↗	↑	↓	↓	↓	↓	↓	↑	↗	
Spray	↑	↗	↑	↑	↑	↗	↑	↑	↗	↓	↓	↓	↑	↑	
SR-10 carburante	↑	↓	↑	↗	↑	↓	↑	↓	↓	↓	↓	↓	↑	↗	
SR-6 carburante	↗	↓	↑	↗	↗	↓	↑	↓	↓	↓	↓	↓	↑	↗	
Stannato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Stannic cloruro	↑	↑	↑		↑	↓	↑	↗	↑	↑	↑	↑	↑	↑	
Stannic cloruro, 50%	↑	↑	↑		↑	↓	↑	↗	↑	↑	↑	↑	↑	↑	
Stannico cloruro di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Stauffer 7700	↗	↓	↑		↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Stearato di butile	↗	↓	↑	↑	↗	↓	↗		↓	↓	↓	↓	↑		
Stearato di calcio	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Stearato di etile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Stearato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Stearato di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Stirene (monomero)	↓	↓	↑	↓	↓	↓	→	↓	↓	↓	↓	↑	↓	↑	
Sulfamato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sulfamato di calcio	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Sulfamato di piombo	↗	↑	↑		↗	↑	↑	↗	↑	↗	↗	↑	↑	↓	
Sulfanilimide	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Sulfocianide di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sulfolano	↗	↑	↗		↗	↗							↑		
Sulfonil cloruro di toluene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Sunoco #3661	↑	↓	↑	↑	↑	↑	↗	↑	↓	↓	↓	↓	↑	↑	
Sunoco SAE 10	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Sunsafe (fluido idraulico resistente al fuoco)	↑	↓	↑	↓	↑	↗	↑		↓	↓	↓	↓	↑	↓	
Swan Finch EP Lube	↑	↓	↑	↑	↑	↑	↓	↑	↓	↓	↓	↓	↑	↑	
Swan Finch Hypoid-90	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Tar, bituminosi	↓	↓	↗	↓	↓	↑	↗	↓	↓	↗	↓	↑	↑	↓	
Tarabuso													↑		
Tartrato acido di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tartrato di chinino	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tartrato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tartrato di sodio e potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tartaro feroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tellone II													↑		
Tetra fosfoglucosio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tetraborato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tetrabromoetano	↓	↓	↑		↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Tetrabromometano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Tetrabromuro di carbonio													↑		
Tetrabutil titanato	↗	↑	↑		↗	↑	↑	↗	↑	↑	↗	↗	↗	↑	
Tetracloroetano	↓	↓	↗	↓	↓	↗		↗	↓	↓	↓	↑	↓	↑	
Tetracloroetilene	↓	↓	↑	↓	↓	↗	↗	↓	↓	↓	↓	↑	↓	↑	
Tetracloruro di acetilene	↓	↑	↑	↓	↓	↗			↑			↓	↑		
Tetracloruro di carbonio	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Tetracloruro di silicio													↑		
Tetracloruro di stagno	↑	↓	↑	↑	↑	↗	↑	↗	↑	↑	↑	↑	↑	↑	
Tetracloruro di stannico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Tetracloruro di titanio	↗	↗	↗	↓	↗	↗	↗	↓	↓	↓	↓	↓	↑	↓	↑
Tetrafluoruro di carbonio	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	↓
Tetrafluoruro di silicio													↑		
Tetrafluoruro di zolfo													↗		
Tetrafosfato di sodio	→	↑	→	↓	→	↑	↑	↑	↗	↑	↑	↑	↑	↑	↓
Tetraidrofurano	↓	↓	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑
Tetralin	↓	↓	↑		↓	↓	↑	↓	↓	↓	↓	↓	↑		
Tetrametil diidropiridina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Tetrametil idrossido di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Tetrametilciclotetrasilossano (TMCTS)													↑		
Tetranitrito di pentaeritrite	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Tetrasulfide di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Tetrossido di azoto (N ₂ O ₄)	↓	↓	↓	↓	↓	↓	↓	↓	→	↓	↓	↓	↗	↓	↑
Tetrossido di diazoto													↗		
Texaco - Capella A e AA	↑	↓	↑	↗	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	↑
Texaco - grasso Uni-Temp	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	↑
Texaco - Meropa 220 (senza piombo)	↑	↓	↑	↗	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	
Texaco - olio cambio 3450	↑	↓	↑	↑	↑	↓	↑	↑	↓	↓	↓	↓	↑	↑	
Texaco - Regal B	↑	↓	↑	↑	↑	↓	↑	↑	↓	↓	↓	↓	↑	↑	
Texamatic - fluido "A" 1581	↑	↓	↑	↗	↑	↗	↗	↗	↓	↓	↓	↓	↑	↑	
Texamatic - fluido "A" 3401	↑	↓	↑	↗	↑	↗	↗	↗	↓	↓	↓	↓	↑	↑	
Texamatic - fluido "A" 3525	↑	↓	↑	↗	↑	↗	↗	↗	↓	↓	↓	↓	↑	↑	
Texamatic - fluido "A" 3528	↑	↓	↑	↗	↑	↗	↗	↗	↓	↓	↓	↓	↑	↑	
Texamatic - olio per trasmissioni "A"	↑	↓	↑	↗	↑	↗	↗	↗	↓	↓	↓	↓	↑	↑	
Texas - olio 1500	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Therminol 44	↓	↓	↑		↓	↓		↓	↓				↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Therminol 55	↗	↓	↑		↗	↓		↓	↓				↑	↗	
Therminol 66													↑		
Therminol FR													↑		
Therminol VP-1, 60, 65	↓	↓	↑		↓	↓		↗	↓				↑	↓	
THIO acido di cloruro													↑		
Thiokol TP-90B	↓	↑	↑		↓	↗	↗		↑			↓	↑		
Thiokol TP-95	↓	↑	↑		↓	↗	↗		↑			↓	↑		
Tidewater Multigear, 140 Lube EP	↑	↓	↑		↑	↑	↗	↑	↓	↓	↓	↓	↑	↑	
Tidewater olio-Beedol	↑	↓	↑		↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	
Tioarsenate di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Tiocianato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Tiocianato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Tiocianato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Tiocianato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Tioetanolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Tiofene (Thiofuran)	↓	↓	↓	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	↑
Tioglicolato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Tioglicolato di dibutile	↗	↓	↑		↗	↓	↗		↓	↓	↓	↓	↑	↓	
Tiosolfato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Tiosolfato di calcio	↗	↑	↑	↑	↑	↗	↑	↑	↑	↗	↗	↗	↗	↑	↓
Tiosolfato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Tiosolfato di sodio	↗	↑	↑	↑	↑	↗	↑	↑	↑	↗	↗	↗	↗	↑	↑
Tiourea	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓
Toluchinone	↗	↓	↑		↗	↓	↗		↓	↓	↓	↓	↑	↓	
Toluene	↓	↓	↗		↓	↓	↓	↗	↓	↓	↓	↓	↑	↓	↑
Toluidina	↗	↓	↑		↗	↓	↗		↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Toluolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Torta Niter	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Trementina	↑	↓	↑	→	↑	↓	↗	↓	↓	↓	↓	↑	↗	↑	
Triacetina	↗	↑	↓	↓	↗	↗	↗	↓	↑	↗	↗	→	↑	↓	↑
Triaril fosfato	↓	↑	↑	↓	↓	↓	↗	→	↑	↓	↓	↑	↓		
Tribromometilbenzene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↑	↓		
Tribromuro di antimonio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↑	↑		
Tribromuro di boro														↑	
Tributil ammina														↑	
Tributil citrato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tributil fosfato	↓	↑	↓	↓	↓	↓	↓	↓	↗	↓	↗	↓	↑	↓	↑
Tributil mercaptano	↓	↓	↑		↓	↓	→	↓	↓	↓	↓	↑	↓		
Tributoxyethyl fosfato	↓	↑	↑	↓	↓	↑	↗		↑	↗	↓	↗	↑	↓	↑
Tricloretilene	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓	↑	
Tricloroacetato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Triclorobenzene	↗		↑	↓	↓	↓	↗		↓	↓	↓	↑	↓		
Tricloroetano	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓		
Tricloroetanoloammine	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑		
Triclorometano	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓		
Tricloronitrometano (cloropicrina)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tricloropenilsilano														↑	
Tricloropropano	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓		
Triclorosilano	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓		
Tricloruro di antimonio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↑	↑		
Tricloruro di arsenico	↑	↓	↓		↑	↑							↑		
Tricloruro di boro													↑		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Tricloruro di etilene	↓	→	↑	↓	↓	↓	→	↓	→	↓	↓	↓	↑	↓	↑
Tricloruro di fosforo	↓	↑	↑		↓	↓	↑		↑			↓	↑		↑
Tricesil fosfato	↓	↗	↗	↓	↓	↓	↗	→	↑	↓	↓	↗	↑	↓	↑
Trietanolammina ammina	↑		↓				↓	↗	↗	↗	↗	↗	↑	↓	↑
Trietil fosfato	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↑	↓		
Trietilaluminio	↓	↗											↑		↑
Trietilborano		↑											↑		↑
Trietilentetrammina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Trifenil fosfito	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Trifluoroetano	↓	↓	↑	↓	↓	↓	↗	↓	↗	↓	↓	↓	↑	↓	
Trifluorometano	↓	↓	↑	↓	↓	↓	↗	↓	↗	↓	↓	↓	↑	↓	
Trifluorovinilcloruro	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Trifluoruro di antimonio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Trifluoruro di azoto														↗	
Trifluoruro di boro														↑	
Trifluoruro di bromo	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↗	↓	
Trifluoruro di cloro	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↗	↓	
Trifluoruro di clorobenzene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Trifosfato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Trifosfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Trimetilammina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Trimetilammina (TMA)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Trimetilbenzene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Trimetilborate (TMB)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Trimetilpentano	↑	↓	↑	↑	↑	↑	↗	↑	↗	↓	↓	↓	↑	↑	
Trinitrotoluene (TNT)	↓	↓	↗	↗	↓	↗	↗	↗	↓	↓	↓	↓	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Zinco naftenato												↑			
Zolfo	↓	↑	↑		↓	↑	↑		↑	↓	↓	↓	↑	↓	↑
Zolfo (fuso)	↓	→	↑	↓	↓	→	→	→	→	↓	↓	↓	↑	↓	↓
Zolfo di calce			↑	→	↓	↗		↓	↓	↓	↓	↑	↓		↑