

**TABELLA DI COMPATIBILITÀ DEI FLUIDI**
**Legenda**

eccellente	↑
buono (OK per tenute statiche)	↗
discutibile (talvolta OK per tenute statiche)	→
scarso	↓

**Guida ai materiali**

<b>NBR</b>	Gomma Nitrilica
<b>EPDM</b>	Etilen-Propilene
<b>FKM</b>	Fluoroelastomero (Viton)
<b>TPU</b>	Poliuretano
<b>HNBR</b>	Gomma Nitr. Idrogenata
<b>CR</b>	Neoprene
<b>FMQ</b>	Fluoro-Silicone
<b>MQ</b>	Silicone
<b>IIR</b>	Butile
<b>BR</b>	Butadiene
<b>IR</b>	Isoprene
<b>SBR</b>	Stirene-Butadiene
<b>FFKM</b>	Perfluoroelastomero (Kalrez)
<b>ACM</b>	Poliacrilato
<b>PTFE</b>	Politetrafluoroetilene

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Abietate di metile			↑	→	↓	↗		↓	↓	↓	↓	↓	↑	↓	
Acetaldeide	↓	↗	↓	↓	↓	→	↓	↗	↗	↗	↗	→	↑	↓	
Acetammide	↑	↑	↓	↓	↑	↑	↑	↗	↗	↓	↓	↓	↑	↓	↑
Acetanilide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di alluminio	↗	↑	↓	↓	↗	↗	↓	↓	↑	↓	↑	↗	↑	↓	
Acetato di ammonio	→	↑	→	↓	→	↗	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di benzile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di bornile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acetato di calcio	↗	↑	↓	↗	↗	↗	↓	↓	↑	↓	↑	↓	↑	↓	
Acetato di cellulosa	→	↗	→	↑	→	↓	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di cobalto	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di isoamile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di isobutile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di isopropile	↓	↗	↓	↓	↓	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑
Acetato di manganese	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acetato di metilamile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di metile	↓	↗	↓	↓	↓	↗	↓	↓	↗	↓	↓	↓	↑	↓	
Acetato di nichel	↗	↑	↓	↓	↗	↗	↓	↓	↑	↓	↑	↓	↑	↓	↑
Acetato di ottile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di piombo	↗	↑	↓	↓	↗	↗	↓	↓	↑	↓	↑	↓	↑	↓	↑
Acetato di potassio	↗	↑	↗	↗	↗	↗	↓	↓	↑	↓	↑	↓	↑	↓	↑
Acetato di propile	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	
Acetato di rame	↗	↑	↓	↓	↗	↗	↓	↓	↑	↓	↑	↓	↑	↓	
Acetato di sodio	↗	↑	↓	↓	↗	↗	↓	↓	↑	↓	↑	↓	↑	↓	
Acetato di stronzio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato di terpinyl	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acetato di vinile	↗	↑	→		↗	↗							↑	↑	
Acetato di zinco	↗	↑	↓	↓	↗	↗	↓	↓	↑	↓	↑	↓	↑	↓	↑
Acetato esilico	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Acetato fenilmercurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato ferrico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato mercurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetato perfluorurato di potassio	↗	↑	↓		↗	↗							↑		
Acetilacetone	↓	↑	↓	↓	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	
Acetilene	↑	↑	↑	↓	↑	↗		↗	↑	↗	↗	↗	↑	↓	↑
Acetilene monovilico	↑	↑	↑		↑	↗		↗	↑	↗	↗	↗	↑		
Acetilene tetrabromuro	↓	↑	↑	↓	↓	↗			↑			↓	↑		
Aceto	↗	↑	↗	↓	↗	↗	→	→	↗	↗	↗	↗	↑	↓	
Acetobutirrato di cellulosa	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acetofenetidine	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acetofenone	↓	↑	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acetone	↓	↑	↓	↓	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	↑
Acetone cianidrina	→	↑	→	↓	→	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Acetonitrile	→	↑	↑										↑		
Acetotoluidide	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acidi grassi	↗	→	↑		↗	↗		→	→	↓	↓	↓	↑		↑
Acidi misti	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Acidi, non organici													↑		
Acidi, organici													↑		
Acido abietico													↑		
Acido acetico al 5%	↗	↑	↑	↓	↗	↑	↗	↑	↑	↗	↗	↗	↑	↓	
Acido acetico glaciale	↗	↑	↗	↓	↗	↓	↗	↑	↗	↗	↗	↗	↑	↓	
Acido acetico, al 30%		↑											↑		
Acido acetico, caldo alta pressione	↓	→	↓	↓	↓	↓	↓	→	↓	↓	↓	↓	↑	↓	
Acido acetilsalicilico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido acetoacetico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido aconitico													↑		
Acido acrilico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido adipico	↑	↑	↑	↓	↑	↑							↑	↓	
Acido alcano-solfonico	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Acido alchilonaftalinico solfonico	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Acido alifatico dicarbossilico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido aminobenzoico													↑		
Acido aminosalicilico													↑		
Acido antranilico													↑		
Acido arachico													↑		
Acido arsenico	↑	↑	↑	→	↑	↑	↑	↑	↑	↑	↑	↑	↑	→	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acido ascorbico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido aspartico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido benzensolfonico 10%	↓	↓	↑	↓	↓	↗	↗	↓	↓	↓	↓	↓	↑	↓	
Acido benzilico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido benzoico	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Acido benzoilesuofonico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido bisolfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido borico	↑	↑	↑	↗	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓	
Acido bromico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido bromidrico	↓	↑	↑	↓	↓	↓	→	↓	↑	↓	↑	↑	↑	↓	↑
Acido bromidrico 40%	↓	↑	↑	↓	↓	↗	→	↓	↑	↓	↑	↓	↑	↓	
Acido butilbenzoico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido butirrico	↗	→	↗	↓	↗	→			↗	↓		↓	↑	↓	↑
Acido camforico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido caprico	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Acido caproico	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Acido carbonico	↑	↑	↑	↗	↑	↗	↑	↑	↑	↗	↑	↗	↑	↓	
Acido chaulmoogric													↑		
Acido cianidrico	↗	↑	↑		↗	↗	↗	→	↑	↗	↑	↑	↑	↓	↑
Acido cinnamico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido citrico	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	↑
Acido clorico	↓	↗	↗	↓	↓	↓	↑	↗	↑	↑	↑	↑	↑	↓	↑
Acido cloridrico (anidro)													↑		
Acido cloridrico (caldo) 37%	↓	→	↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Acido cloridrico (freddo) 37%	↓	→	↑			↓							↑		
Acido cloridrico concentrato (a 20 °C)	↗	↗	↑		↗								↑		↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acido cloridrico concentrato (a 70 °C)	↓	↓	↑	↓	↓	↓	↓	↓				↓	↑	↓	↑
Acido cloridrico, 3 moli a 70 °C	↗	↑	↑	↓	↗	↗	→	↓	↑			→	↑	→	
Acido cloroacetico	↓	↗	↓	↓	↓	↓			↗	↓	↓	↓	↑	↓	↑
Acido cloroamino benzoico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido clorosolfonico	↓	→	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	↑
Acido cresilico	↓	↓	↑	↓	↓	↓		↓	↓	↓	↓	↓	↑	↓	
Acido cromatico	↓	↗	↑	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	↑
Acido crotonico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido di tricloruro di fosforo	↓	↑	↑		↓	↓							↑		
Acido dicloroacetico	→	↓	→	→	→	↓	↗		↓	↓	↓	↓	↑	↓	↑
Acido diclorofenossiacetico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido diglicolico	→	↑	↗	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Acido eptanoico	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Acido erucico													↑		
Acido etilacrilico	↓	↗		↓	↓	↗	↓	↓	↗	↓	↓	↓		↓	
Acido etilsulfurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido fenico (fenolo)	↓	↗	↑	→	↓	↓	↑	↓	↗	↓	↓	↓	↑	↓	
Acido fenilacetico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido fenolsolfonico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido fluoridrico (anidro)													↑		↑
Acido fluoridrico (conc.) caldo	↓	↓	↓	↓	↓								↑	↓	
Acido fluoridrico (conc.) freddo	↓	↗	↗	↓	↓	↓							↑	↓	
Acido fluoroborico	↑	↑											↑		
Acido fluorofosforico													↑		
Acido fluorosolfonico													↑		
Acido fluosilicico	↗	↑	↑		↗	↗							↑		↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acido formico	↓	↗	↓	↓	↓	↗							↑	↓	↑
Acido fosforico 3 molare a 70 °C	↑	↑	↑	↓	↑	↗	↗	↗	↑			↗	↑	→	
Acido fosforico concentrato a 20 °C	↗	↑	↑	↓	↗	↗	→	→	↑				↑	↑	↗
Acido fosforico concentrato a 70 °C	↓	↑	↑	↓	↓	→	→	↓	↑			↗	↑	→	
Acido fosforico, 20 %														↑	
Acido fosforico, 45 %	↗	↑	↑	↓	↗	↗								↑	→
Acido ftalico	↗	↑	↗	↓	↗	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑
Acido fumarico	↑	↗	↑		↑	↗	↑	↗	↓	↗	↑	↗	↑	↓	
Acido furoico														↑	
Acido gallico	↑	↗	↑	↓	↑	↗	↑		↗		↑	↗	↑	↓	
Acido glicerofosforico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido glicolico	↑	↑	↗	↓	↑	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑
Acido gliossilico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido gluconico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido glutammico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido idrofluorosilico	↗	↑	↑		↗	↗	↓	↓	↑		↑	↗	↑		
Acido idrossiacetico	↓	↑	↓	↓	↓	↓	↑	↗	↑	↑	↑	↑	↑	↓	
Acido iodico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido iodidrico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido ipocloroso	↓	↗	↑		↓	↓			↗	↓	↗	↓	↑	↓	
Acido isobutirrico	↑	↗	↓		↑	↓		↗						↑	
Acido lattico Dextro	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido lattico, caldo	↓	↓	↑		↓	↓	↗	↗	↓	↓	↓	↓	↓	↑	↑
Acido lattico, freddo	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	↑
Acido laurico	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Acido linoleico	↗	↓	↗	↗	↗			↗	↓	↓	↓	↓	↑		↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acido maleico	↗	↑	↑	→	↗	↗			↓	↓	↓	↓	↑	→	↑
Acido malico	↑	↗	↑	↓	↑	↗	↑	↗	↓	↑	↗	↑	↑	↓	
Acido mandelico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido metacrilico	↓	↗	↓	↓	↓	↓	↑	↗	↑	↑	↑	↑	↑	↓	
Acido metilacrilico	↓	↗	→	↓	↓	↗	↓	↓	↗	↓	↓	↓	↑	↓	
Acido metilsolfonico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido miristico			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Acido molibdico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido monocloroacetico	↓	↑	↓	↓	↓	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Acido naftalenico			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Acido naftenico	↗	↓	↑		↗	↓	↑	↓	↓	↓	↓	↓	↑		
Acido Neville	↓	↗	↑		↓	↓	↗	↓	↗	↓	↓	↓	↑	↓	
Acido nitrico (0 - 50%)	↓	↗	↑										↑		
Acido nitrico (50-100%)	↓	↓	→										↑		
Acido nitrico 3 molare a 70 °C	↓	↗	→	↓	↓	↓	↓	↓	↗			→	↗	↓	
Acido nitrico concentrato a 20 °C		↓	↗										↑		↑
Acido nitrico concentrato a 70 °C	↓	↓	↓	↓	↓	↓	↓	↓				↓	↗	↓	↑
Acido nitrico, bianco fumante													↗		↑
Acido nitrico, rosso fumante	↓	↓	↗		↓	↓							↑		↑
Acido nitrobenzoico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido nitrosilsolfonico													↑		
Acido nitroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido oleico	↗	↓	↑	↗	↗	↓		↓	↓	↓	↓	↓	↑	↓	↑
Acido orthophos													↑		
Acido ossalico	↗	↑	↑		↗	↗	↑	↗	↑	↗	↗	↗	↑		↑
Acido palmitico	↗	→	↑	↗	↗	↗	↑	↓	↗	↗	↗	↗	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acido para-aminobenzoico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido para-aminosalicilico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido para-nitrobenzoico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido pelagonico													↑		
Acido peracetico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Acido perclorico - 2N	↓	↗	↑	↓	↓	↗	↑	↗	↗	↓	↓	↓	↑	↓	
Acido permanganico													↑		
Acido persolfurico (acido di Caro)													↑		
Acido picrico (aq)	↑	↑	↑		↑	↑	↗		↑	↗	↗	↗	↑		↑
Acido picrico fuso	↗	↗	↑		↗	↗	↗	↓	↗	↗	↗	↗	↑		
Acido pirolegnoso	↓	↗	↓	↓	↓	↗	↓		↗	↓	↓	↓	↑	↓	
Acido pirosofurfurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido piruvico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido propionico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido ricinoleico	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido salicilico	↗	↑	↑	↑	↗	↑	↑		↑	↗	↑	↗	↑		↑
Acido sebacico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido selenico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido selenioso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido solfamminico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido solfanilico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido solfonico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido solfonico aminobenzene													↑		
Acido solfonico benzidina 3	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Acido solfonico cloroetano	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Acido solfonico clorotoluene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acido solfonico di piridina	→	↑	→	↓	→	↑	↑	→	↑	↑	↑	↑	↑	↓	
Acido solfonico naftalene			↑	→	↓	→		↓	↓	↓	↓	↑	↓		
Acido solfonico para-toluene	→	↑	→	↓	→	↑	↑	→	↑	↑	↑	↑	↑	↓	
Acido solforico (20% Oleum)	→	↑	→	↓	→	↑	↑	→	↑	↑	↑	↑	↑	↓	
Acido solforico concentrato a 20 °C		→	↑	→								↑		↑	
Acido solforico concentrato a 70 °C	↓	↓	↑	↓		↓	↓	↓				↓	↑	↓	↑
Acido solforico, 3 molare a 70 °C	→	↑	↑	↓	→	→	↑	↑	↑			→	↑	→	
Acido solforoso		→	↑	↓				↓	→	→	→	→	↑	↓	
Acido stearico	→	→	↑	↑	→	→		→	→	→	→	→	↑	↑	↑
Acido succinico	↑	↑	↑	↓	↑	→	↑	→	↑	↑	↑	↑	↑	↓	↑
Acido tannico (10%)	↑	↑	↑		↑	↑	↑	→	↑	↑	↑	→	↑	↓	↑
Acido tartarico	↑	→	↑	↓	↑	→	↑	↑	→	→	↑	↓	↑	↓	↑
Acido tereftalico	→	↑	→	↓	→	↑	↑	→	↑	↑	↑	↑	↑	↓	
Acido tetrafosforico													↑		
Acido tioacetico	→	↑	→	↓	→	↑	↑	→	↑	↑	↑	↑	↑	↓	
Acido tioglicolico	→	↑	→	↓	→	↑	↑	→	↑	↑	↑	↑	↑	↓	
Acido toluensolfonico	→	↑	→	↓	→	↑	↑	→	↑	↑	↑	↑	↑	↓	
Acido tricloroacetico	→	↑	↓	↓	→	↓	↓		→	→	→	→	↑	↓	↑
Acido trifluoroacetico	→	↑	→	↓	→	↑	↑	→	↑	↑	↑	↑	→	↓	
Acido tungstenico													↑		
Acido undecilenico	→	↓	↑	→	→	↓	→		↓	↓	↓	↓	↑	↓	
Acido undecilici	→	↓	↑	→	→	↓	→		↓	↓	↓	↓	↑	↓	
Acido urico	→	↑	→	↓	→	↑	↑	→	↑	↑	↑	↑	↑	↓	
Acido valerico	→	↑	→	↓	→	↑	↑	→	↑	↑	↑	↑	↑	↓	
Acqua	↑	↑	→	↓	→	↑	↑	→	↑	↑	↑	↑	↑	↓	↑
Acqua deionizzata ozonizzata	→	↑	→	↓	→	↑	↑	→	↑	↑	↑	↑	→	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Acqua deionizzata ultrapura (UPDI)	→	↑	→	↓	→	↑	↑	→	↑	↑	↑	↑	↑	↓	
Acqua DI	→	↑	→	↓		↑	↑	→	↑	↑	↑	↑	↑	↓	
Acqua di bromo	↓	→	↑	↓	↓	↓	→	↓	↓	↓	↓	↓	↑	↓	
Acqua di cloro	↓	→	↑	↓	↓	↓							↑	↓	↑
Acqua di mare (salata)	↑	↑	→	→	↑	→	↑	↑	↑	↑	↑	↑	↑	↓	↑
Acqua pesante	↑	↑		↓	↑	→	↑	↑	↑	↑	↑	↑	↑	↓	
Acqua potabile	↑	↑	↑	↓	↑	→	↑	↑	↑	↑	↑	↑	↑	↓	
Acque reflue	↑	↑	↑	↓	↑	→	↑	↑	↑	↑	↑	↑	↑	↓	
Acridina													↑		
Acrilato di butile	↓	↓	↓		↓	↓	↓	→	↓	↓	↓	↓	↑	↓	
Acrilato di etile	↓	→	↓	↓	↓	↓	↓	→	→	↓	↓	↓	↑	↓	↑
Acrilato di metile	↓	→	↓	↓	↓	↓	↓	↓	→	↓	↓	↓	↑	↓	↑
Acronitrile	↓	↓	↓	↓	↓	↓	↓	↓			→	→	↑	↓	↑
Acroleina	→	↑	↓	↓	→	→	↑	→	↑	↑	↑	↑	↑	↓	
Aero Lubriplate	↑	↓	↑	↑	↑	↑	↑	→	↓	↓	↓	→	↑	↑	
Aero Shell 17 grasso	↑	↓	↑	↑	↑	→	↑	→	↓	↓	↓	↓	↑	↑	
Aero Shell 750	→	↓	↑	↓	→	↓	→	↓	↓	↓	↓	↓	↑	→	
Aero Shell 7A grasso	→	↓	↑	↑	→	→	↑	→	↓	↓	↓	↓	↑	↑	
Aero Shell IAC	↑	↓	↑	↑	↑	→	↑	→	↓	↓	↓	↓	↑	↑	
Aerosafe 2300	↓	↑	↓	↓	↓	↓	→	→	→	↓	↓	↓	↑	↓	
Aerosafe 2300W	↓	↑	↓	↓	↓	↓	→	→	→	↓	↓	↓	↑	↓	
Aerozene 50 (50% Idrazina, 50% UDMH)	↓	↑	↓	↓	↓	↓	↓	↓	↑	↓	↓	↓	→		
Alcani (idrocarburi paraffinici)	↑	↓	↑	↑	↑	→	↑	→	↓	↓	↓	↓	↑	↑	
Alcheni (Idrocarburi olefinici)	→	↓	↑	→	→	↓	→		↓	↓	↓	↓	↑	↓	
Alchile acetone	→	↑	→	↓	→	↑	↑	→	↑	↑	↑	↑	↑	↓	
Alchile alcol	↑	↓	↑	↑	↑	→	↑	→	↓	↓	↓	↓	↑	↑	



Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Amminoazobenzene													↑		
Ammoniaca (anidra)	↗	↑	↓	↓	↗	↑	↓	↗	↑	↓	↓	↓	↗	↓	↑
Ammoniaca e litio, metallo in soluzione	↗	↗	↓	↓	↗		↓	↓	↗	↓	↓	↓	↓	↓	
Ammoniaca, gas, caldo	↓	↗	↓	↓	↓	↗	↓		↗	↓	↓	↓	↗	↓	
Ammoniaca, gas, freddo	↑	↑	↓	↓	↑	↑	↓	↑	↑	↑	↑	↑	↑	↓	
Ammoniaca, liquida (anidro)	↗	↑	↓	↓	↗	↑	↓	↗	↑	↓	↓	↓	↗	↓	↑
Ammonio cloruro di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ammonio persolfato 10%	↓	↑		↓	↓	↑			↑		↑	↓		↓	
Ammonio persolfato soluzione	↓	↑		↓	↓				↑		↑	↓	↑	↓	
Ammonio triellina													↑		
AN-O-3 grado M	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
AN-O-366	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
AN-O-6	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
AN-VV-O-366b Fluido idraulico	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
ANDEROL, L - 826 (di estere)	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
ANDEROL, L - 829 (di estere)	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
ANDEROL, L-774 (di estere)	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
ANG-25 (estere Di Base) (TG749)	↗	↓	↑	↓	↗	↓	↗	↗	↓	↓	↓	↓	↑	↗	
ANG-25 (Estere glicerico)	↗	↑	↑	↓	↗	↗	↗	↗	↗	↗	↗	↗	↑	↓	
Anidride acetica	↓	↗	↓	↓	↓	→	↓	↗	↗	↗	↗	↗	↑	↓	↑
Anidride butirrica	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Anidride carbonica (per decompressione esplosiva)	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Anidride ftalica	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Anidride maleica	↓	↓	↗		↓	↓			↗	↓	↓	↓	↑	↓	↑
Anilina	↓	↗	→	↓	↓	↓	→	↓	↗	↓	↓	↓	↑	↓	↑
Anisolo	↓	↓	↓	↓	↓	↓							↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Ansul etere 161 o 181	→	→	↓	↗	→	↓	→	↓	→	↓	↓	↓	↑	↓	
Antigelo prestone	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Antimonato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Antimonato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Antracene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Antrachinone													↑		
Antrachinone disolfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Antranilato di metile			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Aqua Regia	↓	→	↗		→	↓							↗		↑
Argon	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Aria 0-90 °C	↗	↑	↑	↗	↗	↑	↑	↑	↑	↗	↗	↗	↑	↑	↑
Aria 150-200 °C	↓	↓	↑	↓	↓	↓	↗	↑	↓	↓	↓	↓	↑	↓	↑
Aria 200-260 °C	↓	↓	→	↓	↓	↓	↓	↗	↓	↓	↓	↓	↗	↓	↑
Aria 90-150 °C	→	↗	↑	→	→	↗	↑	↑	↗	↓	↓	↓	↑	↗	↑
Aril ortosilicato													↑		
Aroclor 1248	→	↗	↑	↓	→	↓	↗	↗	↗	↓	↓	↓	↑	↓	
Aroclor, 1254	↓	↗	↑	↓	↓	↓	↗	→	↓	↓	↓	↓	↑	↓	
Aroclor, 1260	↑		↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Arsenato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Arsenato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Arsenato di piombo	↑	↑		↗	↑		↑	↗	↑	↑	↑	↑	↑		
Arsenato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Arsenite													↑		
Arsina													↑		
Asfalto	↗	↓	↑	↗	↗	↗	↗	↓	↓	↓	↓	↓	↑	↗	↑
ASTM olio, n. 1	↑	↓	↑	↗	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
ASTM olio, n. 2	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	↑
ASTM olio, n. 3	↑	↓	↑	↗	↑	↓	↑	→	↓	↓	↓	↓	↑	↑	↑
ASTM olio, n. 4	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
ASTM olio, n. 5	↑	↓	↑		↑	↗							↑		
ASTM, Riferimento combustibile A	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	↑
ASTM, Riferimento combustibile B	↑	↓	↑	→	↑	↓	↑	↓	↓	↓	↓	↓	↑	↓	↑
ASTM, Riferimento combustibile C	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
ASTM, Riferimento combustibile D	↗	↓	↑		↗	↓							↑		
ATL-857	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Atlantic Dominion F	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Atlantic Lube Utro Gear-EP	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Atlantic Utro Gear-e	↑	↓	↑		↑	↗							↑		
Aure 903R (Mobil)	↑	↓	↑	↑	↑	↗	↓	↓	↓	↓	↓	↓	↑	↑	
AUREX 256													↑		
AXAREL 9100													↑		
Azobenzene													↑		
Azoto	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Azoturo di piombo													↑		
Bardol B	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Bayol 35	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Bayol D	↑	↓	↑	↓	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Benzaldeide	↓	↗	↓	↓	↓	↓	↗	↑	↓	↓	↓	↓	↑	↓	↑
Benzaldeide acido disolfonico													↑		
Benzamide	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzantrone	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzene	↓	↓	↑	↓	↓	↓	→	↓	↓	↓	↓	↓	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Benzene di vinile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzene esaclorato													↑		
Benzidina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzil butil-ftalato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Benzil fenolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzil salicilato	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzina	↑	↓	↑	↗	↑	↓	↑	↓	↓	↓	↓	↓	↑	↓	↗
Benzina (Ligroin)	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Benzoato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Benzoato di benzile	↓	↓	↑	↓	↓	↓	↑	↓	↗	↓	↓	↓	↑	↓	
Benzoato di butile o benzoato di n-butile	↓	↑	↑		↓	↓	↑		↑	↓	↓	↗	↑	↓	
Benzoato di calcio	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzoato di etile	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Benzoato di metile	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Benzoato di sodio	↑	↑	↑	↓	↑	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑
Benzoato di vinile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzocatecolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzochinone		↗	↑	↓					↗	↓	↓	↓	↑	↓	
Benzocloruro	↓	↑	↑		↓	↓	↑		↗	↓	↓	↓	↑	↓	
Benzofenone		↗	↑	↓			↑		↗	↓	↓	↓	↑	↓	
Benzoino	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Benzotricloruro	↓	↑	↑		↓	↓							↑		
Benzotrifluoruro	↓	↑	↑		↓	↓							↑		
Bicarbonato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bicarbonato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	



Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Bicarbonato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bicarbonato di sodio	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		↑
Bicromato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bicromato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bifluoruro di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bifluoruro di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Biossido di carbonio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Biossido di cloro	↓	→	↑	↓	↓	↓	↗		→	↓	↓	↓	↑	↓	
Biossido di cloro, 8% Cl	↓	↓	↑	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	
Biossido di manganese	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Biossido di piombo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Biossido di titanio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Biossido di zolfo (anidride solforosa), liquefatto	↓	↑	↓		↓	↓	↗	↗	↗	↓	↓	↓	↑	↓	
Biossido di zolfo (anidride solforosa), secco	↓	↑	↓		↓	↓	↗	↗	↗	↗	↗	↗	↑	↓	↑
Biossido di zolfo (anidride solforosa), umido	↓	↑	↓		↓	↗	↗	↗	↑	↓	↓	↓	↑	↓	
Birra	↑	↑	↑	→	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	↑
Bisodio solfito di toluene													↑		
Bisolfato di chinino	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bisolfato di potassio	↑	↑	↑	↓	↑	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑
Bisolfato di sodio o bisolfito	↑	↑	↑		↑	↑	↑	↑	↑	↗	↗	↗	↑	↓	↑
Bisolfato stannoso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bisolfito di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bisolfito di calcio	↗	↑	↗	→	↗	↗	→	→	↑	↓	↓	↗	↑	→	↑
Bisolfito di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bisolfuro di carbonio	↓	↓	↑		↓	↓	↑	↓	↓	↓	↓	↓	↑	→	
Bisolfuro di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Bisulfide di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bitartrato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bitartrato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Borace	↗	↑	↑	↗	↗	↗	↗	↗	↑	↗	↗	↗	↑	↗	
Borato di sodio	↗	↑	↑	↓	↗	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Bordolese	↗	↑	↑	↓	↗	↗	↗	↗	↑	↗	↗	↗	↑	↓	
Borica	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Borneolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Bray GG-130	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Brayco 719-R (VV-H-910)	→	↑	↓	↓	→	↗	↗	↗	↗	↗	↗		↑	↓	
Brayco 885 (MIL-L-6085A)	↗	↓	↑	↑	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Brayco 910	↗	↑	↓	→	↗	↗	↓	↓	↑	↑	↑	↗	↑	→	
Bret 710	↗	↑	↓	→	↗	↗	↓	↓	↑	↑	↑	↗	↑	→	
Brom - 113	→	↓			→	↓		↓	↓			↓			
Brom - 114	↗	↓	↗		↗	↗		↓	↓	↓	↓	↓	↑		
Bromato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bromo	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Bromobenzene	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Bromobenzene cianuro	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bromoclorotrifluoretano (alotano)	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Bromoformio	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Bromometano (bromuro di metile)	↗	↓	↑		↗	↓	↑		↓	↓	↓	↓	↑	→	
Bromopentane	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bromotrifluoroetilene (BFE)														↑	
Bromotrifluorometano (F-13B1)														↗	
Bromuro benzilico	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Bromuro di acetile	↓	↑	↑	↓	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	
Bromuro di alluminio	↑	↑	↑	→	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Bromuro di ammonio	↑	↑	↑	↑	↑	↑			↑			↑	↑		
Bromuro di argento	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bromuro di calcio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Bromuro di cobalto	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Bromuro di etile	↗	↓	↑	↓	↗	↓	↑		↓	↓	↓		↑		
Bromuro di idrogeno (anidro)													↑		
Bromuro di litio (salamoia)	↑	↑	↑	↓	↑	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Bromuro di metile	↓	↓	↑	↓	↓	↓	↑		↓	↓	↓	↓	↑	↓	↑
Bromuro di metilene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Bromuro di piombo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bromuro di potassio	↑	↑	↑	↓	↑	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑
Bromuro di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Bromuro stannoso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Burro-animale grasso	↑	↗	↑	↗	↑	↗	↑	↗	↗	↓	↓	↓	↑	↗	↑
Butadiene (monomero)	↓	↓	↗	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	↑
Butandiolo	↗	↑	→	↓	↗	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑
Butano	↑	↓	↑	↗	↑	↗	→	↓	↓	↓	↓	→	↑	↑	↑
Butano, 2, 2-dimetile	↑	↓	↑	↓	↑	↗	→	↓	↓	↓	↓	→	↑	↑	
Butano, 2, 3-dimetile	↑	↓	↑	↓	↑	↗	→	↓	↓	↓	↓	→	↑	↑	
Butanolo (alcol butilico)	↑	↗	↑	↓	↑	↑	↑	↗	↗	↑	↑	↑	↑	↓	
Butene 2-etil (2-etil 1-Butene)	↑	↓	↑	↓	↑	↓	→	↓	↓	↓	↓	↓	↑	↑	
Butil Acetil Ricinoleato	↗	↑	↑	↓	↗	↗	↗		↑	↓	↓	↓	↑		
Butil etere	↓	→	→	→	→	↓	→	↓	→	↓	↓	↓	↑	↓	
Butil mercaptano (terziario)	5	↓	↓	↓	↓	↓		↓	↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Butil mercaptano terziario	↓	↓	↑		↓								↑		
Butil perossido di-terz													↑		
Butile acetato o acetato di n-butile	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑
Butile ammina o ammina N-butile	↑	→	↓	↓	↑	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Butile benzoato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Butile benzolate													↑		
Butile carbitolo	↓	↑	→		↓	→	↓	↓	↑	↓	↓	↓	↑	↓	
Butile Cellosolve	→	↗	↓	↓	→	→	↓		↗	↓	↓	↓	↑	↓	
Butile Cellosolve acetato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Butile Cellosolve adipato	↓	↗	↗	↓	↓	↓	↗	↗	↗	↓	↓	↓	↑	↓	
Butile glicolato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Butile lattato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Butile oleato	↓	↗	↑		↓	↓	↗		↗	↓		↓	↑		
Butilene	↗	↓	↑	↓	↗	→	↗	↓	↓	↓	↓	↓	↑	↓	↑
Butirolacetone	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Butirraldeide	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑
Butirrato amilico	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Butirrato di butile o butirrato di n-butile	↓	↑	↑		↓	↓	↑		↑	↓	↓	↓	↑	↓	
Caffè	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Calce Bleach	↑	↑	↑		↑	↑							↑		
Calce caustica	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Calcine liquori	↑	↑	↑	↓	↑		↑		↑				↑	↓	
Canfene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Canfora	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	↑
Caprolattame	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Capronaldeide	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	



Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Cianuro di potassio Cupro	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Cianuro di rame	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Cianuro di sodio	↑	↑			↑	↑	↑	↑	↑	↑	↑	↑	↑		
Cianuro di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cianuro mercurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cicloesano	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	↑
Cicloesanolio	↑	↓	↑		↑	↗	↑	↓	↓	↓	↓	↓	↑		↑
Cicloesanone	↓	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓	↑
Cicloesene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cicloesilammina	↓	→	↓	↓	↓	↓	↑	↗	↓	↓	↓	↓	↑	↓	↑
Cicloesilammina carbonato													↑		
Cicloesilammina laurato	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Ciclopentadiene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Ciclopentano	↑	↓	↑	↑	↑	→	↑	↓	↓	↓	↓	↓	↑	↗	
Ciclopoliolefine	↑	↓	↑	↑	↑	→	↑	↓	↓	↓	↓	↓	↑	↗	
Cimene o p-cimene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Citrato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Citrato di litio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Citrato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Citrato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloralio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Clorammina													↑		↑
Clorato di alluminio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Clorato di bario	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Clorato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Clorato di potassio	↓	↑	↑	↓	↓	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Clorato di sodio	↗	↑	↑	↗	↗	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑
Clordano	↗	↓	↑		↗	→	↗	↓	↓	↓	↓	↓	↑		
Cloridrato di anilina	↗	↗	↗	↓	↗	↓	↗	→	↗	↗	↗	→	↑	↓	
Cloridrato di etilene	↓	→	↑	↓	↓	↓	→	↓	→	↓	↓	↓	↑	↓	
Clorido di sodio	↓	↑	↑	↓	↓	↓	↑	↗	↑	↑	↑	↑	↑	↓	
Cloro (bagnato)													↗		↑
Cloro (Plasma)													↗		
Cloro (secco)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	↑
Cloro 1-Nitro Etano (1-cloro-1-Nitro Etano)	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Cloro acetaldeide	↓	↑	↓	↓	↓	↓	↑	↗	↑	↑	↑	↑	↗	↓	
Cloro ossifluoruri													↗		
Cloro xilenoli	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cloroacetato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloroacetil cloruro													↑		
Cloroacetone	↓	↑	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↗	
Cloroanilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloroantrachinone	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Clorobenzaldeide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Clorobenzene	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Clorobenzene (Mono)	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Clorobenzocloruro	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Clorobenzotrifluoruro	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Clorobromo metano	↓	↗	↑	↓	↓	↓	↗	↓	↗	↓	↓	↓	↑	↓	
Clorobromo propano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Clorobutadiene	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Clorobutano (cloruro di butile)	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Clorocarbonato di etile	↓	↗	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Clorododecano	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Cloroestolo	↗	↓	↑	↓	↗	↗	↗	↓	↓	↓	↓	↓	↑	↗	
Cloroetano	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Cloroetilenbenzene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Clorofenolo	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Cloroformiato di etile	↓	↗	↓	↓	↓	↓	↓	↓	→	↓	↓	↓	↑	↓	
Cloroformiato di metile	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Cloroformio	↓	↓	↗	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑
Cloroidrine	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloroidrine di etilene	↓	↗	↓	↓	↓	↗	↗	→	↗	↗	↗	↗	↑	↓	↑
Cloroidrine di propilene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Cloroidrine solforico (Acido clorosolfonico)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloronaftalene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Cloronitrobenzene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloropicrina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cloroprene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Clorosilani													↑		
Clorosilano metilico													↑		
Clorotoluene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Clorotoluidine	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Clorotrifluoroetilene (CTFE)													↗		
Clorox	↗	↗	↑	↓	↗	↗	↑		↗	↓	↓	↓	↑	↓	
Cloroxylolo													↑		
Cloruri di cromile													↑		
Cloruro ceroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Cloruro cromico													↑		
Cloruro d'argento	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di acetile	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Cloruro di alchile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di Allile	↗	↓	↑		↗	↑							↑		
Cloruro di alluminio	↑	↑	↑	→	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Cloruro di ammonio, 2N	↑	↑	↑	↑	↑	↑			↑			↑	↑		
Cloruro di Anisolo													↑		
Cloruro di antimonio	↑	↗	↑	→	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
Cloruro di bario	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Cloruro di benzile	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Cloruro di benzoile			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di berillio	↑	↑	↑	→	↑	→	→	→	↑	→	→	→	↑	→	
Cloruro di bornile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di butile	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Cloruro di butirrato di metile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di butirile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di cadmio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di calcio	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↑	↗	↑
Cloruro di cianogeno													↑		
Cloruro di cianuro													↑		
Cloruro di clorobenzene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di cobalto	↑	↑	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Cloruro di cobalto, 2N	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Cloruro di etile	↓	↗	↗	↓	↓	↗	↑	↓	↓	↗	↑	↓	↑	→	↑
Cloruro di etilene	↓	↗	↗	↓	↓	↗	↗	↓	↓	↓	↓	↓	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Cloruro di idrogeno gas	↓	↑	↑		↓	→							↑		↑
Cloruro di isobutile	↓	↓	↑		↓	↓							↑		
Cloruro di isocrotilo			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di isopropile	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Cloruro di litio	↑	↑	↑	↓	↑	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Cloruro di magnesio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑		↑
Cloruro di manganese	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di mercurio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di metallile			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di metile	↓	↓	↗	↓	↓	↓	↗	↓	→	↓	↓	↓	↑	↓	↑
Cloruro di metilene	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Cloruro di naftalene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di nichel	↑	↑	↑	→	↑	↗	↑	↑	↑	↑	↑	↑	↑	→	↑
Cloruro di nitrosilici													↑		
Cloruro di ottile	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Cloruro di piombo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di piosulfuro	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di potassio	↑	↑	↑	→	↑	↗	↑	↑	↑	↑	↑	↑	↑	→	↑
Cloruro di propilene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di rame	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↑
Cloruro di sodio	↑	↑	↑	↓	↑	↑		↑	↑	↑	↑	↑	↑	↓	↑
Cloruro di stagno	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Cloruro di stagno ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di stronzio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di Surfuryl	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro di tiofosforile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Cloruro di tionile	↓	↗	↑	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	↑
Cloruro di tricloroacetile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di vinile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	↑
Cloruro di vinilidene	↓	↓	↑	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	
Cloruro di zinco	↑	↑	↑		↑	↑	↑		↑	↑	↑	↑	↑	↓	
Cloruro di zolfo	↓	↓	↑	↓	↓	↓	↑	→	↓	↓	↓	↓	↑	↓	↑
Cloruro ferrico	↑	↑	↑	↑	↑	↗	↑	↗	↑	↑	↑	↑	↑	↑	↑
Cloruro ferroso													↑		
Cloruro manganoso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cloruro mercurico	↑	↑	↑		↑	↑			↑	↑	↑	↑	↑		
Cloruro stannoso (15%)	↑	↑	↑		↑	↑	↑	↗	↑	↑	↑	↑	↑		
Cobalto linoleato														↑	
Cobalto naftelato														↑	
Codeina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Colesterolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Colla	↑	↑	↑	↑	↑	↑			↑				↑	↑	↑
Colofonia	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Coloranti all'anilina	↓	↗	↗	↓	↓	↗	↗	→	↗	↗	↗	↗	↑	↓	
Combustibile Jet A	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Convelex 10	↓			↗	↓	↓		↓	↓	↓	↓	↓			
Coolanol 20 25R 35R 40 & 45A (Monsanto)	↑	→	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↓	
Creosoto, catrame di carbone	↑	↓	↑	→	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Creosoto, legno	↑	↓	↑	→	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Cresoli	↓	↓	↗		↓	↓		↓	↓	↓	↓	↓	↑	↓	↑
Cresolo (metil fenolo)			↑										↑		
Cromati di potassio	↗	↑	↑	↓	↗	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Cromato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cromato di piombo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cromato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cromato di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Cromo solfato di potassio (allume)	↗	↗	↑										↑		
Crotonaldeide	↓	↑	↓	→	↓	↓	↗		↓	↓	↓	↓	↓	↑	↑
Cumaldeide	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Cumene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
DDT (diclorodifeniltricloroetano)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Decalin	↓	↓	↑		↓	↓	↑	↓	↓	↓	↓	↓	↑		
Decano (idrocarburo)	↑	↓	↑	↓	↑	↓	↑	↗	↓	↓	↓	↓	↑	↑	
Destrina	↑	↑	↑	↓	↑	↑	↑	↗	↓	↓	↓	↓	↑	↓	↑
Destrosio	↗	↑	↗	→	↗	↑	↑	↗	↑	↑	↑	↑	↑	→	↑
Dexron	↑	↓	↑	↗	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
Dextron	↑	↓	↑		↑	↗							↑		
Diacetato Allilico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Diachetone	↓	↑	↓	→	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	
Diachetone alcol	↓	↑	↓	↓	↓	↗	↓	↓	↑	↓	↓	↓	↑	↓	↑
Dialchil solfati	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Diamilamine	↗	→	↗	↓	↗	→	↑	↗	↓	↓	↓	↓	↑	↓	
Diazinone	→	↓	↗		→	→	↗	↓	↓	↓	↓	↓	↑		
Dibenzile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dibenzile etere	↓	↗	→	↗	↓	↓			↗	↓	↓	↓	↑	→	↑
Dibenzile sebacato	↓	↗	↗	↗	↓	↓	→	→	↗	↓	↓	↓	↑	↓	
Diborano													↑		
Dibromoetano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Dibromoetilen benzene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Dibromuro di etilene	↓	↓	↑	↓	↓	↓	→	↓	→	↓	↓	↓	↑	↓	
Dibutil Cellosolve adipato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Dibutil etere	↓	→	→	↗	↓	↓	→	↓	→	↓	↓	↓	↓	→	↑
Dibutil Metilendio glicolato	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dibutilammina	↓	↓	↓	↓	↓	→	↓	→	↓	↓	↓	↓	↑	↓	
Dibutile sebacato	↓	↗	↗	↓	↓	↓	↗	↗	↗	↓	↓	↓	↑	↓	↑
Dibutile tiourea	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dicloroanilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Diclorobenzene o o-Diclorobenzene	5	↓	↓	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Diclorobenzene o p-Diclorobenzene	5	↓	↓	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Diclorobutano	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Diclorobutene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dicloroetano	→	↓	↗	→	→	↓	↗		↓	↓	↓	↓	↑	↓	↑
Dicloroetano (DDD)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dicloroetilene	→	↓	↗	↓	→	↓	↗		↓	↓	↓	↓	↑	↓	↑
Dicloroexilamina	↓	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓	
Diclorofenolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dicloroidrina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Dicloroisopropilico etere	↓	→	→	↗	↓	↓	→	↓	↓	↓	↓	↓	↑	→	
Diclorometano	→	↓	↗	→	→	↓	↗		↓	↓	↓	↓	↑	↓	↑
Dicloropropano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dicloropropene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Diclorosilano														↑	
Dicloruro di etilene	↓	↓	↑	↓	↓	↓	→	↓	→	↓	↓	↓	↑	↓	
Dicloruro di metile			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Dicloruro di propilene	↓	↓			↓		↗		↓	↓	↓	↓	↑	↓	
Dicromato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Dicromato di potassio	↑	↑	↑	→	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓	↑
Dieldrin	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dietanolammina (DEA)	→	↗	→	↓	→	↓	↑	↗	↑	↑	↑	↑	↑	↓	
Dietil benzene	↓	↓	↑	↓	↓	↓							↑	↓	
Dietil carbonato	→	→	→	↓	→	→	↑	↗	↑	↑	↑	↑	↑	↓	
Dietil ftalato	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dietil sebacato	↓	↗	↗	↓	↓	↓	↗	↗	↗	↓	↓	↓	↑	↓	↑
Dietilammina	↓	↗	↓	↓	↓	→	↑	↗	↑	↑	↑	↑	↑	↓	↑
Dietilanilina	→	↑	→	↓	→	→	↑	↗	↑	↑	↑	↑	↑	↓	
Dietilditiocarbammato di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Dietilentriammina	↓	↑	↓	↓	↓	↓							↑	↓	
Difenilammina (DPA)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Difenile	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Difenile solfonato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Difenilpropano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Difluorodibromometano	↓	↗		↓	↓	↓		↓	↗	↓	↓	↓	↑	↓	
Difluoroetano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Difluoromonocloroetano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Difosfato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Difosfato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Difosfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Diglicole cloroformiato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Diidrogeno fosfato di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Diidrossidifenilsulfone	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Diisobutil carbinolo	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Diisobutil chetone	↓	↑	↓	↓	↓	↓			↑				↑	↓	↑
Diisobutilene	↗	↓	↑	↓	↗	↓	→	↓	↓	↓	↓	↓	↑	↓	
Diisocianato di toluene (TDI)	↓	↗	↓		↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	
Diisooctyl sebacato	→	→	↗	↓	→	↓	→	→	↓	↓	↓	↓	↑	↓	
Diisopropil benzene	↓	↓	↑	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	
Diisopropil chetone	↓	↑	↓	↓	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	
Diisopropil etere (DIPE)														↑	
Diisopropilidene Acetone	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Diluente per vernici, Duco	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Dimetil acetammide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Dimetil fenil carbinolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dimetil fenil metanolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dimetil formaldeide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Dimetil idrazina asimmetrica (UDMH)	↗	↑	↓		↗	↗	↓	↓	↑	↑	↑	↗	↑		
Dimetil tereftalato (DMT)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dimetilammina (DMA)	↓	↗	↓	→	↓	↓	↓	↗	↗	↗	↗	↗	↑	↓	↑
Dimetilanilina (xilidina)	↓	→	→	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	
Dimetildisulfide (DMD)	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Dimetilformammide (DMF)	↗	↗	↓	↓	↗	↓	↓	↗	↗				↑	↓	
Dimetilidrazina	↗	↑	→	↓	↗	↗	↑	↗	↑	↑	↑	↑	↑	↓	
Dimetilsolfossido (DMSO)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Dinitroclorobenzene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dinitrotoluene (DNT)	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Diocetilamine	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Diossano	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑



Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Diossolano	↓	↗	↓	↓	↓	↓	↓	→	↓	↓	↓	↓	↑	↓	
Diottil sebacato	↓	↗	↗	↗	↓	↓	→	→	↗	↓	↓	↓	↓	↑	↑
Dipentene	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Disilane													↑		
Disilicato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Disolfuro di carbonio	↓	↓	↑		↓	↓	↑	↓	↓	↓	↓	↓	↑	→	↑
Dodecilbenzene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Dow Chemical 50-4		↑	↓			↗	↓		↗			↑	↗		
Dow Chemical ET378	↓			↗	↓	↓		↓	↓	↓	↓	↓		→	
Dow Chemical ET588	→	↑	↓		→	↗	↓		↗			↑	↗		
Dow Corning -11	↗	↑	↑	↑	↗	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Dow Corning -200	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning -220	↑	↑	↑		↑	↑							↑		
Dow Corning -3	↗	↑	↑	↑	↗	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Dow Corning -33	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning -4	↗	↑	↑	↑	↗	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Dow Corning -44	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning -5	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning -510	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning -55	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning 1208, 4050, 6620, F-60, XF-60	↑	↑	↑		↑	↑							↑		
Dow Corning F-61	↑	↑	↑		↑	↑							↑		
Dow Corning-1265 fluorosilicone fluido	↗	↑	↑	↑	↗	↑	→	↑	↑	↑	↑	↑	↑	↑	
Dow Corning-550	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning-704	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Corning-705	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Dow Corning-710	↗	↑	↑	↑	↗	↑	↗	→	↑	↑	↑	↑	↑	↑	
Dow Guard	↑	↑	↑	→	↑	↑	↑	↑	↑	↑	↑	↑	↑	→	
Dowanol P Mix													↑		
Dowtherm, 209	→	↑	↓		→	↗	→	→	↗				↑		
Dowtherm, A	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Dowtherm, E	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
DTE 20 serie, Mobil	↗	↓	↑	↑	↗	↑	↗	↓	↓				↑	↗	
DTE denominata serie, Mobil, leggero-pesante	↑	↓	↑	↑	↑	↗	↑	→	↓	↓		↓	↑		
Elio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Emulsione di Acetato polivinilico		↑				↗			↑			↓	↑		
Epicloridrina	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↓	↑	↑
Eptacloro	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Eptaclorobutene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Eptaldeide (Heptanal)	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Eptano o n-eptano	↑	↓	↑	↗	↑	↗	→	↓	↓	↓	↓	↓	↑	↑	↑
Esacloroacetone	→	↑	→	↓	→	→	↑	↗	↑	↑	↑	↑	↑	↓	
Esaclorobutadiene	↓	↓	↑	↗	↓	↓	↗		↓	↓	↓	↓	↑	↓	↑
Esaclorobutene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Esacloroetano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Esacloruro di uranio			↑										↑		
Esaetil tetrafosfato													↑		
Esafluoroetano (F-116)													↗		
Esafluoroxilene													↑		
Esafluoruro di tungsteno													↗		
Esafluoruro di zolfo	↗	↑	↗		↗	↑							↗	↗	↑
Esaldeide o n-Esaldeide	↓	↑	↓	→	↓	↑	↓	↗	↗	↓	↓	↓	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Esametildisilazano													↑		
Esametileno (cicloesano)	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Esametileno Adipato di diammonio	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Esametilendiammina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↗	↓	
Esametilentetrammina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↗	↓	
Esano o n-esano	↑	↓	↑	↗	↑	↗	→	↓	↓	↓	↓	↓	↑	↑	↑
Esene-1 o n-esene-1	↗	↓	↑	↗	↗	↗	↓	↓	↓	↓	↓	↓	↑	↑	↑
Esilresorcinolo	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Esso - Benzina Oro	↗	↓	↑	↓	↗	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Esso - Carburante 208	↑	↓	↑	↓	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Esso - fluido di trasmissione (tipo A)	↑	↓	↑	→	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Esso - Lubrificante XP90-EP	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Esso - Olio motore	↑	↓	↑	↓	↑	→	↑	↓	↓	↓	↓	↓	↑	↑	
Esso - WS2812 (MIL-L-7808A)	↑	↓	↑	↓	↑	↓	↑	↓	↓	↓	↓	↓	↑	↗	
ESSTIC 42, 43	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Etere etile acetato-organico	↓	↗	↓	↓	↓	↓	↓	↗	↗	↓	↓	↓	↑	↓	
Esteri di silicato	↗	↓	↑	↑	↗	↑	↑	↓	↓	↓	↓	↓	↑		
Etano	↑	↓	↑	↗	↑	↗	→	↓	↓	↓	↓	↓	↑	↑	↑
Etano	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Etano	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Etano	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Etere di cellulosa	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Etere di diallile													↑		
Etere di feniletile	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	↑
Etere di isobuttile	↗	↓	↓		↗	→							↑		
Etere dietilico	↓	↓	↓	↗	↓	→	→	↓	↓	↓	↓	↓	↑	→	↑
Etere dimetilico	↓	↗	↓	↗	↓	↓							↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Etere etilico	→	→	↓	↗	→	↓	→	↓	→	↓	↓	↓	↑	↓	
Etere isopropilico	↓		↓	↓	↓	↓	→	↓	↓	↓	↓	↓	↑	↓	↑
Etere para-bromofenilbenzilico													↑		
Eteri	↓	→	↓	↗	↓	↓	→	↓	↓	↓	↓	↓	↑	→	
Etil etere butilico terziario													↑		
Etil mercaptano	↓		↗		↓	→		→	↓	↓	↓	↓	↑		
Etilammina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Etilato di alluminio													↑		
Etilbenzene	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	↑
Etilcellulosa	↗	↗	↓	↓	↗	↗	↓	↗	↗	↗	↗	↗	↑	↓	
Etilciclopentane	↑	↓	↑	↑	↑	→	↑	↓	↓	↓	↓	↓	↑	↗	
Etile Acetato	↓	↗	↓	↓	↓	↓	↓	↗	↗	→	→	→	↑	↓	↑
Etile Cellosolve	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	
Etile cloruro di ammonio													↑		
Etile esanolo	↑	↑	↑	↓	↑	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Etile nitrito	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Etile pentaclorobenzene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Etile piridina	↗	↑	↓	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	
Etile Valerate	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Etilene	↗	↓	↑	↗	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Etilene cianidrina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Etilene diammina	↓	↑	↓	↓	↓	↓	↓	↑	↑	↗	↑	↗	↗	↓	↑
Etileneimine													↑		
Etilmorfolene stannoso octotato (miscela 50/50)	↓	↗	↓		↓				↗				↓	↑	
Etilmorfolina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Etossietile acetato (EGMEEA)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
F-60 fluido (Dow Corning)	↑	↑	↑	↑	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	
F-61 fluido (Dow Corning)	↑	↑	↑	↑	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	
FC-43 eptacosofluorotributilamina	↑	↑	↑		↑	↑	↑	↑				↓	↑		
FC75 & FC77 (fluorocarbone)	↑	↑	↗		↑	↑	↗	↑	↑			↓	↑		
Fenil acetato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fenil acetato di metile			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Fenilacetammide			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Fenilbenzene	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Fenilene diammina													↑		
Feniletile malonico estere *			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Fenilglicerina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fenilidrazina	↓	↓	↗	↓	↓	↓			↓	↗	↑	↗	↑	↓	
Fenilidrazina cloridrato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fenolato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fenolo	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	→	
Fenolo di amile													↑		
Fenolo, 70% / 30% H2O	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Fenolo, 85% / 15% H2O	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Fenolsolfonato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fenolsolfonato di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fenossido di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ferricianuro di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ferricianuro di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ferro ammonio citrato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ferrocianuro di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ferrocianuro ferrico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Fluidi di boro (HEF)	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Fluidi di lavaggio a secco	→	↓	↑	↓	→	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Fluidi di trasmissione automatica (ATF)	↑	↓	↑	↗	↑	↗		↓	↓	↓	↓	↓	↑	↓	↑
Fluido esam-6		↑	↓			↗	↓		↗			↑	↑		
Fluido Freno DOT3 (tipo glicole)	→	↑	↓	↓	→	↗	↓	→	↗			↑	↑	↑	
Fluido per trasmissione tipo A	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	↑
Fluoro (gas)													↗		
Fluoro (liquido)	↓	↓	↗		↓								↗		↑
Fluoro ceroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fluorobenzene	↓	↓	↗		↓	↓	↗		↓	↓	↓	↓	↑	↓	↑
Fluorolube	↑	↑	↗		↑	↑	↗	↑	↑			↓	↑		
Fluorosilicato di alluminio													↑		
Fluorurati eteri ciclici		↑											↑		
Fluoruri cromatico													↑		
Fluoruri di carbonio	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Fluoruro acido di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fluoruro di alluminio	↑	↑	↑	→	↑	↑	↑	↗	↑	↑	↑	↑	↑		
Fluoruro di ammonio	↑	↑	↗	→	↑	↗			↑			↑	↑	↓	
Fluoruro di berillio	↑	↑	↑	→	↑	→	→	→	↑	→	→	→	↑	→	
Fluoruro di calcio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Fluoruro di idrogeno	↓	↗		↓	↓	↓							↑	↓	
Fluoruro di idrogeno (anidro)	↓	↑	↓		↓		↓		↑	↓	↓	↓	↑	↓	
Fluoruro di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Fluoruro di silicio													↑		
Fluoruro di sodio	↑	↑	↑	↗	↑		↑	↗	↑	↑	↑	↑	↑	↓	
Fluoruro di vinile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	





Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Germano (germanio tetraidride)													↑		
Gliceril fosfato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Glicerina (glicerolo)	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	↑
Glicerolo dicloroidrina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Glicerolo monocloroidrina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Glicerolo triacetato	↗	↑	↓	↓	↗	↗	↑	↗	↑	↑	↑	↑	↑	↓	
Glicidolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Glicole dietilenico	↑	↑	↑	↓	↑	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Glicole esilenico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Glicole etilenico	↑	↑	↑	↗	↑	↗	↑	↑	↑	↑	↑	↑	↑	→	↑
Glicole monoetere													↑		
Glicole propilenico	↑	↑	↑	↓	↑	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Glicole trietilenico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Glicoli	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Glucocianate di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Gluconato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Glucosio	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑		↑
Glutammato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Grassi al silicone	↑	↑	↑	↑	↑	↑	↗	→	↑	↑	↑	↑	↑	↑	↑
Grassi animali	↑	↗	↑	↑	↑	↗							↑	↑	
Grasso al bisolfuro di molibdeno	↑	↓	↑			↓							↑		
Grasso Gulfcrown	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Grasso leggero	↑	↓	↑		↑	↓							↑		
Grasso multiuso Sunoco	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Gulf - oli di sicurezza	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Gulf - oli Legion	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Gulf - fluidi FR G	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Gulf - fluidi FR P	↓	↗	↗	↓	↓	↓	↗	↑	↗	↓	↓	↓	↑	↓	
Gulf - FR fluidi (emulsione)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Gulf - Grasso per alte temperature	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Gulf - oli armonici	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Gulf - oli endurance	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Gulf - oli Paramount	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Hannifin Lube A	↑	↓	↑	↑	↑	↑	↑	↗	↓	↓	↓	↗	↑	↑	
HEF-2 (ad alta energia combustibile)	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Hexone (metil isobutil chetone)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
HiLo MS # 1	↓	↑	↓	↓	↓	↓	→	→	↗	↓	↓	↓	↑	↓	
Houghto-Safe 1010 estere fosfato	↓	↑	↑		↓	↓	↗	→	↑	↓	↓	↓	↑	↓	
Houghto-Safe 1055 estere fosfato	↓	↑	↑		↓	↓	↗	→	↑	↓	↓	↓	↑	↓	
Houghto-Safe 1120 estere fosfato	↓	↗	↑	↓	↓	↓	↗	→	↑	↓	↓	↓	↑	↓	
Houghto-Safe 271 (base acqua e glicole)	↑	↑	↗	↓	↑	↗	↗	↗	↗				↑	↑	↓
Houghto-Safe 5040 (emulsione acqua-olio)	↑	↓	↑	↓	↑	↗	↗	→	↓	↓	↓	↓	↑	↓	
Houghto-Safe 620 acqua/glicole	↑	↑	↗	↓	↑	↗	↗	↗	↗				↑	↑	↓
Houghto-Safe serie 416 & 500	↑	↑			↑										
Hydro-Drive MIH-10 (base di petrolio)	↑	↓	↑	↗	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Hydro-Drive MIH-50 (base di petrolio)	↑	↓	↑	↗	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Hydrolube acqua/glicole etilenico	↑	↑	↑	↓	↑	↗	↗	↗	↗				↑	↑	↓
Hydyne	↗	↑	↓		↗	↗	↓	↓	↗	↗	↗	↗	↑	↑	↓
Hyjet	↓	↑	↓		↓	↓							↑		
Hyjet IV e IV bis	↓	↑	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	
Hyjet S4	↓	↑	↓			↓							↑		
Hyjet W	↓	↑	↓		↓	↓							↑		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Idrazide maleica	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Idrazina	↗	↑	→	↓	↗	↗	↓	↗	↑			↗	↑	→	
Idrazina (anidro)	↓	↗	↓	↓	↓	↗	↓		↗	↓	↓	↑	↑	↓	
Idrazina dicloridrato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Idrazina idrato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Idrocarburi saturi	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Idrochinolo	↓	↓	↑		↓	↓							↗		
Idrochinone	↓	↗	↓		↓	↓	↗		↓	↓	↗	↓	↑	↗	↑
Idrogeno solfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Idroperossido di cumene													↑		
Idrosolfito di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Idrosolfuro di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Idrosolfuro di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Idrossido cromico													↑		
Idrossido di alluminio	↗	↑	↗				↗						↑		
Idrossido di ammonio, 3 molare	↑	↑	→	↓	↑	↑	↑	↑	↗	↗	↗	↗	↗	↓	
Idrossido di ammonio, concentrato	↓	↑	↓	↓	↓	↑	↑	↑	↑	→	→	→	↗	↓	
Idrossido di bario	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	↑
Idrossido di calcio	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	↑
Idrossido di litio	↓	↑	→	↓	↓	↓	↑	↗	↑	↑	↑	↑	↑	↓	
Idrossido di magnesio	↗	↑	↑	↓	↗	↗			↑	↗	↗	↗	↑	↓	
Idrossido di potassio 50%	↗	↑	→	↓	↗	↗	→	→	↑	↗	↗	↗	↑	↓	↑
Idrossido di sodio, 3 molare	↗	↑	↗	↗	↗	↗	↗	↑	↑	↑	↑	↗	↑	↓	
Idrossido di stronzio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Idrossido ferrico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Idrosulfito di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Idroxicitronella			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Idruro di boro													↑		
Idruro di calcio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Idruro di sodio													↑		
Immina di propilene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Indolo			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Industron FF44	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Industron FF48	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Industron FF53	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Industron FF80	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Insulina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Iodato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Iodio	↗	↗	↑		↗	↓	↑		↗		↓	↗	↑		↑
Iodoformio		↑	↑			↗			↓	↓	↓	↓	↑		↑
Ioduro d'ammonio	↑	↑	↑	↑	↑	↑			↑			↑	↑		
Ioduro di bario	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Ioduro di idrogeno (anidro)													↑		
Ioduro di metile	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Ioduro di metilene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Ioduro di potassio	↑	↑	↑	↓	↑	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑
Ioduro di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ioduro ferroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ioduro mercurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ipoclorito di calcio	↗	↑	↑	↓	↗	↗	↗	↗	↑	↗	↗	↗	↑	↓	
Ipoclorito di litio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ipoclorito di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Ipoclorito di sodio	↗	↑	↑	↓	↗	↗	↗	↗	↗	↗	↗	↗	↑	↓	↑
Ipofosfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ipofosfito di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ipofosfito di manganese	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ipofosfito di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Iposolfito di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Isoamilico butirrato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Isoamilico Valerate	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Isoboreolo			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Isobutano	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Isobutile n-butilrato	↓	↑	↑		↓	↓	↑		↑	↓	↓	↓	↑	↓	
Isobutilene	↑	↓	↑	↓	↑	↓	↗		↓	↓	↓	↓	↑	↓	
Isobutirraldeide	↓	↑	↓	↓	↓	↓							↗	↓	
Isocianato di metile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Isodecanolo	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Isododecano	↑	↓	↑	↓	↑	↗	↑	↓	↓	↓	↓	↓	↑	↓	
Isoeugenolo	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Isoforone (chetone)	↓	↗	↓	↓	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓	↑
Isoottano	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	↑
Isopentano	↑	↓	↑	↗	↑	↓	↑	↗	↓	↓	↓	↓	↑	↑	
Isopropanolo	↗	↑	↑	↓	↗	↗	↑	↑	↗	↑	↗	↑	↑	↓	↑
Isopropilacetone	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Isopropilamina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
JP-10	→	↓	↑	→	→	↓	↑	↓	↓			↓	↑	↓	
JP-3 (MIL-J-5624)	↑	↓	↑		↑	↓							↑		↑
JP-4 (MIL-T-5624)	↑	↓	↑	↗	↑	↓	↗	↓	↓	↓	↓	↓	↑	↗	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
JP-5 (MIL-T-5624)	↑	↓	↑	↗	↑	↓	↗	↓	↓	↓	↓	↓	↑	↗	↑
JP-6 (MIL-J-25656)	↑	↓	↑	↗	↑	↓	↗	↓	↓	↓	↓	↓	↑	↗	↑
JP-8 (MIL-T-83133)	↑	↓	↑	↑	↑	→	↗	↓	↓			↓	↑	↑	
JP-9 (MIL-F-81912)	→	↓	↑	→	→	↓	↗	↓	↓			↓	↑	↓	
JP-9-11	↓	↓	↑	↓	↓	↓	↗	↓	↓			↓	↑	↓	
JPX (MIL-F-25604)	↑	↓	↓		↑	↗							↑		
Keystone # 87HX (grasso)	↑	↓	↑	↑	↑	↓	↑	↓	↓	↓	↓	↓	↑	↑	
Lacca solventi	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Lacche	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Lardo grasso animale	↑	↗	↑	↑	↑	↗	↑	↗	↗	↓	↓	↓	↑	↑	
Lattami-aminoacidi	↓	↗	↓		↓	↗	↓		↗	↓	↓	↓	↑		
Lattato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Lattato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Lattato di etile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Lattato di metile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Lattato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Latte	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	↑
Lattoni (esteri ciclici)	↓	↗	↓	↓	↓	↓	↓	↗	↗	↓	↓	↓	↑	↓	
Laurato di amile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Laurato di butile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
LB 135	↑	↑	↑		↑	↑							↑		
Lehigh X1169	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Lehigh X1170	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Ligroin (etere di petrolio o benzene)	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Lindol, fluido idraulico (tipo estere di fosfato)	↓	↑	↗	↓	↓	↓	→	→	↑	↓	↓	↓	↑	↓	
Linoleato di alluminio	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	



Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Linoleato di manganese	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Linoleato di piombo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Liquidi di zucchero di barbabietola	↑	↑	↑		↑	↑							↑		
Liquidi Kel F	↑	↑	↗		↑		↗	↑	↑			↑	↑		
Liquido freni auto	→	↑	↓	↓	→	↗	↓	→	↗			↑	↑	↓	↑
Liquido freni Delco	→	↑	↓		→	↗	↓	→	↗			↑	↑		
Liquido freni Girling	→	↑	↓		→	↗	↓		↗			↑	↑		
Liquido freni Mopar	→	↑	↓		→	↗	↓	→	↗			↑	↑		
Liquimoly	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Liquore bianco	↑	↑	↑		↑	↑							↑		↑
Liquore di Bleach	→	↑	↑	↓	→	↗	↗	↗	↑	↗	↗	→	↑	↓	
Liquore di solfato verde	↗	↑	↑	↓	↗	↗	↗		↑	↗	↗	↗	↑	↓	
Liquore nero	↗	↗	↗	↓	↗	↗							→	↓	↑
Liquori di caliche	↑	↑	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Liquori di solfito	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Liquori di zolfo	↗	↗	↑		↗	↗	↗	↓	↗	↗	↗	↗	↑	↓	
Liquori di zucchero di barbabietola	↑	↑	↑	↓	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓	
Liquori di zucchero di canna	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Litopone	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Lube Sinclair opalino CX-EP	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Lubrificante alta viscosità H2	↑	↑	↑	↓	↑	↗	↗	↑	↑	↗		↑	↑	↓	
Lubrificante alta viscosità U4	↑	↑	↑	↓	↑	↗	↗	↑	↑	↗		↑	↑	↓	
Lubrificante di-estere MIL-L-7808	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Lubrificante EP 28 ELCO	↑	↓	↑	↑	↑	→	↑	↗	↓	↓	↓	↓	↑	↑	
Lubrificanti di-estere sintetici	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Malatione	↗	↓	↑		↗		↗	↓	↓	↓	↓	↓	↑		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Manganese gluconato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Manganese naftenato														↑	
Mannitolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
MCS 312	↓	↓	↑		↓	↓	↑	↑	↓	↓	↓	↓	↑	↓	
MCS 352	↓	↑	↓	↓	↓	↓	→	→	↗	↓	↓	↓	↑	↓	
MCS 463	↓	↑	↓	↓	↓	↓	→	→	↗	↓	↓	↓	↑	↓	
MDI (metilene isocianato di p-fenilene)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Mercaptano	↓	↑	↓	↓	↓	↓	↑	↗	↓	↓	↓	↓	↑	↓	
Mercaptano metilico		↑							↑				↑		
Mercaptobenzotiazolo (MBT)			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Mercurio	↑	↑	↑	↑	↑	↑			↑	↑	↑	↑	↑	↑	↑
Meta-cresolo			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Meta-nitroanilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Meta-toluidina			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Metabisolfito di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Metachromate di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Metacrilato di butile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Metacrilato di metile	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	↑
Metafosfato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Metafosfato di sodio	↑	↑	↑		↑	↗	↑		↑	↑	↑	↑	↑		
Metaldeide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Metano	↑	↓	↑	↓	↑	↗	→	↓	↓	↓	↓	↓	↑	↑	↑
Metanolo	↗	↑	↓	↓	↗	↗	↑	↑	↑	↑	↑	↑	↑	↓	↑
Metasilicato di potassio														↑	
Metasilicato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Metil acetofenone *			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Metil butil chetone	↓	↑	↓	↓	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	
Metil butil etere terziario (MTBE)	→	→	→		→	→							↑		
Metil carbonato	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Metil Cellosolve	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	
Metil cellulosa	↗	↗	↗	↗	↗	↗	↓	↗	↗	↗	↗	↗	↑	↓	
Metil cloroformio	↓	↓	↑		↓	↓							↑		
Metil etere	↑	↓	↑		↑	→	↑	↑	↓	↑	↑	↓	↑	↓	
Metil etil chetone (MEK)	↓	↗	↓	↓	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	↑
Metil etil chetone perossido	↓	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↓	↑	↓	
Metil isobutil chetone	↓	↑	↓	↓	↓	↓	↑	↗	↑	↑	↑	↑	↑	↓	
Metil isobutil chetone (MIBK)	↓	→	↓	↓	↓	↓	↓	↓	→	↓	↓	↓	↑	↓	↑
Metil isopropil chetone	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	
Metil Isovalerate			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Metil-2-pirrolidone o n-metil-2-pirrolidone		↗											↑		
Metilal													↑		
Metilammina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Metilato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Metilchetone esilico (2-ottanone)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Metilciclopentano	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Metile acetoacetato	↓	↗	↓	↓	↓	→	↓	↗	↗				↑	↓	
Metile cicloesanone	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Metile cloroacetato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Metile etile oleato			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Metile oleato	↓	↗	↑		↓		↗		↗	↓		↓	↑		
Metile Pentadiene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Metilglicerolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Metilisobutil carbinolo	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Metilpirrolidina			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Metilpirrolidone			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Metossietanolo (DGMA)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Metoxiclor													↑		
MIL-A-6091	↗	↑	↑	↓	↗	↑	↑	↑	↑	↑	↑	↑	↑	↓	
MIL-C-4339	↑	↓	↑	↑	↑	↓	↑	→	↓	↓	↓	↓	↑	↑	
MIL-C-7024	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-C-8188	↗	↓	↗	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	→	
MIL-E-9500	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
MIL-F-16884	↑	↓	↑	→	↑	→	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-F-17111	↑	↓	↑	→	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
MIL-F-25558 (RJ-1)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-F-25656	↑	↓	↑	↗	↑	↓	↗	↓	↓	↓	↓	↓	↑	↗	
MIL-F-5566	↗	↑	↑	↗	↗	↗	↑	↑	↑	↗	↑	↗	↑	↓	
MIL-F-81912 (JP-9)	→	↓	↑	→	→	↓	↗	↓	↓				↓	↑	↓
MIL-F-82522 (RJ-4)	↗	↓	↑	↑	↗	↓	↑	↓	↓	↑	↑	↓	↑	↑	
MIL-G-10924	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-G-15793	↑	↓	↑	↑	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
MIL-G-21568	↑	↑	↑	↑	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	
MIL-G-25013	↑	↑	↑	→	↑	↗	↑	↓	↑	↓	↓	↓	↑	↑	
MIL-G-25537	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-G-25760	↗	↓	↑	↗	↗	↗	↗	↓	↓	↓	↓	↓	↑	↗	
MIL-G-3278	↗	↓	↑	↗	↗	↓	↗	↓	↓	↓	↓	↓	↑	↑	
MIL-G-3545	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-G-4343	↗	→	↑	↑	↗	↗	↑	→	→	↑	↑	↑	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
MIL-G-5572	↑	↓	↑	↗	↑	↓	↑	↓	↓	↓	↓	↓	↑	↓	↗
MIL-G-7118	↗	↓	↑	→	↗	↗	↑	↓	↓	↓	↓	↓	↑	→	
MIL-G-7187	↑	↓	↑	↑	↑	↓	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-G-7421	↗	↓	↑	↗	↗	↗	↗	↓	↓	↓	↓	↓	↑	↓	
MIL-G-7711	↑	↓	↑	↑	↑	↓	↑	↗	↓	↓	↓	↓	↑	↗	
MIL-H-13910	↑	↑	↑	↓	↑	↑	↗	↓	↑	↑	↑	↑	↑	↗	
MIL-H-19457	↓	↗	↑	↓	↓	↓	↓	→	↑	↓	↓	↓	↑	↓	
MIL-H-22251	↗	↑			↗	↗		↓	↑			↗			
MIL-H-27601	↑	↓	↑	→	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
MIL-H-46170 da -25 a +200 °C	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-H-46170 da -30 a +135 °C	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-H-46170 da -50 a +135 °C	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-H-46170 da -55 a +135 °C	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-H-5606 da -54 a +113 °C	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-H-5606 da -54 a +135 °C	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-H-6083	↑	↓	↑	↑	↑	↑	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-H-7083	↑	↑	↗	↓	↑	↗	↑	↑	↑	→	→	↗	↑	↓	
MIL-H-8446 (MLO-8515)	↗	↓	↑	↓	↗	↑	↑	↓	↓	↓	↓	↓	↑	→	
MIL-J-5161	↗	↓	↑	↗	↗	↓	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-L-15016	↑	↓	↑	↑	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
MIL-L-15017	↑	↓	↑	↑	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
MIL-L-17331	↑	↓	↑		↑			↓	↓	↓	↓	↓	↑		
MIL-L-2104	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-L-21260	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-L-23699	↗	↓	↑	→	↗	→	↗	↓	↓	↓	↓	↓	↑	→	
MIL-L-25681	↗	↑	↑	→	↗	↗	↗	↓	↑	↗	↗	↗	↑	↗	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
MIL-L-3150	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-L-6081	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-L-6082	↑	↓	↑	↑	↑	↗	↑	→	↓	↓	↓	↓	↑	↑	
MIL-L-6085	↗	↓	↑	→	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
MIL-L-6387	↗	↓	↑	↑	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
MIL-L-7808	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
MIL-L-7870	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-L-9000	↑	↓	↑	→	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
MIL-L-9236	↗	↓	↑	↗	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
MIL-O-3503	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
MIL-P-27402	↗	↑			↗	↗		↓	↑			↗			
MIL-R-25576 (RP-1)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-S-3136, carburante tipo I	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
MIL-S-3136, carburante tipo II	↗	↓	↑	↗	↗	↓	↗	↓	↓	↓	↓	↓	↑	→	
MIL-S-3136, carburante tipo III	↗	↓	↑	↗	↗	↓	↗	↓	↓	↓	↓	↓	↑	→	
MIL-S-3136, carburante tipo IV, alto assorbimento	↑	↓	↑	↑	↑	↓	↑	↗	↓	↓	↓	↓	↑	↑	
MIL-S-3136, carburante tipo IV, basso assorbimento	↑	↓	↑	↑	↑	↑	↑	→	↓	↓	↓	↓	↑	↑	
MIL-S-3136, carburante tipo V, medio assorbimento	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
MIL-S-81087	↑	↑	↑	↑	↑	↑	↗	→	↑	↑	↑	↑	↑	↑	
MIL-T-5624, JP-4, JP-5	↑	↓	↑	↗	↑	↓	↗	↓	↓	↓	↓	↓	↑	↗	
MIL-T-83133	↑	↓	↑	↑	↑	→	↗	↓	↓			↓	↑	↑	
MLO-7277 idr.	→	↓	↑	→	→	↓	→	↓	↓	↓	↓	↓	↑	→	
MLO-7557	→	↓	↑	→	→	↓	→	↓	↓	↓	↓	↓	↑	→	
MLO-8200 idr.	↗	↓	↑	↑	↗	↑	↗	↓	↓	↓	↓	↓	↑		
MLO-8515	↗	↓	↑	↑	↗	↑	↑	↓	↓	↓	↓	↓	↑	→	
Mobil 24dte	↑	↓	↑		↑	↗							↑		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Mobil 254 lubrificante													↑		
Mobil Delvac 1100, 1110, 1130, 1120	↑	↓	↑		↑	↗							↑		
Mobil HF	↑	↓	↑		↑	↗							↑		
Mobil Nivac 20, 30	↑	↑	↑		↑	↑							↑		
Mobil SHC 500 serie	→	↓	↑	↗	→	↗	↗	↗	↓				↑	↑	
Mobil SHC 600 serie	→	↓	↑	↑	→	↗	↗	→	↓			↓	↑	↑	
Mobil Therm 600	↑	↓	↑		↑	↗							↑		
Mobil Velocite c	↑	↓	↑		↑	↗							↑		
Mobilgas WA200 ATF	↑	↓	↑		↑	↗							↑		
Mobilgear serie 600	→	→	↑	↗	→	↑	↑	↑	→	→	↓	↓	↑	↑	
Mobilgear serie SHC ISO	→	→	↑	↗	→	↗	↑	↑	→	→	↓	↓	↑	↑	
Mobilgrease HP	↗	↓	↑	↑	↗	↗	↑	↗	↓		↓	↓	↑	↑	
Mobilgrease HTS	↗	↓	↑	↑	↗	↗	↑	↗	↓		↓	↓	↑	↑	
Mobilgrease SM	↗	↓	↑	↑	↗	↗	↑	↗	↓		↓	↓	↑	↑	
Mobilith serie AW	↗	↓	↑	↑	↗	↗	↑	↗	↓		↓	↓	↑	↑	
Mobilith serie SHC	↗	↓	↑	↑	↗	→	↑	↗	↓		↓	↓	↑	↑	
Mobiljet II lubrificante													↑		
Mobilmistlube serie	→	→	↑	↗	→	↑	↑	↑	→	→	↓	↓	↑	↑	
Mobiloil SAE 20	↑	↓	↑		↑	↗							↑		
Mobilux	↑	↓	↑		↑	↗							↑		
Molibdenato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Monobromobenzene	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Monobromotoluene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Monoclorobenzene	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Monoclorobutene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Monocloroidrina													↑		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Monocloruro di zolfo	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	↑
Monocromato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Monoetanolamina (MEA)	↓	↗	↓	↓	↓	↓	↓	↗	↗	↗	↗	↗	↑	↓	
Monoetilico ammina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Monoisopropilamina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Monometil anilina	↓	↑	↗	↓		↑	↑	↗	↑	↑	↑	↑	↑	↓	
Monometil etere (etere dimetilico)													↑		
Monometil etere (etere metilico)	↑	↓	↑										↑		
Monometil idrazina	↗	↑			↗	↗		↓	↑			↗	↑		
Monometilamine (MMA)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Monometilanilina	↓	↗	↗	↓	↓	↓			↗	↓	↓	↓	↑	↓	
Mononitrotoluene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Mononitrotoluene & Dinitrotoluene (miscela 40/60)	↓	↑	→	↓	↓	↓	→	↓	↓	↓	↓	↓	↗	↓	
Monossido di carbonio	↑	↑	↗	↑	↑	↗	↗	↑	↑	↗	↗	↗	↑		↑
Mordenzanti ossido													↑		
Morfolina			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	↑
Nafta	↗	↓	↑	↗	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	↗
Naftalene	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑		↑
Naftenato di calcio													↑		
Naftilammina													↑		
Neon	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Nicotina			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Nicotinamide (Niacinamide)			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Nicotinamide cloridrata	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrati cromatico													↑		
Nitrato ceroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Nitrato d'argento	↗	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	↗	↑
Nitrato di alluminio	↑	↑	↑	→	↑	↑		↗	↑	↑	↑	↑	↑	↓	
Nitrato di amile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrato di ammonio solfato	↑	↑	↓		↑	↑			↑	↑	↑	↗	↑	↓	
Nitrato di ammonio, 2N	↑	↑			↑	↑			↑			↑		↗	
Nitrato di bario	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrato di bismuto	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrato di cadmio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrato di calcio	↑	↑	↑	↗	↑	↑	↑	↗	↑	↑	↑	↑	↑	↗	↑
Nitrato di cellulosa *	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrato di dicloroetilammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrato di litio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrato di nichel	↑	↑	↑		↑	↑	↑	↗	↑	↑	↑	↑	↑		
Nitrato di piombo	↑	↑	↑	↓	↑	↗	↑	↗	↑	↑	↑	↑	↑		↑
Nitrato di potassio	↗	↑	↑	→	↗	↗	↑	↑	↑	↑	↑	↑	↑	→	↑
Nitrato di potassio mercurioso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrato di rame	↗	↑	↑	↓	↗	↗							↑	↓	↑
Nitrato di sodio	↗	↑	↑	↓	↗	↗		↓	↑	↑	↑	↗	↑	↓	↑
Nitrato di stronzio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrato di torio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrato di zinco	↑	↑	↑		↑	↑			↑	↑	↑	↑	↑	↓	
Nitrato di zirconio	↑	↑	↑	↓	↑	↑	↑	↑	↑	↗	↗	↗	↑	↓	
Nitrato ferrico	↑	↑	↑	↗	↑	↑	↑	↗	↑	↑	↑	↑	↑	↗	
Nitrato mercurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrito di amile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrito di ammonio	↑	↑			↑	↗		↗	↑	↑	↑	↑	↑		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Nitrito di litio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrito di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitroanilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrobenzene	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑
Nitrocellulosa	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitroclorobenzene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrocloroformio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrodietilanilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrodifenil etero														↑	
Nitroetano	↓	↗	↓	↓	↓	↗	↓	↓	↗	↗	↗	↗	↑	↓	
Nitrofenolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrofluorobenzene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitroglicerina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Nitroglicerolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitroisopropilbenzene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrometano	↓	↗	↓	↓	↓	→	↓	↓	↗	↗	↗	→	↑	↓	↑
Nitropropano	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑
Nitrotiofene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nitrotoluene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Nonano	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Noryl GE fenolico	↑	↑			↑										
Nuovi fluidi in sviluppo	↑	↗	↑		↑	↑	↑	↑	↗	↗	↑	↗	↑		
Nyvac FR200 Mobil	↑	↑	↑		↑	↗			↓	↓		↓	↑		
Octachloro Toluene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↓	↓	
Oleato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Olefine			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Oleum (acido solforico fumante)	↓	↓	↑	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Oleum spiriti	↗	↓	↑	→	↗	→	↗	↓	↓	↓	↓	↓	↑		
Oli di silicone	↑	↑	↑	↑	↑	↑	→	→	↑	↑	↑	↑	↑	↑	↑
Oli fluorocarbonati		↑											↗		↑
Oli idraulici (base sintetica)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Oli lubrificanti (a base di petrolio)	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Oli lubrificanti (base sintetica)			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Oli lubrificanti (Di ester)	↗	↓	↑		↗	→	↗	↓	↓	↓	↓	↓	↑	↗	
Oli lubrificanti (grezzi e raffinati)	↗	↓	↑		↗	→							↑		
Oli lubrificanti SAE 10, 20, 30, 40, 50	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Oli minerali	↑	↓	↑	↑	↑	↗	↑	↗	→	↓	↓	↓	↑	↑	↑
Oli motori	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Oli solfonati	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Olio animale (olio di strutto)	↑	↗	↑	↗	↑	↗	↑	↗	↗	↓	↓	↓	↑	↑	
Olio bianco	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	↑
Olio Bunker	↗	↓	↑	↗	↗	↓	↑	↗	↓	↓	↓	↓	↑	↑	↑
Olio Bunker C (olio combustibile)	↑		↑										↑		
Olio combustibile, # 6	↗	↓	↑	↗	↗	↓	↑	↑	↓	↓	↓	↓	↑	↑	↗
Olio combustibile, 1 e 2	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	↗
Olio combustibile, acido	↑	↓	↑	↗	↑	↗	↑	↑	↓	↓	↓	↓	↑	↑	↗
Olio d'oliva	↑	↓	↑	↑	↑	↗	↑	→	↗	↓	↓	↓	↑	↑	↑
Olio da taglio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Olio del trasformatore	↗	↓	↑	↑	↗	↓	↑	↗	↓	↓	↓	↓	↑	↗	↑
Olio del trasformatore Askarel	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Olio del trasformatore Pyranol	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Olio di anilina	↓	↗	→	↓	↓	↓	→	↓	↗	↓	↓	↓	↗	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Olio di arachidi	↑	↓	↑	↑	↑	↓	↑	↑	→	↓	↓	↓	↑	↑	
Olio di cocco	↑	↓	↑	↑	↑	↗	↑	↑	→	↓	↓	↓	↑	↑	↑
Olio di colza	↗	↓	↑	↗	↗	↗	↑	↓	↑	↓	↓	↓	↑	↗	↑
Olio di fegato di merluzzo	↑	↑	↑	↑	↑	↗	↑	↗	↑	↓	↓	↓	↑	↑	↑
Olio di lavanda	↗	↓	↑	↓	↗	↓							↑	↗	↑
Olio di legno	↑	↓	↑	→	↑	↗	↗	↓	→	↓	↓	↓	↑	↑	
Olio di legno cinese (olio di Tung)	↑	↓	↑	→	↑	↗	↗	↓	→	↓	↓	↓	↑		
Olio di mais	↑	↓	↑	↑	↑	↗	↑	↑	→	↓	↓	↓	↑	↗	↑
Olio di Neatsfoot	↑	↗	↑	↑	↑	↓	↑	↗	↗	↓	↓	↓	↑	↑	
Olio di pesce	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	↑
Olio di petrolio greggio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Olio di petrolio, sopra i 120 ° C	↓	↓	↗	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Olio di petrolio, sotto i 120 ° C	↑	↓	↑	↗	↑	↗	↗	↗	↓	↓	↓	↓	↑	↗	
Olio di pino	↗	↓	↑	↑	↗	↓	↑	↓	↓	↓	↓	↓	↑	↑	↑
Olio di pino bianco	↗	↓	↑		↗	↓	↑	↓	↓	↓	↓	↓	↑		
Olio di piridina	↓	↗	↓		↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	
Olio di ricino	↑	↗	↑	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	
Olio di semi di cotone	↑	↓	↑	↑	↑	↗	↗	↑	→	↓	↓	↓	↑	↑	↑
Olio di semi di lino	↑	→	↑	↗	↑	↗	↑	↑	→	↓	↓	↓	↑	↗	↑
Olio di soia	↑	↓	↑	↗	↑	↗	↑	↑	→	↓	↓	↓	↑	↗	
Olio di Tung (olio di legno della Cina)	↑	↓	↑	→	↑	↗	↗	↓	→	↓	↓	↓	↑		
Olio Halowax	↓	↓	↑		↓	↓	↑	↓	↓	↓	↓	↓	↑		
Olio idraulico (base di petrolio, industriale)	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Olio rosso (MIL-H-5606)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Olio rosso linea 100	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Olio standard Mobilube GX90-EP Lube	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Olio turbina	↑	↓	↑	↑	↑	↓	↑	↓	↓	↓	↓	↓	↑	↑	
Olio turbina #15 (MIL-L-7808A)	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Olio Turbo #35	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Olio vegetale	↑	↓	↑		↑	↗	↑	↑	→	↓	↓	↓	↑	↗	
Oronite 8200	↗	↓	↑	↑	↗	↑	↑	↓	↓	↓	↓	↓	↑		
Oronite 8515	↗	↓	↑	↑	↗	↑	↑	↓	↓	↓	↓	↓	↑		
Orto-cloro etil Benzene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Orto-cloroanilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Orto-clorofenolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Orto-cresolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Orto-diclorobenzene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Orto-Nitrotoluene	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ortosilicato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ortosilicato tetraetile (TEOS)													↑		
OS 45 tipo III (OS45)	↗	↓	↑	↓	↗	↑	↗	↓	↓	↓	↓	↓	↑		
OS 45 tipo IV (OS45-1)	↗	↓	↑	↓	↗	↑	↗	↓	↓	↓	↓	↓	↑		
OS 70	↗	↓	↑	↓	↗	↑	↗	↓	↓	↓	↓	↓	↑		
Ossalato di alluminio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossalato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossalato di butile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossalato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossalato di etile	↓	↗	↑	↑	↓	↓	↗	↓	↓	↓	↑	↓	↑	↓	
Ossalato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossalato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossicloruro di bismuto	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossicloruro di fosforo													↑		↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Ossidi di azoto	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossido cromico	↓	↗	↑		↓	↓							↑		
Ossido di arsenico													↑		
Ossido di bario	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Ossido di berillio	↑	↑	↑	→	↑	→	→	→	↑	→	→	→	↑	→	
Ossido di cadmio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossido di calcio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Ossido di difenile	↓	↓	↑	↓	↓	↓	↗	→	↓	↓	↓	↓	↑	↓	↑
Ossido di difenilene													↑		
Ossido di etilene	↓	↗	↓	↓	↓	↓	↓	↓	→	↓	↓	↓	↑	↓	
Ossido di etilene, (12%) e Freon 12 (80%)	→	↗	↓	↓	→	↓	↓	↓	↗	↓	↓	↓	↗	↓	
Ossido di mesitile (chetone)	↓	↑	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑
Ossido di molibdeno	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossido di piombo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ossido di propilene	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑
Ossido di rame	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Ossido di vanadio	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Ossido di zinco	↑	↑	↑		↑		↑		↑	↑	↑	↑	↑	↓	
Ossigeno liquido	↓	↓	↓		↓	↓							↗		
Ossigeno liquido (LOX)	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↗	↓	
Ossigeno, 150-200 °C	↓	↓	↗	↓	↓	↓	↓	↑	↓	↓	↓	↓	↑	↓	
Ossigeno, 90-150 °C	↓	↓	↗		↓								↑		
Ossigeno, freddo	↗	↑	↑	↑	↗	↑	↑	↑	↑	↗	↗	↗	↑	↗	
Ottadecano	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
Ottanale (n-Octanaldeide)	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Ottano o n-ottano	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Ozono	↓	↑	↑	↑	→	↗	↑	↑	↗	↓	↓	↓	↑	↗	↑
Par-al-chetone	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓		↓	
Para-clorofenolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Para-diclorobenzene	↓	↓	↑	↓	↓		↗	↓	↓	↓	↓	↓	↑	↓	
Para-formaldeide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Para-nitroanilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Para-nitrofenolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Paracimene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Paracresol monobutilettere													↑		
Paraffine	↑	↓	↑	↗	↑	↑	↑	↗	↓	↓	↓	↓	↑	↑	↑
Paraldeide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Paration			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Parker O Lube	↑	↓	↑	↑	↑	↑	↑	↗	↓	↓	↓	↗	↑	↑	
Pectina (liquore)			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	↑
Penicillina (liquido)			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Pentacloroetano			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Pentaclorofenolo	→	↗	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Pentacloruro di antimonio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Pentaeritrite	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Pentafluoroetano (F-125)													↗		
Pentafluoruro di antimonio													↗		
Pentafluoruro di bromo	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↗	↓	
Pentafluoruro di iodio	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↗	↓	
Pentano o n-pentano	↑	↓	↑	↓	↑	↗	→	↓	↓	↓	↓	→	↑	↑	↑
Pentano, 2 metile	↑	↓	↑	↓	↑	↗	→	↓	↓	↓	↓	↓	↑	↑	
Pentano, 3 metile	↑	↓	↑	↓	↑	↗	→	↓	↓	↓	↓	↓	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Pentano, dimetil 2-4	↑	↓	↑	↓	↑	↗	→	↓	↓	↓	↓	↓	↑	↑	
Pentanoato di pentile	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Pentossido di vanadio	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Pentoxone													↑		
Perborato di sodio	↗	↑	↑		↗	↗	↑	↗	↑	↗	↗	↗	↑		
Percarbonato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Perclorato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Perclorato di litio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Perclorato di potassio	↓	↑	↑	↓	↓	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑
Perclorato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Percloroetilene	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Perfluoropropano													↗		
Perfluorotrietilammine													↗		
Permanganato di calcio													↑		
Permanganato di potassio	↓	↑	↑	↗	↓	↗	↑	↗	↑	↑	↑	↑	↑	→	↑
Perossidisolfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Perossidisolfato ferrico	↑	↑	↑		↑	↑							↑		
Perossido di bario	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Perossido di benzoile													↑		
Perossido di calcio													↑		
Perossido di idrogeno	↗	↑	↑		↗	↑	↑	↑	↑	↗	↗	↗	↑	↓	↑
Perossido di idrogeno 90%	↓	→	↑		↓	↓	↗	↗	→	↓	↓	↓	↑	↓	↑
Perossido di potassio													↑		
Perossido di sodio	↗	↑	↑	↓	↗	↗	↑	↓	↑	↗	↗	↗	↑	↓	
Persolfato di potassio	↓	↑	↑	↓	↓	↗	↑	↗	↑	↑	↑	↑	↑	↓	↑
Petrolato	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	



Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Petrolato etere	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Petrolio a base di grasso	↑	↓	↑	↑	↑	→	↑	↓	↓	↓	↓	↓	↑	↑	
Petrolio greggio	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑		↑
Petrolio greggio acido	→	↓	↑	↓	→	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Picrato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Pine Tar	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Pinene	↗	↓	↑	↗	↗	↗	↑	↓	↓	↓	↓	↓	↑	↓	↑
Piombo (fuso)													↑		
Piombo naftenato													↑		
Piombo tetraetile	↗	↓	↑		↗	↓	↗		↓	↓	↓	↓	↑		↑
Piombo tetraetile "Blend"	↗	↓	↑		↗	↓	↗		↓	↓	↓	↓	↑		
Piperazina			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Piperidina	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Piranhia (H2SO4:H2O2) (70:30)													↑		
Piridina	↓	↓	↓	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	↑
Piridina solfonato di calcio													↑		
Pirofosfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Pirogallolo (acido pirogallico)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Pirosulfato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Pirrolo	↓	↓	↓		↓	↓	↓	↗	↓	↗	↗	↗	↑	↓	↑
Plumbite di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Polietilene glicole	↗	↑	→		↗	↗							↑		
Poliglicerina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Poliglicoli	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Polisolfuro di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Polisolfuro di bario	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Potassa caustica	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Potassio (fuso)														↓	
Potassio solfato di alluminio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
PRL - olio idr. per alta Temp	↗	↓	↑	↗	↗	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Produttore di gas	↑	↓	↑	↑	↑	↗	↗	↗	↓	↓	↓	↓	↑	↗	
Propano	↑	↓	↑	↗	↑	↗	↗	↓	↓	↓	↓	↓	↑	↗	↑
Propil nitrato	↓	↗	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	
Propile Acetone o Acetone n-propilico	↓	↑	↓	↓	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	
Propilene	↓	↓	↑	↓	↓	↓	→	↓	↓	↓	↓	↓	↑	↓	
Propionaldeide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Propionato di amile	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Propionato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Propionato di propile	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Propionitrile	↑	↓	↑		↑	↗							↑		
Propylamine	↓	↓	↓	↓	↓	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Propylbenzene			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Protossido di azoto	↑	↑	↑		↑			↑					↑		↑
Punto nero 77	↑	↑	↑	→	↑	→	→	→	↑	→	→	→	↑	→	
Pydraul, 10E	↓	↑	↓	↓	↓	↓	↓	↑	↑	↓	↓	↓	↑	↓	
Pydraul, 115E	↓	↑	↑	↓	↓	↓	→	↓	↑	↓	↓	↓	↑	↓	
Pydraul, 230 C, 312 C, 540 C, A200	↓	↓	↑	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Pydraul, 29ELT 30E, 50E, 65E	↓	↑	↑	↓	↓	↓	↑	↑	↑	↓	↓	↓	↑	↓	
Pydraul, 90e	↓	↑	↑		↓	↓								↑	
Pyrogard 42, 43, 55	↓	↑	↑		↓	↓								↑	
Pyrogard 53, Mobil estere fosfato	↓	↑	↑	↓	↓	↓	↓	↓	↑	↓	↓	↓	↑	↓	
Pyrogard D, emulsione acqua in olio Mobil	↑	↓	↓	↑	↑	↗	↗	→	↓	↓	↓	↓	↑		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Pyrolube	↓	↗	↑	↓	↓	↓	↗	↗	↗	↓	↓	↓	↑	↓	
Quinizarin	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Radiazioni (Gamma, 1.0 E+07 Rads)	→	↗	↓	↓	→		↓	↗	↓				↗		
Raffinato	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Rame acetato di ammonio	↓	↗	↓	↓	↓	→	↑	↗	↑	↑	↑	↑	↑	↓	
Rame gluconato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Rame naftenato													↑		
Reagente di Fisher		↗													
Resine epossidiche		↑	↓			↑			↑				↑		
Resorcinolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Riboflavina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
RJ-1 (MIL-F-25558)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
RJ-4 (MIL-F-82522)	↗	↓	↑	↗	↗	↓	↑	↓	↓			↓	↑	↗	
Rodio													↑		
RP-1 (MIL-R-25576)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Saccarina in soluzione	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Salamoia	↑	↑	↑		↑								↑		
Salamoia (acqua salata)	↑	→	↑		↑	↓							↑		
Sale ammoniaco	↑	↑	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Sale di Glauber	↓	↗	↑	↓	↓	↗	↑		↗	↓	↗	↓	↑	↓	
Sale di Wolmar	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↗	
Sali di alluminio	↑	↑	↑	→	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Sali di ammonio	↑	↑	→		↑	↑	→	↑	↑		↑	↑	↑	→	
Sali di bario	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑
Sali di calcio	↑	↑	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	
Sali di magnesio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Sali di mercurio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Sali di nichel	↑	↑	↑	→	↑	↗	↑	↑	↑	↑	↑	↑	↑	→	
Sali di potassio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Sali di rame	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Sali di sodio	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↑	↑	
Sali di zinco	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Salicilato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Salicilato di litio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Salicilato di metile	↓	↗			↓	↓			↗			→	↑		
Salicilato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Santo Safe 300	↓	→	↑		↓	↓	↑	↑	→	↓	↓	↓	↑	↓	
Sapone in soluzione	↑	↑	↑	↗	↑	↗	↑	↑	↑	↑	↑	↗	↑	↗	↑
Seleniuro di idrogeno													↑		
Servizio Città # 65 # 120 # 250	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Servizio Città AP-Koolmoter olio cambio EP 140 Lube	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Servizio Città Pacemaker # 2	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Sesquisilicate di sodio													↑		
SF 1154 GE Silicone liquido	↗	↑	↑	↗	↗	↑	↑	↓	↑		↑	↑	↑	↑	
SF1147 GE Silicone liquido	↗	→	↑		↗			↓	→				↑		
SF96 GE Silicone liquido	↗	↑	↑	↗	↗	↑	↑	↓	↑	↑	↑	↑	↑	↑	
Shell 3XF fluido per miniera (resis. fuoco)	↑	↓	↑	↓	↑	↗	↑		↓	↓	↓	↓	↑	↓	
Shell Alvania grasso #2	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Shell Carnea 19 e 29	↑	↓	↑	↗	↑	↓	↑		↓	↓	↓	↓	↑	↑	
Shell Diala	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Shell Irus 905	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Shell Lo Hydrax 27 e 29	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Shell Marin 72	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Shell Tellus #32 a base di petrolio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Shell Tellus #68	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Shell Tellus 27 (Base di petrolio)	↑	↓	↑		↑	↗							↑		
Shell Tellus 33	↑	↓	↑		↑	↗							↑		
Shell UMF (5% aromatici)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Shellac	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Silano													↑		
Silicato di calcio	↑	↑	↑		↑	↑			↑	↑	↑	↑	↑		
Silicato di etile	↑	↑	↑		↑	↑	↑		↑	↗	↗	↗	↑		
Silicato di potassio													↑		
Silicato di sodio	↑	↑	↑		↑	↑			↑	↑	↑	↑	↑	↑	↑
Skelly, solvente B, C, E	↑	↓	↑		↑	↓	↑		↓	↓	↓	↓	↑		
Skydrol 500 B4	↓	↑	↓	↓	↓	↓	→	→	↗	↓	↓	↓	↑	↓	
Skydrol 7000	↓	↑	↗	↓	↓	↓							↑	↓	
Skydrol LD-4	↓	↑	↓	↓	↓	↓	→	→	↗	↓	↓	↓	↑	↓	
Socony Mobile tipo A	↑	↓	↑	↗	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
Socony Vacuum AMV AC781 (grasso)	↑	↓	↑	↗	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
Socony Vacuum PD959B	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Soda Ash	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		
Soda caustica (idrossido di sodio)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sodio (fuso)													↓		
Sodio arsenito	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sodio cianamidico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sodio cianato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sodio Diacetato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Sodio etilato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sodio monofosfato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sodio resinato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sodio solfato di alluminio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sodio stannato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sodium Silicofluoride													↑		
Solfanilico cloruro	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Solfato acido di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato acido di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato alluminato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato cromico													↑		
Solfato d'argento	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di alluminio	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↗	↑	↓	
Solfato di ammonio	↑	↑	↓		↑	↑			↑	↑	↑	↗	↑	↓	↑
Solfato di ammonio ferrico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di anilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di antimonio													↑		
Solfato di bario	↑	↑	↑	↑	↑	↑							↑	↑	
Solfato di berillio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di Brucina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di cadmio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di calcio	↑	↑	↑	↑	↑	↑	↗	↑	↑	↑	↑	↑	↑	↓	
Solfato di cerio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di cobalto	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di dietile	↓	↑	↓	↓	↓	↓		↗					↑		
Solfato di etile	↓	↑	↓	↓	↓	↑							↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Solfato di manganese	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di nichel	↑	↑	↑	→	↑	↑	↑	↑	↑	↗	↗	↗	↑	↓	↑
Solfato di nichel ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di nicotina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di piridina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di potassio	↑	↑	↑	→	↑	↗	↑	↑	↑	↑	↗	↗	↑	↓	
Solfato di rame	↑	↑	↑	↑	↑	↑	↑	↑	↗	↗	↗	↗	↑	↓	↑
Solfato di rame 10 %	↑	↑	↑	↗	↑	↑	↑	↑	↗	↗	↗	↗	↑	↓	↑
Solfato di rame 50 %	↑	↑	↑	→	↑	↑	↑	↑	↗	↗	↗	↗	↑	↓	↑
Solfato di sodio	↗	↑	↑	↓	↗	↗	↑	↑	↑	↗	↗	↗	↑	↓	↑
Solfato di titanio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato di zinco	↑	↑	↑	↓	↑	↑	↑	↑	↑	↗	↗	↗	↑	↓	
Solfato e solfito di magnesio	↑	↑	↑		↑	↑	↑	↑	↑	↗	↗	↗	↑	↓	↑
Solfato ferrico	↑	↑	↑		↑	↑							↑		
Solfato ferroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato ferroso di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato manganoso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato mercurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfato rameico	↗	↗	↑										↑		
Solfato stannoso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfito di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfito di anilina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfito di calcio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↗	↗	↗	↑	↓	
Solfito di potassio	↑	↑	↑	→	↑	↑	↑	↑	↑	↑	↗	↗	↑	↓	
Solfito mercurico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfonato fenolico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Solfonilcloruro	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↗	↓	
Solfuro d'idrogeno (secco, caldo)	↓	↑	↓		↓	↗	→	→	↑	↓	↓	↓	↑	↓	↑
Solfuro d'idrogeno (secco, freddo)	↑	↑	↓		↑	↑	→	→	↑	↑	↑	↑	↑	↓	↑
Solfuro d'idrogeno (umido freddo)	↓	↑	↓		↓	↑	→	→	↑	↓	↓	↓	↑	↓	↑
Solfuro d'idrogeno (umido, caldo)	↓	↑	↓		↓	↗	→	→	↑	↓	↓	↓	↑	↓	↑
Solfuro di alchile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Solfuro di ammonio	↗	↑	↓	↓	↗	↗			↑	↑	↑	↗	↑	↓	
Solfuro di bario	↑	↑	↑	↑	↑	↑	↑	↑	↑	↗	↗	↗	↑	↓	
Solfuro di cadmio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfuro di calcio	↑	↑	↑	↑	↑	↑	↑	↑	↑	↗	↗	↗	↑	↓	
Solfuro di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Solfuro di sodio e solfito	↑	↑	↑	↑	↑	↑	↑	↑	↑	↗	↗	↗	↑	↓	↑
Solfuro di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Soluzione decappante	↓	→	↗	↓	↓	↓	↓	↓	→	↓	↓	↓	↑	↓	↑
Soluzione di acqua detergente	↑	↑	↑	↓	↑	↗	↑	↑	↑	↗	↗	↗	↑	↓	↑
Soluzione elettrolitica (Co,Cu, Au,In,Fe,Pb,Ni,Ag,Sn,Zn)	↑	↑	↑		↑								↑		
Soluzioni antigelo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	↑
Soluzioni di Bleach	↓	↑	↑	↓	↓	↓							↑	↓	
Soluzioni di borace	↗	↑	↗	↓	↗	↓							↑	↓	
Soluzioni di liscivia	↗	↑	↗	↓	↗	↗	↗	↗	↑	↗	↗	↗	↑	↓	
Soluzioni di saccarosio	↑	↑	↑	↓	↑	↗	↑	↑	↑	↑	↑	↑	↑	↓	
Soluzioni per cromatura	↓	↗	↑	↓	↓	↓	↗	↗	↗	↓	↓	↓	↑	↓	
Soluzioni per placcatura (altre)	↑	↑	↑		↑	↓		↓	↑			↓	↑		
Soluzioni per placcature di cromo	↓	↗	↑	↓	↓	↓	↗	↗	↗	↓	↓	↓	↑	↓	
Solvente Stoddard	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	↑
Solventi clorurati, secco	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Solventi clorurati, umidi	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Solvesso 100, 150													↑		
Sorbitolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sovasol nr. 1, 2, e 3	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↗	
Sovasol nr. 73 e 74	↗	↓	↑	↗	↗	↗	↑	↓	↓	↓	↓	↓	↑	↗	
Spry	↑	↗	↑	↑	↑	↗	↑	↑	↗	↓	↓	↓	↑	↑	
SR-10 carburante	↑	↓	↑	↗	↑	↓	↑	↓	↓	↓	↓	↓	↑	↗	
SR-6 carburante	↗	↓	↑	↗	↗	↓	↑	↓	↓	↓	↓	↓	↑	↗	
Stannato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Stannic cloruro	↑	↑	↑		↑	↓	↑	↗	↑	↑	↑	↑	↑		
Stannic cloruro, 50%	↑	↑	↑		↑	↓	↑	↗	↑	↑	↑	↑	↑		
Stannico cloruro di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Stauffer 7700	↗	↓	↑		↗	↓	↗	↓	↓	↓	↓	↓	↑	↗	
Stearato di butile	↗	↓	↑	↑	↗	↓	↗		↓	↓	↓	↓	↑		
Stearato di calcio	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Stearato di etile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Stearato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Stearato di zinco	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Stirene (monomero)	↓	↓	↑	↓	↓	↓	→	↓	↓	↓	↓	↓	↓	↓	↑
Sulfamato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sulfamato di calcio	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Sulfamato di piombo	↗	↑	↑		↗	↑	↑	↗	↑	↗	↗	↗	↑	↓	
Sulfanilimide	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Sulfocianide di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Sulfolano	↗	↑	↗		↗	↗							↑		
Sulfonil cloruro di toluene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Sunoco #3661	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Sunoco SAE 10	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
SunSAFE (fluido idraulico resistente al fuoco)	↑	↓	↑	↓	↑	↗	↑		↓	↓	↓	↓	↑	↓	
Swan Finch EP Lube	↑	↓	↑	↑	↑	↓	↑	↓	↓	↓	↓	↓	↑	↑	
Swan Finch Hypoid-90	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Tar, bituminosi	↓	↓	↗	↓	↓	↓	↑	↗	↓	↓	↗	↓	↑	↓	↑
Tarabuso													↑		
Tartrato acido di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tartrato di chinino	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tartrato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tartrato di sodio e potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tartrato ferroso	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tellone II													↑		
Tetra fosfoglicosio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tetraborato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tetrabromoetano	↓	↓	↑		↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Tetrabromometano	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Tetrabromuro di carbonio													↑		
Tetrabutil titanato	↗	↑	↑		↗	↗	↓	↓	↗	↗	↗	↗	↑		
Tetracloroetano	↓	↓	↗	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	↑
Tetracloroetilene	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Tetracloruro di acetilene	↓	↑	↑	↓	↓	↗			↑			↓	↑		
Tetracloruro di carbonio	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Tetracloruro di silicio													↑		
Tetracloruro di stagno	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Tetracloruro di stannico	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Tetracloruro di titanio	↗	↗	↗	↓	↗	↗	↗	↓	↓	↓	↓	↓	↑	↓	↑
Tetrafluoruro di carbonio	↗	↓	↑	↓	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Tetrafluoruro di silicio													↑		
Tetrafluoruro di zolfo													↗		
Tetrafosfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tetraidrofurano	↓	↓	↓	↓	↓	↓	↓	↓	↗	↓	↓	↓	↑	↓	↑
Tetralin	↓	↓	↑		↓	↓	↑	↓	↓	↓	↓	↓	↑		
Tetrametil diidropiridina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Tetrametil idrossido di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tetrametilciclotetrasilossano (TMCTS)													↑		
Tetranitrato di pentaeritrite	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tetrasulfide di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tetrossido di azoto (N2O4)	↓	↓	↓	↓	↓	↓	↓	↓	→	↓	↓	↓	↗	↓	↑
Tetrossido di diazoto													↗		
Texaco - Capella A e AA	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Texaco - grasso Uni-Temp	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Texaco - Meropa 220 (senza piombo)	↑	↓	↑	↗	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Texaco - olio cambio 3450	↑	↓	↑	↑	↑	↓	↑	↓	↓	↓	↓	↓	↑	↑	
Texaco - Regal B	↑	↓	↑	↑	↑	↓	↑	↓	↓	↓	↓	↓	↑	↑	
Texamatic - fluido "A" 1581	↑	↓	↑	↗	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
Texamatic - fluido "A" 3401	↑	↓	↑	↗	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
Texamatic - fluido "A" 3525	↑	↓	↑	↗	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
Texamatic - fluido "A" 3528	↑	↓	↑	↗	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
Texamatic - olio per trasmissioni "A"	↑	↓	↑	↗	↑	↗	↗	↓	↓	↓	↓	↓	↑	↑	
Texas - olio 1500	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Therminol 44	↓	↓	↑		↓	↓		↓	↓				↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Therminol 55	↗	↓	↑		↗	↓		↓	↓				↑	↗	
Therminol 66													↑		
Therminol FR													↑		
Therminol VP-1, 60, 65	↓	↓	↑		↓	↓		↗	↓				↑	↓	
THIO acido di cloruro													↑		
Thiokol TP-90B	↓	↑	↑		↓	↗	↗		↑			↓	↑		
Thiokol TP-95	↓	↑	↑		↓	↗	↗		↑			↓	↑		
Tidewater Multigear, 140 Lube EP	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Tidewater olio-Beedol	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Tioarsenate di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tiocianato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tiocianato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tiocianato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tiocianato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tioetano	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tiofene (Thiofuran)	↓	↓	↓	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	↑
Tioglicolato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tioglicolato di dibutile	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Tiosolfato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tiosolfato di calcio	↗	↑	↑	↑	↗	↑	↑	↑	↑	↗	↗	↗	↑	↓	
Tiosolfato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tiosolfato di sodio	↗	↑	↑	↑	↗	↑	↑	↑	↑	↗	↗	↗	↑	↓	↑
Tiourea	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Toluchinone	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Toluene	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Toluidina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Toluolo	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Torta Niter	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	
Trementina	↑	↓	↑	→	↑	↓	↗	↓	↓	↓	↓	↓	↗	↑	↑
Triacetina	↗	↑	↓	↓	↗	↗	↓		↑	↗	↗	→	↑	↓	↑
Triaril fosfato	↓	↑	↑	↓	↓	↓	↗	→	↑	↓	↓	↓	↑	↓	
Tribromometilbenzene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Tribromuro di antimonio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Tribromuro di boro													↑		
Tributil ammina													↑		
Tributil citrato	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tributil fosfato	↓	↑	↓	↓	↓	↓	↓	↗	↓	↗	↓	↓	↓	↓	↑
Tributil mercaptano	↓	↓	↑		↓	↓	→	↓	↓	↓	↓	↓	↑	↓	
Tributoxyethyl fosfato	↓	↑	↑	↓	↓	↑	↗		↑	↗	↓	↗	↑	↓	↑
Tricloretilene	↓	↓	↗	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	↑
Tricloroacetato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Triclorobenzene	↗		↑	↓	↓	↓	↗		↓	↓	↓	↓	↑	↓	
Tricloroetano	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Tricloroetanoammine	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Triclorometano	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Tricloronitrometano (cloropicrina)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tricloropenilsilano													↑		
Tricloropropano	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Triclorosilano	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Tricloruro di antimonio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Tricloruro di arsenico	↑	↓	↓		↑	↑							↑		
Tricloruro di boro													↑		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Tricloruro di etilene	↓	→	↑	↓	↓	↓	→	↓	→	↓	↓	↓	↑	↓	↑
Tricloruro di fosforo	↓	↑	↑		↓	↓	↑		↑			↓	↑		↑
Tricresil fosfato	↓	↗	↗	↓	↓	↓	↗	→	↑	↓	↓	↗	↑	↓	↑
Trietanolammia ammina		↑		↓		↓			↗	↗	↗	↗	↑	↓	↑
Trietil fosfato	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Trietilalluminio		↓	↗										↑		↑
Trietilborano			↑										↑		↑
Trietilentetrammina	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Trifenil fosfito	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Trifluoroetano	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Trifluorometano	↓	↓	↑	↓	↓	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Trifluorovinilcloruro	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Trifluoruro di antimonio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Trifluoruro di azoto													↗		
Trifluoruro di boro													↑		
Trifluoruro di bromo	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↗	↓
Trifluoruro di cloro	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↗	↓
Trifluoruro di clorobenzene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Trifosfato di potassio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Trifosfato di sodio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Trimetilammia	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Trimetilammia (TMA)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Trimetilbenzene	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Trimetilborate (TMB)	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Trimetilpentano	↑	↓	↑	↑	↑	↗	↑	↗	↓	↓	↓	↓	↑	↑	
Trinitrotoluene (TNT)	↓	↓	↗	↗	↓	↗	↗		↓	↓	↓	↓	↑	↓	↑

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Triossido di antimonio	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Triossido di arsenico	↑	↓	↓		↑	↑							↑		
Triossido di boro													↑		
Triossido di molibdeno	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Triossido di zolfo secco	↓	↗	↑		↓	↓	↗	↗	↗	↗	↗	→	↑	↓	
Triottil fosfato	↓	↑	↗	↓	↓	↓	↗	→	↑	↓	↓	↓	↑	↓	↑
Tripolifosfato	↓	↑	↗	↓	↓	→	↑	→	↑	↓	↓	↓	↑	↓	
Tripropionate di cellulosa	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Trisilicato di magnesio													↑		
Trisopropilbenzencloruro	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
Trisulfide di arsenico	↑	↓	↓		↑	↑							↑		
Tungstato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Tungstato di calcio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Ucon - Hydrolube J-4	↑	↑	↑	↓	↑	↗	↗	↑	↑	↗		↑	↑	↓	
Ucon - lubrificante 50-HB-100	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		
Ucon - lubrificante 50-HB-260	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		
Ucon - lubrificante 50-HB-5100	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		
Ucon - lubrificante 50-HB-660	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		
Ucon - lubrificante 50-HB55	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		
Ucon - lubrificante LB-1145	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		
Ucon - lubrificante LB-135	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		
Ucon - lubrificante LB-285	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		
Ucon - lubrificante LB-300X	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		
Ucon - lubrificante LB-625	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		
Ucon - lubrificante LB-65	↑	↑	↑		↑	↑	↑	↑	↗	↗	↗	↑			
Ucon - olio 50-HB-280x	↗	↑	→		↗	↗							↑		

Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Ucon - olio fluido termovettore 500 (glicole polialcaleno)	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		
Ucon - olio LB-385	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		
Ucon - olio LB-400X	↑	↑	↑		↑	↑	↑	↑	↑	↑	↑	↑	↑		
Univis 40 (fluido idraulico)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Univolt #35 (olio minerale)	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Valeraldeide	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Valerato di ammonio	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Valerato di metile			↑	→		↓	↗		↓	↓	↓	↓	↑	↓	
Vapore sotto i 200 °C	↓	↑	↓	↓	↓	↓	↓	→	↗	↓	↓	↓	↑	↓	
Vapore, 200-260 °C	↓	→	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Vapore, sopra ai 260 °C													↑		
Vapori di mercurio	↑	↑	↑		↑	↑			↑	↑	↑	↑	↑		
Vernice	↗	↓	↑	→	↗	↓	↗	↓	↓	↓	↓	↓	↑	↓	
Versilube F44, F55	↑	↑	↑		↑	↑							↑		
Versilube F50	↑	↑	↑	↑	↑	↑	↑	→	↑	↑	↑	↑	↑	↑	
Vetriolo (bianco)	→	↑	→	↓	→	↑	↑	↗	↑	↑	↑	↑	↑	↓	
Vini e whisky	↑	↑	↑	↓	↑	↑	↑	↑	↑	↑	↑	↑	↑	↓	↑
Vinilpiridina	↗	↓	↑	→	↗	↓	↗		↓	↓	↓	↓	↑	↓	
VV-H-910	→	↑	↑	↓	→	↗	↗	↗	↗	↗	↗	↑	↑	↗	
Wagner 21B (fluido freni)	→	↑	↓		→	↗	↓	→	↗			↑	↑		
Wemco C	↑	↓	↑	↑	↑	↗	↑	↓	↓	↓	↓	↓	↑	↑	
Xenon	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	↑	
Xilene	↓	↓	↗	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	↑
Xilideni misto ammine aromatiche	↓	↗	↓	↓	↓	↓	↓	↓	↓	↓	↓	↓	↑	↓	
Xilolo	↓	↓	↑	↓	↓	↓	↑	↓	↓	↓	↓	↓	↑	↓	
Zeoliti	↑	↑	↑		↑	↑	↑		↑	↑	↑	↑	↑	↑	↑



Fluidi	NBR	EPDM	FKM	TPU	HNBR	CR	FMQ	MQ	IIR	BR	IR	SBR	FFKM	ACM	PTFE
Zinco naftenato													↑		
Zolfo	↓	↑	↑		↓	↑	↑		↑	↓	↓	↓	↑	↓	↑
Zolfo (fuso)	↓	→	↑	↓	↓	→	→	→	→	↓	↓	↓	↑	↓	
Zolfo di calce			↑	→	↓	↗			↓	↓	↓	↓	↑	↓	